



Designation: A1078/A1078M – 22

Standard Specification for Epoxy-Coated Steel Dowels for Concrete Pavement¹

This standard is issued under the fixed designation A1078/A1078M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers plain steel dowel bars with protective fusion-bonded epoxy coating for use in concrete pavements.

1.2 This specification is applicable for orders in either inch-pound units (as Specification A1078) or in SI units (as Specification A1078M).

1.3 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with this specification.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—The coating applicator is identified throughout this specification as the manufacturer.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

A615/A615M [Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement](#)

A775/A775M [Specification for Epoxy-Coated Steel Reinforcing Bars](#)

A934/A934M [Specification for Epoxy-Coated Prefabricated Steel Reinforcing Bars](#)

A1055/A1055M [Specification for Zinc and Epoxy Dual-Coated Steel Reinforcing Bars](#)

D4417 [Test Methods for Field Measurement of Surface Profile of Blast Cleaned Steel](#)

2.2 *Society for Protective Coatings Specifications:*³

SSPC-PA 2 [Measurement of Dry Coating Thickness with Magnetic Gauges](#)

SSPC-SP 10 [Near-White Blast Cleaning](#)

SSPC-VIS 1 [Pictorial Surface Preparation Standards for Painting Steel Surfaces](#)

2.3 *Concrete Reinforcing Steel Institute Documents:*⁴

CRSI [Voluntary Certification Program for Fusion Bonded Epoxy Coating Applicator Plants](#)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *epoxy powder coating, n*—a fusion-bonded epoxy coating product containing pigments, thermosetting epoxy resins, cross-linking agents, and other additives, which is applied in the form of a powder onto a clean, heated metallic substrate and fuses to form a continuous barrier coating.

3.1.2 *final coat, n*—the last application of the Type 1 or Type 2 coating.

3.1.3 *holiday, n*—discontinuity in a coating that is not discernible to a person with normal or corrected vision.

3.1.4 *patching material, n*—liquid two-part epoxy coating used to repair damaged coating and to coat uncoated areas on the surface of a coated bar.

3.1.5 *plain bar, n*—steel bar without protrusions.

3.1.6 *pretreatment, n*—a preparation of the blast-cleaned steel surface prior to coating application that is formulated to pre-treat the metal to promote coating adhesion, reduce metal/coating reactions, improve corrosion resistance, and increase blister resistance.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept. 1, 2022. Published November 2022. Originally approved in 2012. Last previous edition approved in 2019 as A1078/A1078M – 19. DOI: 10.1520/A1078_A1078M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society for Protective Coatings (SSPC), 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656, <http://www.sspc.org>.

⁴ Available from Concrete Reinforcing Steel Institute (CRSI), 933 N. Plum Grove Rd., Schaumburg, IL 60173-4758, <http://www.crsi.org>.

*A Summary of Changes section appears at the end of this standard



3.1.7 *Type 1 coating, n*—epoxy powder coating meeting Annex A1 of Specification **A775/A775M** or Annex A1 of Specification **A1055/A1055M**.

3.1.8 *Type 2 coating, n*—epoxy powder coating meeting Annex A1 of Specification **A934/A934M**.

4. Ordering Information

4.1 Orders for epoxy-coated steel dowels under this specification shall contain the following information:

- 4.1.1 Quantity of dowels,
- 4.1.2 Diameter of dowels (5.3),
- 4.1.3 Type of coating (5.5), and
- 4.1.4 ASTM designation A1078 [A1078M] and year of issue.

4.2 The purchaser shall have the option to specify additional requirements, including but not limited to the following:

- 4.2.1 Requirements for plain bars, if other than ASTM designation A615 [A615M] and year of issue (5.1),
- 4.2.2 Length of dowels, if other than 18 in. [460 mm] (5.4),
- 4.2.3 Grade of steel if other than Grade 60 [420] (5.1),
- 4.2.4 Test report for type of coating used, if desired (5.6),
- 4.2.5 Representative sample of epoxy coating powder (5.10),
- 4.2.6 Test report for review to confirm that the epoxy powder conforms to Annex A1 (5.5),
- 4.2.7 Quantity of patching material (5.11.4),
- 4.2.8 Requirements for patching (7.7),
- 4.2.9 Pretreatment of the abrasive blast-cleaned steel surface, if required (6.5),
- 4.2.10 Cutting of dowels with Type 2 coating, if permitted (7.6),
- 4.2.11 Thickness of coating on dowels, if other than 8 mils [200 µm] (8.1.1),
- 4.2.12 Place of testing, if other than manufacturer's plant (8.2.3),
- 4.2.13 Timing of holiday checks for Type 1 coatings, if other than before cutting (8.2.2),
- 4.2.14 Specific requirements for number of tests and frequency of tests (9.1),
- 4.2.15 Report on results of tests performed on the coated dowels being furnished (8.3.3),
- 4.2.16 Waive the requirement of patching of coated dowels prior to shipment (13.1),
- 4.2.17 Thickness of patching material, if other than as specified in ASTM designation A775 [A775M], A1055 [A1055M], or A934 [A934M] (13.3),
- 4.2.18 Requirements for inspection (12.1),
- 4.2.19 Manufacturer qualification and certification requirements,
- 4.2.20 Other special requirements, if any.

NOTE 2—It is recommended that the coating application procedures and processes be audited by an independent certification program for epoxy coating applicator plants such as that provided by the Concrete Reinforcing Steel Institute, or equivalent.

5. Materials

5.1 Dowels shall consist of plain bars. Unless otherwise specified, the bars shall be Grade 60 [420] and conform to

Specification A615 [Specification A615M]. The bars shall be free of contaminants such as oil, grease, paint or chlorides.

5.2 Incoming bars found to be contaminated shall be rejected.

5.3 Dowels shall be 1¼ in. [32 mm] or 1½ in. [38 mm] in diameter or as specified by the purchaser.

5.4 The coated dowels shall have an overall length of 18 in. [460 mm] or as specified by the purchaser.

5.5 The coating type shall be specified by the purchaser. Type 1 coatings shall be qualified in accordance with Annex A1 of Specification **A775/A775M** or Specification **A1055/A1055M**. Type 2 coatings shall be qualified in accordance with Annex A1 of Specification **A934/A934M**.

5.6 Upon request, the purchaser shall be provided with the test report for coatings used.

5.7 A written certification shall be furnished to the purchaser that properly identifies the designation of each lot of epoxy powder coating used in the order, material quantity represented, date of manufacture, name and address of the epoxy powder coating manufacturer, and a statement that the supplied powder coating is the same composition as that qualified in accordance with 5.5.

5.8 The powder coating shall be stored in a temperature-controlled environment following the documented recommendations of the powder coating manufacturer until ready for use. At this point, if the storage temperature is below the plant ambient temperature, the powder coating shall be given sufficient time to reach a temperature that is within ±5 °F [±2 °C] of the plant ambient temperature.

5.9 The powder coating shall be used within the powder coating manufacturer's written recommended shelf life.

5.10 If specified in the order, a representative 8 oz [0.2 kg] sample of the epoxy powder coating shall be supplied to the purchaser from each batch. The sample shall be packaged in an airtight container and identified by lot number.

5.11 Patching material for repairing damaged coating and for coating uncoated areas shall be inert in concrete, and feasible for repairs at the applicator plant or at the fabricating shop.

5.11.1 The powder coating manufacturer shall specify the approved patching material to be used with their powder.

5.11.2 Patching material shall be approved in accordance with Annex A2 of Specification **A775/A775M** prior to use.

5.11.3 The patching material manufacturer shall specify the method of metal surface preparation, and the procedures for application of the patching material.

5.11.4 If specified in the order, patching material shall be supplied to the purchaser.

6. Surface Preparation

6.1 Blast media found to be salt contaminated from exposure to deicing salt, salt spray or the manufacturing process, shall not be used.

6.2 The surface of the steel to be coated shall be cleaned by abrasive blast-cleaning to near-white metal in accordance with