



Designation: A1094/A1094M – 26

Standard Specification for Continuous Hot-Dip Galvanized Steel Bars for Concrete Reinforcement¹

This standard is issued under the fixed designation A1094/A1094M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers steel reinforcing bars, with protective zinc or zinc-alloy coatings applied by the continuous hot-dip process.

NOTE 1—The galvanizer is identified throughout this specification as the manufacturer.

1.2 Guidelines for construction practices at the job-site are presented in [Appendix X1](#).

1.3 Guidelines for use of continuous hot-dip galvanized reinforcing bars with non-galvanized steel forms are presented in [Appendix X2](#).

1.4 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered requirements of the specification.

1.5 This specification is applicable for orders in either inch-pound units (as Specification A1094) or SI units (as Specification A1094M).

1.6 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with this specification.

1.7 *This specification does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this specification to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

- [A90/A90M Test Method for Weight \[Mass\] of Coating on Iron and Steel Articles with Zinc or Zinc-Alloy Coatings](#)
- [A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement](#)
- [A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement](#)
- [A780/A780M Practice for Repair of Damaged and Uncoated Areas of Hot-Dip Galvanized Coatings](#)
- [A996/A996M Specification for Rail-Steel and Axle-Steel Deformed Bars for Concrete Reinforcement](#)
- [A1035/A1035M Specification for Deformed and Plain, Low-Carbon, Chromium, Steel Bars for Concrete Reinforcement](#)
- [B6 Specification for Zinc](#)
- [B487 Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section](#)
- [B852 Specification for Continuous Galvanizing Grade \(CGG\) Zinc Alloys for Hot-Dip Galvanizing of Sheet Steel](#)
- [E376 Practice for Measuring Coating Thickness by Magnetic-Field or Eddy Current \(Electromagnetic\) Testing Methods](#)

3. Terminology

3.1 Definitions of Terms Specific to This Specification:

3.1.1 *continuous hot-dip galvanizing, n*—the process of uninterrupted passage of long lengths of steel products through a molten bath of zinc or zinc-alloy to produce a metallurgically bonded zinc alloy coating to the steel.

3.1.1.1 *Discussion*—To control alloy formation and promote adhesion and ductility of the metallurgically bonded zinc or

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved April 1, 2026. Published April 2026. Originally approved in 2015. Last previous edition approved in 2020 as A1094/A1094M – 20. DOI: 10.1520/A1094_A1094M-26.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

zinc-alloy coating with the steel base metal, the molten coating metal composition normally contains a percentage of aluminum usually in the range from 0.05 % to 0.25 %. This aluminum is purposely supplied to the molten coating bath, either as a specified ingredient in the zinc spelter or by the addition of a master alloy containing aluminum.

3.1.2 *lot, n*—all bars of one size furnished to the same steel reinforcing bar specification that have been coated within a single production shift.

4. Ordering Information

4.1 Orders for continuous hot-dip galvanized steel bars for concrete reinforcement under this specification shall include the following information:

4.1.1 Specification for reinforcing bars, deformed or plain, to be coated (ASTM designation and year of issue) (5.1),

4.1.2 Quantity of bars,

4.1.3 Size and grade of bars, and

4.1.4 ASTM designation A1094 [A1094M] and year of issue.

4.2 The purchaser shall have the option to specify additional requirements, including but not limited to, the following:

4.2.1 If chromate treatment is waived (6.5),

4.2.2 Requirements for inspection (8.1),

4.2.3 Manufacturer certification and report of test results (10.1), and

4.2.4 Other special requirements, if any.

5. Materials

5.1 The steel reinforcing bars shall conform to one of the following specifications: A615, A706, A996, or A1035 [A615M, A706M, A996M, or A1035M].

5.2 *Coating Bath Metal*—The bath metal used to produce continuous hot-dip galvanized steel bars for concrete reinforcement shall meet the requirements of Specifications B6 or B852.

6. Zinc Coating Process

6.1 The reinforcing bars shall be coated by passing individual bars through a zinc or zinc-alloy flooded trough or tube located above a zinc or zinc-alloy bath, then immediately through an air or steam wiping device to remove excess coating from the bars.

NOTE 2—During the wiping process, care should be taken to maintain a uniformly thick coating around the perimeter of the bar.

6.2 It shall be the responsibility of the manufacturer to maintain identity of the reinforcing bars throughout the coating process and to the point of shipment.

6.3 Thickness of Coating:

6.3.1 The average thickness of zinc or zinc-alloy coating for all specimens tested shall not be less than specified in Table 1.

6.4 Coating Thickness Tests:

6.4.1 Coating thickness tests shall be performed in accordance with one of the following test methods:

6.4.1.1 *Magnetic Thickness Gauge Measurements*—The thickness of the coating shall be determined by magnetic thickness gauge measurements in accordance with Practice E376, or

6.4.1.2 *Microscopy*—The thickness of the coating shall be determined by cross-sectional and optical measurement in accordance with Test Method B487. A cross-section sample of the coated steel shall be polished and examined with an optical microscope to determine the coating thickness. Measurements of thickness shall not be taken on points located on ribs or deformations, or

6.4.1.3 *Stripping Method*—The thickness of the coating shall be determined by stripping the coating from a reinforcing bar in accordance with Test Method A90/A90M. This test method shall not be used for deformed steel reinforcing bars.

NOTE 3—Due to variations in the surface areas of deformed bars as a function of deformation pattern and bar size, this method to measure coating thickness is not appropriate for deformed bars. This is a destructive test for small samples of plain bars with a minimum of 3 in.² [2000 mm²] of surface area,

6.4.2 The referee method to be used shall be Test Method B487.

6.4.3 *Number of Tests*—For determination of the coating thickness using the magnetic method, three random samples shall be tested from each lot. For each magnetic thickness gauge measurement sample, five or more measurements shall be made at various points throughout the sample so as to represent the entire surface of the sample. A total of at least fifteen measurements shall be averaged to obtain the coating thickness. For the microscopy method, five samples shall be tested per lot. Each sample shall be measured on four sides and the total of twenty measurements shall be averaged to obtain the coating thickness. For the stripping method, three samples per lot shall be tested.

6.4.4 *Retests*—If the average zinc coating thickness fails to meet the requirements of Table 1, six additional random samples from the lot shall be tested. If the average zinc coating thickness of the six samples conforms to the requirements of Table 1, the lot shall be accepted.

6.5 *Chromating*—The zinc coating shall be chromate treated unless waived by the purchaser.

NOTE 4—The purpose of chromate treatment is to preclude a reaction between the bars and fresh portland cement paste.

6.5.1 If the chromate treatment is performed immediately after zinc or zinc-alloy coating, it shall be accomplished by quenching the steel reinforcing bars in a solution containing at least 0.2 weight [mass] % of pure sodium dichromate in water (such as 3 oz/10 gal [2 kg/m³] of quench water) or by quench chromating in a minimum of 0.2 % chromic acid solution. The solution shall be at least 90 °F [32 °C]. The zinc or zinc-alloy coated reinforcing bars shall be immersed in the solution for at least 20 s.

TABLE 1 Minimum Average Coating Thickness Grade and Equivalent Weight [Mass]^A

Coating Grade	μm	mils	oz/ft ²	g/m ²	mg/cm ²
50	50	2.0	1.2	360	36

^A The value in micrometres (μm) is based on the Coating Grade. The other values are based on conventions using the following formulae: mils = μm × 0.03937; oz/ft² = μm × 0.0232; g/m² = μm × 7.14; and mg/cm² = μm × 0.714.