



Designation: A1110/A1110M – 21

Standard Specification for Cold-Formed Welded and Seamless Carbon Steel Structural Tubing in Rounds and Shapes with 52 KSI [360 MPa] Minimum Yield Strength and Impact Requirements¹

This standard is issued under the fixed designation A1110/A1110M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers cold-formed welded and seamless carbon steel round, square, rectangular, or special shape structural tubing for welded, riveted, or bolted construction of bridges and buildings, and for general structural purposes where impact properties are required.

1.2 This tubing is produced in both welded and seamless sizes with a periphery of 88 in. [2235 mm] or less, and a specified wall thickness from 0.148 in. [4 mm] up to 0.875 in. [22 mm].

1.3 The welded and seamless tubing can be supplied in two different grades each with a specified impact test temperature. Different strength levels, CVN acceptance criteria, and impact test temperatures than listed may be available. To determine their availability, the purchaser should contact the producer (see 4.1.4 and 4.1.13).

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.5 The text of this specification contains notes and footnotes that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved Sept. 1, 2021. Published September 2021. Originally approved in 2018. Last previous edition approved in 2018 as A1110/A1110M – 18. DOI: 10.1520/A1110_A1110M-21.

1.7 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A751 Test Methods and Practices for Chemical Analysis of Steel Products

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A1058 Test Methods for Mechanical Testing of Steel Products—Metric

2.2 Military Standards:

MIL-STD-129 Marking for Shipment and Storage³

2.3 Federal Standards:

Fed. Std. No. 123 Marking for Shipment³

2.4 AIAG Standard:

B-1 Bar Code Symbology Standard⁴

2.5 Steel Tube Institute Standard:⁵

Methods to Check Dimensional Tolerances on Hollow Structural Sections

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology A941.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁴ Available from Automotive Industry Action Group (AIAG), 26200 Lahser Rd., Suite 200, Southfield, MI 48033-7156, <http://www.aiag.org>.

⁵ Available from the Steel Tube Institute (STI), 2516 Waukegan Rd., STE 172, Glenview, IL 60025-1774, <https://steeltubeinstitute.org>.

*A Summary of Changes section appears at the end of this standard

4. Ordering Information

4.1 Orders for material under this specification shall contain information concerning as many of the following items as are required to describe the desired material adequately:

- 4.1.1 Quantity (feet [metres] or number of lengths),
- 4.1.2 Name of material (cold-formed tubing),
- 4.1.3 Method of manufacture (seamless or welded),
- 4.1.4 Grade (A or B) and Test Temperature (1 or 2), or other tensile strength, CVN acceptance criteria, and test temperature,
- 4.1.5 Size (outside diameter and wall thickness for round tubing, and outside dimensions and wall thickness for square and rectangular tubing),
- 4.1.6 Copper-containing steel (see [Table 1](#)), if applicable,
- 4.1.7 Length (random, multiple, specific; see [11.3](#)),
- 4.1.8 End condition (see [16.3](#)),
- 4.1.9 Burr removal (see [16.3](#)),
- 4.1.10 Certification (see [Section 18](#)),
- 4.1.11 ASTM specification designation and year of issue,
- 4.1.12 End use,
- 4.1.13 Special requirements, including flare testing on round tubing or other destructive weld tests to be conducted in lieu of or in addition to those specified, and
- 4.1.14 Bar coding (see [19.3](#)).

5. Process

5.1 The steel shall be made by one or more of the following processes: basic-oxygen or electric-furnace.

5.2 When steels of different grades are sequentially strand cast, the steel producer shall identify the resultant transition material and remove it using an established procedure that positively separates the grades.

6. Manufacture

6.1 The tubing shall be made by a seamless or welding process.

6.2 Welded tubing shall be made from flat-rolled steel by the electric-resistance-welding process. The longitudinal butt joint of welded tubing shall be welded across its thickness in such a manner that the structural design strength of the tubing section is assured.

6.3 The weld shall not be located within the radius of the corners of any shaped tube unless specified by the purchaser.

NOTE 1—Welded tubing is normally furnished without removal of the inside flash.

7. Heat Analysis

7.1 Each heat analysis shall conform to the requirements specified in [Table 1](#) for heat analysis.

8. Product Analysis

8.1 The tubing shall be capable of conforming to the requirements specified in [Table 1](#) for product analysis.

8.2 If product analyses are made, they shall be made using test specimens taken from two lengths of tubing from each lot of 500 lengths, or fraction thereof, or two pieces of flat-rolled stock from each lot of a corresponding quantity of flat-rolled stock. Methods and practices relating to chemical analysis shall be in accordance with Test Methods, Practices, and Terminology [A751](#). Such product analyses shall conform to the requirements specified in [Table 1](#) for product analysis.

8.3 If both product analyses representing a lot fail to conform to the specified requirements, the lot shall be rejected.

8.4 If only one product analysis representing a lot fails to conform to the specified requirements, product analyses shall be made using two additional test specimens taken from the lot. Both additional product analyses shall conform to the specified requirements or the lot shall be rejected.

9. Tensile and Charpy Requirements

9.1 The material, as represented by the test specimen or specimens, shall conform to the requirements as to tensile and CVN properties prescribed in [Table 2](#).

9.2 CVN Impact Tests are required for Grades A and B. The customer may select either test temperature with either grade listed in [Table 2](#). The customer may also request a different test temperature and CVN acceptance criteria than listed in [Table 2](#). If a temperature is not specified, then Temperature 1 is the default. The acceptance criteria for sub sized specimens shall be proportional to that of a full size bar in accordance with Test Methods and Definitions [A370](#) or Test Methods [A1058](#).

10. Flattening and Flaring Tests

10.1 The flattening test shall be made on round structural tubing. A flaring test on round tubing up to and including 10 in.

TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A, and B ^C	
	Heat Analysis	Product Analysis
Carbon, max ^A	0.26	0.30
Manganese, max ^A	1.35	1.40
Phosphorus, max	0.035	0.045
Sulfur, max	0.035	0.045
Copper, min ^B	0.20	0.18

^A For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage point above the specified maximum for manganese is permitted, up to a maximum of 1.50 % by heat analysis and 1.60 % by product analysis.

^B If copper-containing steel is specified in the purchase order.

^C Additional alloying elements such as Columbium, Vanadium, Titanium, or others may be added at the manufacturer's discretion to meet the tensile and CVN requirements. These additional elements shall be reported.

TABLE 2 Tensile and Charpy Requirements

	Round and Shaped Structural Tubing	
	Grade A	Grade B
Tensile strength, min, psi [MPa]	65 000 [450]	70 000 [480]
Yield strength, min, psi [MPa]	52 000 [360]	57 000 [393]
Elongation in 2 in. [50 mm], min, % ^A	19	17
Test Temperature, °F [°C]	–20 [–29]	–40 [–40]
CVN Minimum Average Impact ft-lbs [J]	25 [34]	25 [34]
based on a set of 3 full sized specimens ^B		

^A The minimum elongation values specified apply only to tests performed prior to shipment of the tubing.

^B See Test Methods and Definitions [A370](#) or Test Methods [A1058](#) for acceptance criteria for sub size specimens.