



Designation: A209/A209M – 03 (Reapproved 2022)

Standard Specification for Seamless Carbon-Molybdenum Alloy-Steel Boiler and Superheater Tubes¹

This standard is issued under the fixed designation A209/A209M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers several grades of minimum-wall-thickness, seamless, carbon-molybdenum alloy-steel, boiler and superheater tubes.

1.2 This specification covers tubes $\frac{1}{2}$ to 5 in. [12.7 to 127 mm] inclusive, in outside diameter and 0.035 to 0.500 in. [0.9 to 12.7 mm], inclusive, in minimum wall thickness.

1.3 An optional supplementary requirement is provided and, when desired, shall be so stated in the order.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved March 1, 2022. Published March 2022. Originally approved in 1938. Last previous edition approved in 2017 as A209/A209M – 03 (2017). DOI: 10.1520/A0209_A0209M-03R22.

² For ASME Boiler and Pressure Vessel Code application see related Specification SA-209 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. General Requirements

3.1 Product furnished under this specification shall conform to the requirements of Specification **A1016/A1016M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A1016/A1016M** constitutes nonconformance with this specification. In case of conflict with the requirements of this specification and Specification **A1016/A1016M**, this specification shall prevail.

4. Materials and Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed.

4.2 The tubes shall be made by the seamless process and shall be either hot-finished or cold-finished, as specified.

4.3 *Heat Treatment*—Hot-finished tubes shall be heat treated at a temperature of 1200 °F [650 °C] or higher. Cold-finished tubes shall, after the final cold finishing, be heat treated at a temperature of 1200 °F [650 °C] or higher, or tubing may be furnished in the full-annealed, isothermal annealed, or normalized and tempered condition. If furnished in the normalized and tempered condition, the minimum tempering temperature shall be 1200 °F [650 °C].

5. Chemical Composition

5.1 The steel shall conform to the requirements given in **Table 1**.

5.2 *Product Analysis*

5.2.1 An analysis shall be made by the manufacturer of one billet or one tube from each heat. The chemical composition thus determined, shall conform to the requirements given in **Table 1**.

5.2.2 If the original test for product analysis fails, retests of two additional billets or tubes shall be made. Both retests for the elements in question shall meet the requirements of the specification; otherwise all remaining material in the heat or lot (See **7.1**) shall be rejected or, at the option of the producer, each billet or tube may be individually tested for acceptance. Billets or tubes that do not meet the requirements of the specification shall be rejected.