



Designation: A447/A447M – 11 (Reapproved 2021)

Standard Specification for Steel Castings, Chromium-Nickel-Iron Alloy (25-12 Class), for High-Temperature Service¹

This standard is issued under the fixed designation A447/A447M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers iron-base, heat-resisting alloy castings of the 25 % chromium, 12 % nickel class, intended for structural elements, containers, and supports in electric furnaces, petroleum still tube supports, and for similar applications up to 2000 °F [1095 °C].

1.2 In the absence of significant proportions of elements other than those prescribed in Section 5, the two types of alloys covered by this specification may in general be distinguished as follows:

1.2.1 *Type I*—Alloys characterized by relatively low limiting creep stress at temperatures between 1500 and 2000 °F [815 and 1095 °C], and relatively high ductility at ordinary temperatures after aging for short periods at temperatures between 1300 and 1500 °F [705 and 815 °C].

1.2.2 *Type II*—Alloys having relatively high limiting creep stress but which may develop low ductility at ordinary temperatures when aged for short periods at temperatures between 1350 and 1500 °F [730 and 815 °C].

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3.1 Within the text, the SI units are shown in brackets.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved May 1, 2021. Published May 2021. Originally approved in 1944. Last previous edition approved in 2016 as A447/A447M – 11 (2016). DOI: 10.1520/A0447_A0447M-11R21.

2. Referenced Documents

2.1 ASTM Standards:²

A781/A781M Specification for Castings, Steel and Alloy, Common Requirements, for General Industrial Use

A800/A800M Practice for Estimating Ferrite Content of Stainless Steel Castings Containing Both Ferrite and Austenite

A957/A957M Specification for Investment Castings, Steel and Alloy, Common Requirements, for General Industrial Use

A1067/A1067M Specification for Test Coupons for Steel Castings

E8/E8M Test Methods for Tension Testing of Metallic Materials

E21 Test Methods for Elevated Temperature Tension Tests of Metallic Materials

3. General Conditions for Delivery

3.1 Except for investment castings, material furnished to this specification shall conform to the requirements of Specification A781/A781M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A781/A781M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A781/A781M, this specification shall prevail.

3.2 Investment castings furnished to this specification shall conform to the requirements of Specification A957/A957M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A957/A957M constitutes nonconformance with this specification. In the case of conflict between the requirements of this specification and Specification A957/A957M, Specification A957/A957M shall prevail.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Which standard (A447 or A447M) applies,

4.1.3 The version of the alloy, that is, Type I or Type II, to be supplied (Sections 1, 11, 12, 13, and 14).

4.1.4 Options in the specification (Section 9), and

4.1.5 The supplementary requirements desired, including the standards of acceptance.

5. Process

5.1 The alloy for the castings shall be made by the electric-furnace process or by any other process approved by the purchaser.

6. Heat Treatment

6.1 Except as otherwise agreed upon between the manufacturer and the purchaser, the manufacturer shall not be required to heat treat the castings.

7. Chemical Composition

7.1 The castings shall conform to the requirements of Table 1 as to chemical composition.

8. Sampling

8.1 Material for the tests specified in Sections 11, 13, and 14 may be taken from separately cast test blocks of a form such as that shown in Fig. 2 of Specification A1067/A1067M, from another type of test block, from the castings, or from coupons attached to the castings as may be agreed upon between the manufacturer and the purchaser.

8.2 Material for the magnetic permeability test specimen (Section 12) may be taken, prior to heat treatment, from the same coupon as the specimen for the tension test after aging; from suitable specimens cast as parts of separately cast test blocks; or, by agreement between the manufacturer and the purchaser, from castings representing the melt.

8.3 In the case of castings for unusual or severe service, the test coupons shall be attached to the castings at convenient locations as may be agreed upon between the manufacturer and the purchaser.

TABLE 1 Chemical Requirements

Element	Composition, %
Ni ^A	10.00–14.00
Cr	23.00–28.00
C	0.20–0.45
N, max	0.20
Mn, max	2.50
Si, max	1.75
P, max	0.030
S, max	0.030
Fe and other elements	as may be agreed upon between the manufacturer and the purchaser

^A Commercial nickel usually carries a small amount of cobalt, and within the usual limits cobalt shall be counted as nickel.

8.4 In all cases, it shall be the manufacturer's duty to provide a sufficient number of samples for the specified tests.

9. Number of Tests

9.1 The purchaser shall specify not more than two tests selected from the following list, with the restriction that not more than one of the tension tests at high temperature (that is, 9.1.3 or 9.1.4) may be required:

9.1.1 Tension test after aging,

9.1.2 Magnetic permeability test,

9.1.3 Stress-rupture test, and

9.1.4 Short-time, high-temperature tension test.

10. Retests

10.1 *Mechanical Tests*—If any of the specimens first chosen for any of the mechanical tests agreed upon fails to conform to the specified requirements, an additional specimen from the same melt may be tested. This additional specimen shall conform to the requirements prescribed for the test in question.

10.2 *Magnetic Test*—If the magnetic permeability of the specimen first tested does not conform to the requirement prescribed in 12.1, three additional specimens from the same melt may be tested. At least two of these shall conform to the prescribed requirement.

11. Tensile Properties After Aging

11.1 The tensile properties of the material after aging shall conform to the following requirements:

	Type I	Type II
Tensile strength, min, ksi [MPa]	80 [550]	80 [550]
Elongation ^A in 2 in. (4D), min, %	9	4
Elongation ^B in 5D, min, %	8.7	3.9

^A These minima shall apply when tested according to Test Methods E8.

^B These minima shall apply when tested according to Test Methods E8M.

11.2 Samples from which the tension specimens are to be taken shall be heated for 24 h at 1400 ± 25 °F [760 ± 14 °C] and allowed to cool at least down to 400 °F [205 °C] at rates not exceeding 200 °F [110 °C]/h. The tension test specimens shall be machined from the heat-treated sample, and shall conform to the dimensions shown in Fig. 8 of Test Methods E8/E8M.

11.3 The tension test shall be made in accordance with Test Methods E8/E8M. The speed of the head of the testing machine shall be so adjusted that the rate of separation of the gage marks on the test specimen shall not exceed 0.1 in./min [0.05 mm/s].

12. Magnetic Permeability

12.1 The magnetic permeability of the material shall conform to the following requirements:

	Magnetic Permeability, max
Type I	1.70
Type II	1.05

NOTE 1—The magnetic permeability test gives a qualitative indication of the ferrite content for alloys falling within the range of chemical composition specified in Section 7, excluding iron and other elements as may be agreed upon. When special alloying elements are specified, the