



Designation: A706/A706M – 22a

Standard Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement¹

This standard is issued under the fixed designation A706/A706M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 *General*—This specification covers deformed and plain low-alloy steel bars in cut lengths and coils for concrete reinforcement intended for applications where restrictive mechanical properties and chemical composition are required for compatibility with controlled tensile property applications or to enhance weldability. The standard sizes and dimensions of deformed bars and their number designations are given in [Table 1](#).

1.2 *Grade*—Bars are of three minimum yield strength levels: namely, 60 000 psi [420 MPa], 80 000 psi [550 MPa], and 100 000 psi [690 MPa] designated as Grade 60 [420], Grade 80 [550], and Grade 100 [690], respectively.

1.3 Plain bars, in sizes up to and including 2½ in. [63.5 mm] in diameter in coils or cut lengths, when ordered, shall be furnished under this specification. For ductility properties (elongation and bending), test provisions of the nearest smaller nominal diameter deformed bar size shall apply. Requirements providing for deformations and marking shall not be applicable.

1.4 *Controlled Tensile Properties*—This specification limits tensile properties ([Table 2](#)) to provide the desired yield/tensile properties for controlled tensile property applications.

1.5 *Welding*—This specification limits chemical composition ([6.2](#)) and carbon equivalent ([6.4](#)) to enhance the weldability of the material. When this steel is to be welded, a welding procedure suitable for the chemical composition and intended use or service should be used. The use of the latest edition of AWS D1.4/D1.4M is recommended. The AWS D1.4/D1.4M Welding Code describes the proper selection of the filler metals, preheat/interpass temperatures, as well as, performance and procedure qualification requirements.

NOTE 1—As a result of the 117 000 psi minimum tensile strength for

Grade 100 [690], users of this specification should be aware that ACI 318 Type 1 mechanical splice requirements of 125 % of specified yield strength requirements in tension and compression, found in many acceptance criteria, may result in an invalid mechanical splice qualification or verification test when the tensile strength of the bar is between 117 000 psi and 125 000 psi.

1.6 [Annex A2](#) describes the methods for determination of uniform elongation (E_{lu}). [Annex A2](#) is mandatory when Supplementary Requirement S1 is specified by the purchaser (see [4.2.6](#)).

1.7 Requirements for alternate bar sizes are presented in [Annex A1](#). The requirements in [Annex A1](#) only apply when specified by the purchaser (see [4.2.5](#)).

1.8 The text of this specification references notes and footnotes that provide explanatory material. These notes and footnotes, excluding those in tables, shall not be considered as requirements of this specification.

1.9 This specification is applicable for orders in either inch-pound units (Specification A706) or in SI units [Specification A706M].

1.10 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with this specification.

1.11 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.12 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Dec. 1, 2022. Published February 2023. Originally approved in 1974. Last previous edition approved in 2022 as A706/A706M – 22. DOI: 10.1520/A0706_A0706M-22A.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Deformed Bar Designation Numbers, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No.	Nominal Weight, lb/ft [Nominal Mass, kg/m]	Nominal Dimensions ⁴			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
3 [10]	0.376 [0.560]	0.375 [9.5]	0.11 [71]	1.178 [29.9]	0.262 [6.7]	0.015 [0.38]	0.143 [3.6]
4 [13]	0.668 [0.994]	0.500 [12.7]	0.20 [129]	1.571 [39.9]	0.350 [8.9]	0.020 [0.51]	0.191 [4.9]
5 [16]	1.043 [1.552]	0.625 [15.9]	0.31 [199]	1.963 [49.9]	0.437 [11.1]	0.028 [0.71]	0.239 [6.1]
6 [19]	1.502 [2.235]	0.750 [19.1]	0.44 [284]	2.356 [59.8]	0.525 [13.3]	0.038 [0.97]	0.286 [7.3]
7 [22]	2.044 [3.042]	0.875 [22.2]	0.60 [387]	2.749 [69.8]	0.612 [15.5]	0.044 [1.12]	0.334 [8.5]
8 [25]	2.670 [3.973]	1.000 [25.4]	0.79 [510]	3.142 [79.8]	0.700 [17.8]	0.050 [1.27]	0.383 [9.7]
9 [29]	3.400 [5.060]	1.128 [28.7]	1.00 [645]	3.544 [90.0]	0.790 [20.1]	0.056 [1.42]	0.431 [10.9]
10 [32]	4.303 [6.404]	1.270 [32.3]	1.27 [819]	3.990 [101.3]	0.889 [22.6]	0.064 [1.63]	0.487 [12.4]
11 [36]	5.313 [7.907]	1.410 [35.8]	1.56 [1006]	4.430 [112.5]	0.987 [25.1]	0.071 [1.80]	0.540 [13.7]
14 [43]	7.65 [11.38]	1.693 [43.0]	2.25 [1452]	5.32 [135.1]	1.185 [30.1]	0.085 [2.16]	0.648 [16.5]
18 [57]	13.60 [20.24]	2.257 [57.3]	4.00 [2581]	7.09 [180.1]	1.58 [40.1]	0.102 [2.59]	0.864 [21.9]

⁴ The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

TABLE 2 Tensile Requirements

	Grade 60 [420]	Grade 80 [550]	Grade 100 [690]
Tensile strength, min, psi [MPa]	80 000 [550]	100 000 [690]	117 000 [805]
Yield strength, min, psi [MPa]	60 000 [420]	80 000 [550]	100 000 [690]
Yield strength, max, psi [MPa]	78 000 [540]	98 000 [675]	118 000 [815]
Ratio of actual tensile strength to actual yield strength, min	1.25	1.25	1.17
Elongation in 8 in. [200 mm], min, %			
Bar Designation Nos.			
3, 4, 5, 6 [10, 13, 16, 19]	14	12	10
7, 8, 9, 10, 11 [22, 25, 29, 32, 36]	12	12	10
14, 18 [43, 57]	10	10	10

2. Referenced Documents

2.1 ASTM Standards:²

- A6/A6M** Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
- A370** Test Methods and Definitions for Mechanical Testing of Steel Products
- A510/A510M** Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel
- A615/A615M** Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- A700** Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment
- A751** Test Methods and Practices for Chemical Analysis of Steel Products
- E8/E8M** Test Methods for Tension Testing of Metallic Materials
- E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E290** Test Methods for Bend Testing of Material for Ductility

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 AWS Standard:³

AWS D1.4/D1.4M Structural Welding Code—Reinforcing Steel

2.3 U.S. Military Standard:⁴

MIL-STD-129 Marking for Shipment and Storage

2.4 U.S. Federal Standard:⁴

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

2.5 ACI Building Code:⁵

ACI Code-318 Building Code Requirements for Structural Concrete and Commentary

2.6 Canadian Standards Association:⁶

G30.18 Carbon steel bars for concrete reinforcement

2.7 ISO Standards:⁷

ISO 15630-1 Steel for the reinforcement and prestressing of concrete – Test methods – Part 1: Reinforcing bars, rods and wire

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *deformations, n*—transverse protrusions on a deformed bar.

3.1.2 *deformed bar, n*—steel bar with protrusions; a bar that is intended for use as reinforcement in reinforced concrete and related construction.

3.1.2.1 *Discussion*—The surface of the bar is provided with lugs or protrusions that inhibit longitudinal movement of the bar relative to the concrete surrounding the bar in such construction. The lugs or protrusions conform to the provisions of this specification.

3.1.3 *plain bar, n*—steel bar without protrusions.

³ Available from American Welding Society (AWS), 8669 NW 36 Street, #130, Miami, FL 33166-6672, <http://www.aws.org>.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁵ Available from American Concrete Institute, 38800 Country Club Dr., Farmington Hills, MI, 48331-3439, <http://www.concrete.org>.

⁶ Available from Canadian Standards Association (CSA), 178 Rexdale Blvd., Toronto, ON M9W 1R3, Canada, <http://www.csagroup.org>.

⁷ Available from International Organization for Standardization (ISO), ISO Central Secretariat, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.