



Designation: A841/A841M – 17 (Reapproved 2025)

Standard Specification for Steel Plates for Pressure Vessels, Produced by Thermo- Mechanical Control Process (TMCP)¹

This standard is issued under the fixed designation A841/A841M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers steel plates produced by the thermo-mechanical control process (TMCP). The plates are intended primarily for use in welded pressure vessels. A description of the TMCP method is given in [Appendix X1](#).

1.2 Due to the inherent characteristics of the TMCP method, the plates cannot be formed at elevated temperatures without sustaining significant losses in strength and toughness. Except for Grade G, the plates may be formed and post-weld heat-treated at temperatures not exceeding 1200 °F [650 °C], providing the requirements of [6.1](#) are met. Grade G plates may be formed at temperatures not exceeding 985 °F [530 °C] provided the requirements of [6.1](#) are met.

1.3 The maximum permitted nominal thickness of plates furnished to this specification is 4 in. [100 mm] for Grades A, B, and C; 1.5 in. [40 mm] for Grades D,³ E, and F; and 2 in. [50 mm] for Grade G.

1.4 Grade G is susceptible to magnetization. Use of magnets in handling after heat treatment should be avoided if residual magnetism would be detrimental to subsequent fabrication or service.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents. Therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

¹ This specification is under the jurisdiction of ASTM Committee [A01](#) on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee [A01.11](#) on Steel Plates for Boilers and Pressure Vessels.

Current edition approved March 1, 2025. Published March 2025. Originally approved in 1985. Last previous edition approved in 2017 as A841/A841M – 17. DOI: 10.1520/A0841_A0841M-17R25.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-841/SA-841M in Section II of that Code.

³ ExxonMobil Upstream Research Company has patents pending concerning the use of chemistry ranges in ASTM A841 Grade D, in combination with specific TMCP routes and/or specific microstructural features. Interested parties are invited to submit information regarding identification of alternatives to these patented items to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

1.6 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:⁴

[A20/A20M](#) Specification for General Requirements for Steel Plates for Pressure Vessels

[A435/A435M](#) Specification for Straight-Beam Ultrasonic Examination of Steel Plates

[A577/A577M](#) Specification for Ultrasonic Angle-Beam Examination of Steel Plates

[A578/A578M](#) Specification for Straight-Beam Ultrasonic Examination of Rolled Steel Plates for Special Applications

3. General Requirements and Ordering Information

3.1 Plates supplied to this product specification shall conform to Specification [A20/A20M](#), which outlines the testing and retesting methods and procedures, permissible variations in dimensions, quality and repair of defects, marking, loading, etc.

3.2 Specification [A20/A20M](#) also establishes the rules for ordering information that should be complied with when purchasing plates to this specification.

3.2.1 If the plates are to be subjected to warm forming or post-weld heat treatment, the order must indicate the temperatures and times-at-temperature that will be utilized in such operations. (See [6.1](#) and Specification [A20/A20M](#), Supplementary Requirement S3.)

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

- 3.3.1 Vacuum treatment,
- 3.3.2 Additional or special tension testing,
- 3.3.3 Additional or special impact testing, and
- 3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification **A20/A20M**.

3.5 If the requirements of this specification are in conflict with the requirements of Specification **A20/A20M**, the requirements of this specification shall prevail.

4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification **A20/A20M**.

4.2 The plates shall be produced by the thermo-mechanical control process.

5. Chemical Composition

5.1 The chemical composition on heat analysis shall conform to the requirements given in **Table 1**, except as otherwise provided in Supplementary Requirement S17 of Specification **A20/A20M** when that requirement is involved.

5.2 If a product analysis is made on a sample taken from the standard location (see Specification **A20/A20M**), the results of the analysis shall not deviate from the limits for the heat analysis by more than the values given in **Table 2**.

6. Mechanical Requirements

6.1 If the plates are to be subjected to warm forming or post-weld heat treatment, the test coupons shall be subjected to heat treatment to simulate such fabrication operations. (See **3.2.1** and Specification **A20/A20M**, Supplementary Requirement S3.)

6.2 *Tension Test Requirements*—The plates as represented by the tension-test specimens shall conform to the requirements given in **Table 3**.

6.2.1 *Number and Location of Test Coupons*—Two tension tests shall be made from each plate-as-rolled. One test coupon shall be taken from a corner of the plate on each end.

6.3 Notch Toughness Test Requirements:

6.3.1 Except for Grade G, longitudinal Charpy V-notch tests shall be made in accordance with Specification **A20/A20M**.

6.3.2 For Grades A, B and C, unless the test temperature and absorbed energy requirements are specified in the purchase order, the tests shall be conducted at -40°F [-40°C] and the average absorbed energy for each set of three full size specimens shall be 15 ft·lb [20 J] or more.

6.3.3 For Grade D, unless the test temperature and the lateral expansion requirements are specified in the purchase order, the tests shall be conducted at -40°F [-40°C] and the lateral expansion for each specimen shall be 0.015 in. [0.4 mm] or more.

6.3.4 For Grades E and F, unless the test temperature and absorbed energy requirements are specified in the purchase order, the tests shall be conducted at -40°F [-40°C] and the average absorbed energy for each set of three full size specimens shall be 20 ft·lb [27 J] or more.

6.3.5 For Grade G, transverse Charpy V-notch tests shall be made in accordance with Specification **A20/A20M**. Unless the test temperature is specified in the purchase order, the tests shall be conducted at -320°F [-195°C]. Each specimen shall have a lateral expansion opposite the notch of not less than 0.015 in. [0.38 mm], up to a plate thickness of 1.25 in. [31.75 mm] inclusive; and 0.019 in. [0.48 mm] at a plate thickness of 2.0 in. [50 mm]. Values of lateral expansion for plate thicknesses between 1.25 in. [31.75 mm] and 2.0 in. [50 mm] shall be determined by linear interpolation.

7. Marking

7.1 In addition to the marking required in Specification **A20/A20M**, each plate shall be legibly stamped with the letters “TMC” following the stamped specification designation.

8. Keywords

8.1 pressure containing parts; pressure vessel steel; steel plates; steel plates for pressure vessel applications