



Designation: A990/A990M – 23

Standard Specification for Castings, Iron-Nickel-Chromium and Nickel Alloys, Specially Controlled for Pressure-Retaining Parts for Corrosive Service¹

This standard is issued under the fixed designation A990/A990M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers iron-nickel-chromium and nickel alloy castings specially processed with restricted melt practices, weldability testing, and nondestructive examination (NDE) requirements.

1.2 A number of grades of iron-nickel-chromium and nickel alloy castings are included in this specification. Since these grades possess varying degrees of suitability for service in corrosive environments, it is the responsibility of the purchaser to determine which grade shall be furnished. Selection will depend on design and service conditions, mechanical properties, and corrosion-resistant characteristics.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3.1 This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable M-specification designation (SI units), the inch-pound units shall apply. Within the text, the SI units are shown in brackets.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Nov. 1, 2023. Published November 2023. Originally approved in 1998. Last previous edition approved in 2021 as A990/A990M – 21. DOI: 10.1520/A0990_A0990M-23.

2. Referenced Documents

2.1 ASTM Standards:²

- A351/A351M Specification for Castings, Austenitic, for Pressure-Containing Parts
- A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel
- A494/A494M Specification for Castings, Nickel and Nickel Alloy
- A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts
- A743/A743M Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel, Corrosion Resistant, for General Application
- A744/A744M Specification for Castings, Iron-Chromium-Nickel, Corrosion Resistant, for Severe Service
- A802/A802M Practice for Steel Castings, Surface Acceptance Standards, Visual Examination
- A903/A903M Specification for Steel Castings, Surface Acceptance Standards, Magnetic Particle and Liquid Penetrant Inspection
- A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts
- E94/E94M Guide for Radiographic Examination Using Industrial Radiographic Film
- E165/E165M Practice for Liquid Penetrant Testing for General Industry
- E186 Reference Radiographs for Heavy-Walled (2 to 4½ in. (50.8 to 114 mm)) Steel Castings
- E272 Reference Radiographs for High-Strength Copper-Base and Nickel-Copper Alloy Castings
- E280 Reference Radiographs for Heavy-Walled (4½ to 12 in. (114 to 305 mm)) Steel Castings
- E446 Reference Radiographs for Steel Castings Up to 2 in. (50.8 mm) in Thickness

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

2.2 AWS Standards:³

AWS A5.4 Specification for Stainless Steel Electrodes for Shielded Metal Arc Welding

AWS A5.9 Specification for Bare Stainless Steel Welding Electrodes and Rods

AWS A5.11/A5.11M Specification for Nickel and Nickel-Alloy Welding Electrodes for Shielded Metal Arc Welding

AWS A5.14/A5.14M Specification for Nickel and Nickel-Alloy Bare Welding Electrodes and Rods

2.3 ASME/ANSI Standard:⁴

ASME/ANSI B16.34 Valves—Flanged, Threaded, and Welding End

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *accessible surface, n*—surface that can be welded on without cutting access holes in the casting.

3.1.2 *refined ingot, n*—metal processed by argon-oxygen-decarburization (AOD) or vacuum-oxygen-decarburization (VOD) and cast to a size and shape suitable for remelting.

3.1.3 *revert, n*—gates, risers, and castings. Also includes scrapped machinery and fabricated items, chips, and turnings.

4. General Conditions for Delivery

4.1 Other than investment castings, material furnished to this specification shall conform to the requirements of Specification **A703/A703M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A703/A703M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A703/A703M**, this specification shall prevail.

4.2 *Investment Castings*—Material furnished to this specification shall conform to the requirements of Specification **A985/A985M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A985/A985M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A985/A985M**, Specification **A985/A985M** shall prevail.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements may include, but are not limited to, the following:

5.1.1 Quantity.

5.1.2 Grade designation (**Table 1**).

5.1.3 Description of the casting by pattern number or drawing. Dimensional tolerances should be included on the casting drawing.

5.1.4 Nondestructive inspection class required (**Table 2**). Class D will be supplied unless otherwise specified.

5.1.5 Wetted surfaces (**Table 2**).

5.2 The purchaser shall specify any supplementary requirements desired, including standards of acceptance, required to adequately describe the desired material.

6. Process and Manufacture

6.1 Alloys, except for nickel-base alloys with 25 to 35 % Cu, shall be made by one of the two following processes:

6.1.1 Electric arc or induction furnace melting followed by AOD or VOD refining, or

6.1.2 Electric arc or induction furnace melting of refined ingot.

6.2 Nickel-base alloys with 25 to 35 % Cu shall be made by **6.1.1** or **6.1.2** or by electric arc or induction melting of virgin or primary metals.

6.3 Additions of up to 5 % are permitted for compositional adjustments and deoxidation.

³ Available from American Welding Society (AWS), 8669 NW 36 Street, #130, Miami, FL 33166-6672, <http://www.aws.org>.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

TABLE 1 Chemical Requirements^{A,B}

Element, %	Grade					
	CK3MCuN	CN3MCu	CW2M	CW2MC	M35-1	N2M
Carbon	0.025	0.030	0.020	0.020	0.35	0.020
Manganese	1.20	1.50	1.00	1.00	1.50	1.00
Silicon	0.75	1.00	0.80	0.45	1.25	0.80
Phosphorus	0.020	0.030	0.030	0.015	0.030	0.030
Sulfur	0.010	0.015	0.015	0.015	0.015	0.015
Molybdenum	6.0–7.0	2.0–3.0	15.0–17.5	8.0–10.0	...	30.0–33.0
Iron	Balance	Balance	2.00	5.0	3.5	3.00
Nickel	17.5–19.5	27.5–30.5	Balance	Balance	Balance	Balance
Chromium	19.5–20.5	19.0–22.0	15.0–17.5	20.0–23.0	...	1.00
Nitrogen	0.18–0.24	...	...	...	...	...
Copper	0.50–1.00	3.0–3.5	...	0.50	26.0–33.0	0.20
Tungsten	...	...	1.00	0.50	...	0.20
Vanadium	...	...	...	0.20	...	0.20
Niobium ^C	...	...	...	3.1–4.5	...	...

^A Where ellipses (...) appear in this table, there is no requirement and the element need not be analyzed for or reported.

^B All values are maximums unless a range is provided.

^C Columbium (Cb) and niobium (Nb) are interchangeable names for the same element 41.