



Designation: B101 – 22

Standard Specification for Lead-Coated Copper Sheet and Strip for Building Construction¹

This standard is issued under the fixed designation B101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for lead-coated copper sheet and strip in flat lengths (or in coils) in ounce-weight thicknesses for roofing, flashing, gutters, downspouts, and for the general sheet metalwork for outside building construction. The lead coating is applied by hot dipping.

1.1.1 Products produced to this specification are not intended for electrical applications.

1.1.2 This product is not designed to be used for decorative, ornamental, or wall panel applications.

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—A companion specification for copper sheet and strip for building construction is Specification B370.

1.3 The following hazard caveat pertains to the test method portion, Section 17, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1935. Last previous edition approved in 2019 as B101–12 (2019). DOI: 10.1520/B0101-22.

2. Referenced Documents

2.1 ASTM Standards:²

B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

B370 Specification for Copper Sheet and Strip for Building Construction

B846 Terminology for Copper and Copper Alloys

B950 Guide for Editorial Procedures and Form of Product Specifications for Copper and Copper Alloys

E8/E8M Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E37 Test Methods for Chemical Analysis of Pig Lead (Withdrawn 2020)³

E46 Test Methods for Chemical Analysis of Lead- and Tin-Base Solder (Withdrawn 1994)³

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)³

E112 Test Methods for Determining Average Grain Size

E478 Test Methods for Chemical Analysis of Copper Alloys

3. General Requirements

3.1 The following sections of Specification B248 constitute a part of this specification:

3.1.1 Significance of numerical limits,

3.1.2 Inspection,

3.1.3 Rejection and rehearing,

3.1.4 Certification,

3.1.5 Test reports, and

3.1.6 Packaging and package marking.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

3.2 In addition, when a section with a title identical to that referenced in 3.1, above, appears in this specification, it contains additional requirements that supplement those appearing in Specification B248.

4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology B846.

4.2 Definitions of Terms Specific to This Standard:

4.2.1 *coil*—a length of the product wound into a series of connected turns.

4.2.1.1 *Discussion*—The unqualified term “coil” as applied to “flat product” usually refers to a coil in which the product is spirally wound, with the successive layers on top of one another. (Sometimes called a “roll.”)

4.2.2 *flashing, n*—an impervious lead-coated copper sheet or strip used in a building envelope to create a barrier to prevent water penetration or direct the flow of moisture.

4.2.2.1 *Discussion*—This can include, but is not limited to, the heads of windows and doors, the edge components of roof systems, changes in building planes, around chimneys, roof vents, skylights, decks and other penetrations, and other conditions requiring a watertight or water-shedding solution.

4.2.3 *lead-coated copper sheet (for building construction), n*—a rolled flat product over 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

4.2.4 *lead-coated strip (for building construction), n*—a rolled flat product up to and including 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

4.2.5 *lengths, mill, n*—straight lengths, including ends, that are conveniently manufactured in the mills.

4.2.5.1 *Discussion*—Full length pieces are usually 8 ft, 10 ft, or 12 ft (2.44 m, 3.05 m, or 3.66 m) and subject to established length tolerances.

4.2.6 *ounce-weight*—the weight of uncoated copper sheet or strip expressed in ounces per square foot.

4.2.7 *thickness, ounce-weight, n*—the metal thickness that corresponds to the ounce weight.

5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification, as applicable:

- 5.1.1 ASTM designation and year of issue.
- 5.1.2 Temper (Section 8 and Table 2),
- 5.1.3 How furnished: flat lengths or in coils,
- 5.1.4 Quantity: total weight or sheets of each size,
- 5.1.5 Ounce-weight or ounce-weight thickness of the uncoated copper sheet or strip (Table 3),
- 5.1.6 Dimensions: width and length (Section 12),

5.2 The following options are available and, when required, shall be specified at the time of placing of the order:

- 5.2.1 Heat identification or traceability details.
- 5.2.2 Certification, where required (see 5.1.4),
- 5.2.3 Test report, where required (see 5.1.5), and

5.2.4 If the material being purchased is intended for use by agencies of the U.S. government, refer to Section 11.

5.2.5 Other variations in coating or texture shall be furnished by agreement in writing between the purchaser and the manufacturer or supplier.

6. Materials and Manufacture

6.1 Materials:

6.1.1 The material of manufacture shall be in the form of copper strip or sheet that conforms to the requirements of Specification B370.

6.1.2 The lead coating shall conform to the chemical requirements of Table 1.

NOTE 2—Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.

6.2 Manufacture:

6.2.1 The product shall be manufactured by hot dipping the copper sheet or strip in a bath of molten lead to produce the finished product.

6.2.2 Unless otherwise specified, the lead coating shall be applied to the copper sheet after slitting and cutting to the specified length.

6.2.3 Unless otherwise specified, the lead coating shall be applied to the copper strip before slitting.

7. Chemical Composition

7.1 The copper sheet or strip shall have a minimum copper, including silver, content of 99.5 %.

7.2 Any copper that complies with 7.1 shall be acceptable.

7.3 If limits for unnamed elements are required, they shall be established and analysis required by agreement between the manufacturer or supplier and purchaser.

7.4 The lead coating shall conform to the chemical requirements of Table 1.

8. Temper

8.1 The standard tempers of the uncoated copper sheet and strip described in this specification are given in Table 2.

8.1.1 Annealed Temper O60.

8.1.2 Cold rolled tempers H00 (eighth hard, cold-rolled); and H01 (quarter hard, cold-rolled high yield).

**TABLE 1 Chemical Requirements for Lead
Used to Coat Copper Sheet**

Element	Composition, % (Maximum unless shown as range or remainder)
Silver	0.02
Copper	0.08
Arsenic plus antimony	0.10
Zinc	0.005
Iron	0.01
Bismuth	0.08
Lead	remainder
Tin	3.0-4.0
Phosphorus	0.03