



Designation: B248 – 22

Standard Specification for General Requirements for Wrought Copper and Copper- Alloy Plate, Sheet, Strip, and Rolled Bar¹

This standard is issued under the fixed designation B248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the general requirements common to several wrought product specifications. Unless otherwise specified in the purchase order or in an individual specification, these general requirements shall apply to copper and copper-alloy plate, sheet, strip, and rolled bar supplied under each of the following product specifications issued by ASTM: **B19**, **B36/B36M**, **B96/B96M**, **B101**, **B103/B103M**, **B121/B121M**, **B122/B122M**, **B130**, **B152/B152M**, **B169/B169M**, **B194**, **B370**, **B422/B422M**, **B465**, **B534**, **B591**, **B592**, **B694**, **B740**, **B747**, **B768**, **B888/B888M**, and **B936**.²

1.2 *Units*—This specification is the companion specification to SI Specification **B248M**; therefore, no SI equivalents are shown in this specification.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:³

¹ This specification is under the jurisdiction of the ASTM Committee **B05** on Copper and Copper Alloys and is the direct responsibility of Subcommittee **B05.01** on Plate, Sheet, and Strip.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1951. Last previous edition approved in 2017 as B248 – 17. DOI: 10.1520/B0248-22.

² The UNS system for copper and copper alloys (see Practice **E527**) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

B19 Specification for Cartridge Brass Sheet, Strip, Plate, Bar, and Disks
B36/B36M Specification for Brass Plate, Sheet, Strip, And Rolled Bar
B96/B96M Specification for Copper-Silicon Alloy Plate, Sheet, Strip, and Rolled Bar for General Purposes and Pressure Vessels
B100 Specification for Wrought Copper-Alloy Bearing and Expansion Plates and Sheets for Bridge and Other Structural Use
B101 Specification for Lead-Coated Copper Sheet and Strip for Building Construction
B103/B103M Specification for Phosphor Bronze Plate, Sheet, Strip, and Rolled Bar
B121/B121M Specification for Leaded Brass Plate, Sheet, Strip, and Rolled Bar
B122/B122M Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver), and Copper-Nickel Alloy Plate, Sheet, Strip, and Rolled Bar
B130 Specification for Commercial Bronze Strip for Bullet Jackets
B152/B152M Specification for Copper Sheet, Strip, Plate, and Rolled Bar
B169/B169M Specification for Aluminum Bronze Sheet, Strip, and Rolled Bar
B193 Test Method for Resistivity of Electrical Conductor Materials
B194 Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar
B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)
B370 Specification for Copper Sheet and Strip for Building Construction
B422/B422M Specification for Copper-Aluminum-Silicon-Cobalt Alloy, Copper-Nickel-Silicon-Magnesium Alloy, Copper-Nickel-Silicon Alloy, Copper-Nickel-Aluminum-Magnesium Alloy, and Copper-Nickel-Tin Alloy Sheet and Strip

*A Summary of Changes section appears at the end of this standard

B465 Specification for Copper-Iron Alloy Plate, Sheet, Strip, and Rolled Bar

B534 Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

B591 Specification for Copper-Zinc-Tin and Copper-Zinc-Tin-Iron-Nickel Alloys Plate, Sheet, Strip, and Rolled Bar

B592 Specification for Copper-Zinc-Aluminum-Cobalt Alloy, Copper-Zinc-Tin-Iron Alloy Plate, Sheet, Strip, and Rolled Bar

B694 Specification for Copper, Copper-Alloy, Copper-Clad Bronze (CCB), Copper-Clad Stainless Steel (CCS), and Copper-Clad Alloy Steel (CAS) Sheet and Strip for Electrical Cable Shielding

B740 Specification for Copper-Nickel-Tin Spinodal Alloy Strip

B747 Specification for Copper-Zirconium Alloy Sheet and Strip

B768 Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Strip and Sheet

B820 Test Method for Bend Test for Determining the Formability of Copper and Copper Alloy Strip

B846 Terminology for Copper and Copper Alloys

B888/B888M Specification for Copper Alloy Strip for Use in Manufacture of Electrical Connectors or Spring Contacts

B936 Specification for Copper-Chromium-Iron-Titanium Alloy Plate, Sheet, Strip and Rolled Bar

E8/E8M Test Methods for Tension Testing of Metallic Materials

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry (Withdrawn 2022)⁴

E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)⁴

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁴

E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)⁴

E106 Test Methods for Chemical Analysis of Copper-Beryllium Alloys (Withdrawn 2011)⁴

E112 Test Methods for Determining Average Grain Size

E118 Test Methods for Chemical Analysis of Copper-Chromium Alloys (Withdrawn 2010)⁴

E121 Test Methods for Chemical Analysis of Copper-Tellurium Alloys (Withdrawn 2010)⁴

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E478 Test Methods for Chemical Analysis of Copper Alloys

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E1004 Test Method for Determining Electrical Conductivity Using the Electromagnetic (Eddy Current) Method

2.3 *ASME Code*:⁵

ASME Boiler and Pressure Vessel Code

3. Terminology

3.1 For definitions of terms related to copper and copper alloys, see Terminology **B846**.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *lengths, mill, n*—straight lengths, including ends, that can be conveniently manufactured in the mills. Full-length pieces are usually 8 ft, 10 ft, or 12 ft and subject to established length tolerances.

3.2.2 *lengths, stock, n*—straight lengths that are mill cut and stored in advance of orders. They are usually 8 ft, 10 ft, or 12 ft and subject to established length tolerances.

3.2.3 *rolled bar, n*—a rolled flat product over 0.188 in. thick and up to and including 12 in. wide, with sheared, sawed, or machined edges, in straight lengths or coils (rolls).

4. Materials and Manufacture

4.1 *Materials*:

4.1.1 The material of manufacture shall be a cast bar, cake, or slab of such purity and soundness as to be suitable for processing into the products to the product specification listed in Section 1.

4.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.

4.2 *Manufacture*:

4.2.1 The product shall be manufactured by such hot-working, cold-working and annealing processes as to produce a uniform wrought structure in the finished product.

4.2.2 The product shall be hot- or cold-worked to the finished size and subsequently annealed, when required, to meet the temper properties specified.

4.3 *Edges*—The edges shall be slit, sheared, sawed, or rolled edges, as specified. Slit edges shall be furnished unless otherwise specified in the contract or purchase order. See **5.6** for edge descriptions and corresponding tables for tolerances.

5. Dimensions, Weights, and Permissible Variations

5.1 *General*—For the purpose of determining conformance with the dimensional requirements prescribed in this specification, any measured value outside the specified limiting values for any dimension may be cause for rejection.

NOTE 1—Blank spaces in the tolerance tables indicate either that the material is not available or that no tolerances have been established.

5.2 *Thickness*—The standard method of specifying thickness shall be in decimal fractions of an inch. For material

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.