



Designation: B408 – 22

Standard Specification for Nickel-Iron-Chromium Alloy Rod and Bar¹

This standard is issued under the fixed designation B408; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers UNS N08120, UNS N08800, UNS N08810, UNS N08811,³ and UNS N08890 in the form of hot-worked and cold-worked rod and bar. Alloy UNS N08800 is normally employed in service temperatures up to and including 1100 °F (593 °C). Alloys UNS N08120, UNS N08810, UNS N08811, and UNS N08890 are normally employed in service temperatures above 1100 °F (593 °C) where resistance to creep and rupture is required, and they are annealed to develop controlled grain size for optimum properties in this temperature range.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1957. Last previous edition approved in 2016 as B408 – 06 (2016). DOI: 10.1520/B0408-22.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-408 in Section II of that Code.

³ New designations established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

2. Referenced Documents

2.1 ASTM Standards:⁴

B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

B899 Terminology Relating to Non-ferrous Metals and Alloys

E8/E8M Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E112 Test Methods for Determining Average Grain Size

E1473 Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys

3. Terminology

3.1 Definitions of Terms:

3.1.1 The terms and definitions of Terminology B899 are applicable to this specification.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bar, n*—material of rectangular (flats), hexagonal, or square solid section up to and including 10 in. (254 mm) in width and 1/8 in. (3.2 mm) and over in thickness in straight lengths.

3.2.1.1 *Discussion*—Hot-worked rectangular bar in widths 10 in. (254 mm) and under may be furnished as hot-rolled plate with sheared or cut edges in accordance with Specification B408, provided the mechanical property requirements of Specification B408 are met.

4. Ordering Information

4.1 Orders for material to this specification should include information with respect to the following:

4.1.1 ASTM designation, and year of issue.

4.1.2 Alloy designation or UNS number.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

4.1.3 *Section*—Rod (round) or bar (square, hexagonal, or rectangular).

4.1.4 *Dimensions*—Dimensions including length (Section 8, Tables 1-4 incl).

4.1.5 *Condition* (Table 5 and Appendix X1).

4.1.6 *Finish* (Appendix X1).

4.1.7 *Quantity* (feet or number of pieces).

4.1.8 *Certification*—State if certification or a report of test results is required (Section 16).

4.1.9 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished.

4.1.10 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which test or inspections are to be witnessed.

5. Materials and Manufacture

5.1 *Heat Treatment*—The minimum temperature of the final heat treatment for each alloy shall be as follows:

5.1.1 *UNS N08120*—2150 °F (1177 °C);

5.1.2 *UNS N08810*—2050 °F (1121 °C);

5.1.3 *UNS N08811 and UNS N08890*—2100 °F (1149 °C).

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 6.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in Specification B880.

7. Mechanical Properties and Other Requirements

7.1 *Mechanical Properties*—The material shall conform to the mechanical properties specified in Table 5.

7.2 *Grain Size*—Annealed UNS Alloys N08120, N08810, N08811, and N08890 shall conform to an average grain size of ASTM No. 5 or coarser.

8. Dimensions and Permissible Variations

8.1 *Diameter, Thickness, or Width*—The permissible variations from the specified dimensions as measured on the

TABLE 2 Permissible Variations in Diameter or Distance

Specified Dimension, in. (mm) ^A	Permissible Variations from Specified Dimensions, in. (mm)	
	+	–
Rod and bar, hot-worked:		
1 (25.4) and under	0.016 (0.41)	0.016 (0.41)
Over 1 (25.4) to 2 (50.8), incl	0.031 (0.79)	0.016 (0.41)
Over 2 (50.8) to 4 (101.6), incl	0.047 (1.19)	0.031 (0.79)
Over 4 (101.6)	0.125 (3.18)	0.063 (1.60)
Rod, rough turned or ground:		
Under 1 (25.4)	0.005 (0.13)	0.005 (0.13)
1 (25.4) and over	0.031 (0.79)	0
Forging quality rod ^B		
Under 1 (25.4)	0.005 (0.13)	0.005 (0.13)
1 (25.4) and over	0.031 (0.79)	0

^A Dimensions apply to diameter of rods, to distance between parallel surfaces of hexagons and squares, and separately to width and thickness of rectangles.

^B Spot grinding is permitted to remove minor surface imperfections. The depth of these spot ground areas shall not exceed 3 % of the diameter of the rod.

diameter or between parallel surfaces of cold-worked rod and bar shall be as prescribed in Table 1, and of hot-worked rod and bar as prescribed in Table 2.

8.2 *Out-of-Round*—Hot-worked rods and cold-worked rods (except “forging quality”) all sizes, in straight lengths, shall not be out-of-round by more than one half the total permissible variations in diameter shown in Table 1 and Table 2, except for hot-worked rods ½ in. (12.7 mm) in diameter and under, which may be out-of-round by the total permissible variations in diameter shown in Table 2.

8.3 *Corners*—Cold-worked bars will have practically exact angles and sharp corners.

8.4 *Machining Allowances for Hot-Worked Materials*—When the surfaces of hot-worked products are to be machined, the allowances prescribed in Table 3 are recommended for normal machining operations.

8.5 *Length*—The permissible variations in length of cold-worked and hot-worked rod and bar shall be as prescribed in Table 4.

8.5.1 Rods and bars ordered to random or nominal lengths will be furnished with either cropped or saw-cut ends; material ordered to cut lengths will be furnished with square saw-cut or machined ends.

8.6 *Straightness*:

8.6.1 The permissible variations in straightness of cold-worked rod and bar as determined by the departure from straightness shall be as prescribed in Table 7.

8.6.2 The permissible variations in straightness of hot-worked rod and bar as determined by the departure from straightness shall be as specified in Table 8.

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and condition, smooth, commercially straight or flat, and free of injurious imperfections.

TABLE 1 Permissible Variations in Diameter or Distance Between Parallel Surfaces of Cold-Worked Rod and Bar

Specified Dimension, in. (mm) ^A	Permissible Variations from Specified Dimension, in. (mm)	
	+	–
Rounds:		
1/16 (1.6) to 3/16 (4.8), excl	0	0.002 (0.05)
3/16 (4.8) to 1/2 (12.7), excl	0	0.003 (0.08)
1/2 (12.7) to 15/16 (23.8), incl	0.001 (0.03)	0.002 (0.05)
Over 15/16 (23.8) to 1 1/16 (49.2), incl	0.0015 (0.04)	0.003 (0.08)
Over 1 1/16 (49.2) to 2 1/2 (63.5), incl	0.002 (0.05)	0.004 (0.10)
Hexagons, squares, rectangles:		
1/2 (12.7) and less	0	0.004 (0.10)
Over 1/2 (12.7) to 7/8 (22.2), incl	0	0.005 (0.13)
Over 7/8 (22.2) to 1 1/4 (31.8), incl	0	0.007 (0.18)
Over 1 1/4 (31.8) to 2 (50.8), incl	0	0.009 (0.23)

^A Dimensions apply to diameter of rounds, to distance between parallel surfaces of hexagons and squares, and separately to width and thickness of rectangles.