



Designation: B444 – 23

Standard Specification for Nickel-Chromium-Molybdenum-Niobium Alloys and Nickel-Chromium-Molybdenum-Silicon Alloy Pipe and Tube¹

This standard is issued under the fixed designation B444; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² covers nickel-chromium-molybdenum-niobium alloys (UNS N06625 and UNS N06852) and nickel-chromium-molybdenum-silicon alloy (UNS N06219)³ in the form of cold-worked seamless pipe and tube. The general requirements for pipe and tube are covered by Specification B829.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary caveat pertains only to the test methods portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved July 1, 2023. Published July 2023. Originally approved in 1966. Last previous edition approved in 2018 as B444 – 18. DOI: 10.1520/B0444-23.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-444 in Section II of that Code.

³ New designation established in accordance with Practice E527 and SAE J 1086, Practice for Numbering Metals and Alloys (UNS).

2. Referenced Documents

2.1 ASTM Standards:⁴

B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube

B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

B899 Terminology Relating to Non-ferrous Metals and Alloys

E112 Test Methods for Determining Average Grain Size

G28 Test Methods for Detecting Susceptibility to Intergranular Corrosion in Wrought, Nickel-Rich, Chromium-Bearing Alloys

G48 Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution

3. Terminology

3.1 Definition of Terms:

3.1.1 The terms and definitions of Terminology B899 apply.

4. Ordering Information

4.1 Orders for material to this specification shall include information with respect to the following:

4.1.1 Alloy name or UNS number,

4.1.2 ASTM designation,

4.1.3 Condition (temper) (see 5.2, 5.3, Table 1, and Annex A1),

4.1.3.1 If neither grade of N06625 is specified, Grade 1 will be supplied.

4.1.4 Finish (See Appendix X1.1),

4.1.5 Dimensions:

4.1.5.1 *Tube*—Specify outside diameter and nominal or minimum wall,

4.1.5.2 *Pipe*—Specify standard pipe size and schedule,

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Room Temperature Tensile Properties and Heat Treatment^{A,B}

Condition	Tensile Strength, min, ksi (MPa) ^C	Yield Strength (0.2 % offset), min, ksi (MPa) ^C	Elongation in 2 in. or 50.8 mm (or 4 D), min, %
Alloy N06625			
Grade 1 (annealed) ^D	120 (827)	60 (414)	30
Grade 2 (solution annealed) ^E	100 (690)	40 (276)	30
Alloy N06219			
All (solution annealed)	96 (660)	39 (270)	30
Alloy N06852			
All (solution annealed)	85 (586)	35 (241)	30

^A Not applicable to outside diameters under 1/8 in. (3.2 mm) and to wall thicknesses under 0.015 in. (0.38 mm).

^B Hot forming quality pipe and tubing is furnished to chemical requirements and surface inspection only. No tensile properties are required.

^C The minimum strength values apply only to tubing in straight lengths.

^D Annealed at 1600 °F (871 °C) minimum.

^E Solution annealed at 2000 °F (1093 °C) minimum, with or without subsequent stabilization anneal at 1800 °F (982 °C) minimum to increase resistance to sensitization.

4.1.5.3 *Length*—Cut to length or random,

4.1.6 *Quantity*—Feet (or meters) or number of pieces,

4.1.7 *Hydrostatic Test or Nondestructive Electric Test*—Specify type of test (see 7.2),

4.1.8 *Hydrostatic Pressure Requirements*—Specify test pressure if other than required by 8.1.1,

4.1.9 *Certification*—State if certification is required,

4.1.10 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished (see 6.2),

4.1.11 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed, and

4.1.12 *Small-Diameter Tube and Tube with Specified Wall Thickness 3 % or Less of the Specified Outside Diameter (Converter Sizes)*—See Annex A1.

4.1.13 *Supplementary Ordering Requirements*: Grain Size Test (S1); Intergranular Corrosion Test (S2); Pitting and Crevice Corrosion Test (S3) may be ordered as an option by the purchaser in the purchase order indicating which tests are to be included.

5. Materials and Manufacture

5.1 Material furnished under this specification shall conform to the applicable requirements of Specification B829 unless otherwise provided herein.

5.2 UNS N06625 products are furnished in two grades of different heat-treated conditions:

5.2.1 Grade 1 (annealed)—Material is normally employed in service temperatures up to 1100 °F (593 °C).

5.2.2 Grade 2 (solution annealed)—Material is normally employed in service temperatures above 1100 °F (593 °C) when resistance to creep and rupture is required.

NOTE 1—Hot-working or reannealing may change properties significantly, depending on working history and temperatures.

5.3 Alloys UNS N06219 and UNS N06852 are supplied in the solution annealed condition only.

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 2. One test is required for each lot as defined in Specification B829.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in Table 1 of Specification B880.

7. Mechanical Properties and Other Requirements

7.1 *Tension Test*—One test per lot shall be performed. The material shall conform to the tensile properties specified in Table 1. The sampling and specimen preparation are as covered in Specification B829.

7.2 *Hydrostatic or Nondestructive Electric Test*—Each pipe or tube shall be subjected to either the hydrostatic test or to the nondestructive electric test. The type of test to be used shall be at the option of the manufacturer, unless otherwise specified in the purchase order.

8. Test Methods

8.1 *Hydrostatic Test*—Each pipe or tube with an outside diameter 1/8 in. (3 mm) and larger and with wall thickness of 0.015 in. (0.38 mm) and over shall be tested in accordance with Specification B829. The allowable fiber stress for material in the condition furnished, is as follows:

UNS N06625:

Grade 1—30 000 psi (207 MPa)

UNS N06625:

Grade 2—25 000 psi (172 MPa)

UNS N06219:

All—24 000 psi (165 MPa)

UNS N06852:

All—21 000 psi (145 MPa)

TABLE 2 Chemical Requirements

Element	Composition Limits, %		
	N06852	N06625	N06219
Carbon	0.05 max	0.10 max	0.05 max
Manganese	0.50 max	0.50 max	0.50 max
Silicon	0.50 max	0.50 max	0.70-1.10
Phosphorus	0.015 max	0.015 max	0.020 max
Sulfur	0.015 max	0.015 max	0.010 max
Chromium	20.0-23.0	20.0 min	18.0-22.0
	...	23.0 max	...
Niobium ^B + Tantalum	...	3.15 min	...
	...	4.15 max	...
Niobium ^B	0.51-1.00	...	...
Cobalt (if determined)	...	1.0 max	1.0 max
Molybdenum	8.0-10.0	8.0 min	7.0-9.0
		10.0 max	...
Iron	15.0-20.0	5.0 max	2.0-4.0
Aluminum	0.40 max	0.40 max	0.50 max
Titanium	0.40 max	0.40 max	0.50 max
Copper	...	...	0.50 max
Nickel ^A	Bal.	58.0 min	Bal.

^A Element shall be determined arithmetically by difference.

^B Columbium and Niobium are interchangeable names for the same element and both names are acceptable for use in B02.07 specifications.