



Designation: B616 – 23

Standard Specification for Refined Rhodium¹

This standard is issued under the fixed designation B616; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers refined rhodium as sponge and powder in three grades as follows:

1.1.1 *Grade 99.80*—Rhodium having a purity of 99.80 %,

1.1.2 *Grade 99.90*—Rhodium having a purity of 99.90 %, and

1.1.3 *Grade 99.95*—Rhodium having a purity of 99.95 %.

1.1.4 For the purposes of determining conformance with this specification, an observed value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding method of Practice E29.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:²

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials and Test Methods.

Current edition approved April 1, 2023. Published May 2023. Originally approved in 1977. Last previous edition approved in 2018 as B616 – 96 (2018). DOI: 10.1520/B0616-96R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

B542 Terminology Relating to Electrical Contacts and Their Use

B899 Terminology Relating to Non-ferrous Metals and Alloys

3. Terminology

3.1 For definitions of the terms pertaining to this standard, reference shall be made to Terminology B542 and B899.

4. Manufacture

4.1 The material may be produced by any refining process that yields a product capable of meeting the chemical requirements of this specification. The purchaser, upon request, shall be informed of the refining process used.

5. Chemical Requirements

5.1 The material should conform to the requirements for chemical composition as prescribed in Table 1.

5.2 Analysis shall be made using the manufacturer's standard methods. In the event of disagreement as to the chemical composition of the metal, methods of chemical analysis for reference purposes shall be determined by a mutually acceptable laboratory.

6. Sampling

6.1 The value of this material is such that special attention must be paid to sampling procedures. The purchaser and manufacturer shall agree upon sampling procedures used.

6.2 *Lot Size*—Sampling lots shall consist of the following:

6.2.1 *Sponge*—A single refining lot and

6.2.2 *Powder*—A single refining lot.

7. Rejection and Rehearing

7.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

7.2 *Investigation of Claims*—In a question of chemical composition, a new sample shall be drawn by representatives of both parties in accordance with Section 6. The properly