



Designation: B633 – 23

Standard Specification for Electrodeposited Coatings of Zinc on Iron and Steel¹

This standard is issued under the fixed designation B633; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

INTRODUCTION

This specification provides a standard to order an electrodeposited zinc coating that mitigates corrosion of iron and steel articles in order to extend the service life of parts. The service life is reduced when such a coating stops protecting the iron or steel substrate resulting in corrosion of the substrate.

The pretreatment and plating process can introduce hydrogen that can cause internal hydrogen embrittlement in high strength steels causing loss of strength and ductility. It is generally agreed that steels below 1200 MPa are not susceptible to such embrittlement.

1. Scope*

1.1 This specification covers material and process requirements for electrodeposited zinc coatings applied to iron or steel articles to protect them from corrosion.

1.2 This specification is not intended to provide the design activity with all the background needed to properly specify their zinc coating requirements. The users of Specification B633 are encouraged to review this specification in its entirety including the appendices, and access the supplementary papers, other standards, and published literature referenced herein and within other related references.

1.3 The coatings are provided in four standard thickness classes (4.1), in the as-plated condition or with one of five types of supplementary finishes (4.2).

1.4 High strength metals, including high strength steels having a tensile strength greater than 1700 MPa (247 ksi, 46 HRC) should not be zinc electroplated in accordance with this specification.

1.5 It does not cover continuous processes for electrodeposited zinc coated steel wire or sheets (see Specification A591/A591M for sheets).

1.6 For zinc electroplating of mechanical fasteners, the purchaser is encouraged to consider Specification F1941/F1941M.

1.7 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.9 *This standard has been revised to address RoHS requirements that seek to limit the exposure of workers and the public from exposure to toxic metals. Additional types V and VI have been added to permit non-chromate passivate treatments to be used in replacement of hexavalent chromium.*

1.10 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

A591/A591M Specification for Steel Sheet, Electrolytic Zinc-Coated, for Light Coating Weight [Mass] Applications (Withdrawn 2005)³

B117 Practice for Operating Salt Spray (Fog) Apparatus

¹ This specification is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.06 on Soft Metals.

Current edition approved Jan. 1, 2023. Published January 2023. Originally approved in 1978. Last previous edition approved in 2019 as B633 – 19. DOI: 10.1520/B0633-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

- B183** Practice for Preparation of Low-Carbon Steel for Electroplating
- B201** Practice for Testing Chromate Coatings on Zinc and Cadmium Surfaces
- B242** Guide for Preparation of High-Carbon Steel for Electroplating
- B254** Practice for Preparation of and Electroplating on Stainless Steel
- B320** Practice for Preparation of Iron Castings for Electroplating
- B322** Guide for Cleaning Metals Prior to Electroplating
- B374** Terminology Relating to Electroplating
- B487** Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section
- B499** Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals
- B504** Test Method for Measurement of Thickness of Metallic Coatings by the Coulometric Method
- B567** Test Method for Measurement of Coating Thickness by the Beta Backscatter Method
- B568** Test Method for Measurement of Coating Thickness by X-Ray Spectrometry
- B571** Practice for Qualitative Adhesion Testing of Metallic Coatings
- B602** Guide for Attribute Sampling of Metallic and Inorganic Coatings
- B697** Guide for Selection of Sampling Plans for Inspection of Electrodeposited Metallic and Inorganic Coatings
- B748** Test Method for Measurement of Thickness of Metallic Coatings by Measurement of Cross Section with a Scanning Electron Microscope
- B762** Guide of Variables Sampling of Metallic and Inorganic Coatings
- B849** Specification for Pre-Treatments of Iron or Steel for Reducing Risk of Hydrogen Embrittlement
- B850** Guide for Post-Coating Treatments of Steel for Reducing the Risk of Hydrogen Embrittlement
- D2092** Guide for Preparation of Zinc-Coated (Galvanized) Steel Surfaces for Painting (Withdrawn 2008)³
- F1470** Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection
- F1940** Test Method for Process Control Verification to Prevent Hydrogen Embrittlement in Plated or Coated Fasteners
- F1941/F1941M** Specification for Electrodeposited Coatings on Mechanical Fasteners, Inch and Metric
- F2078** Terminology Relating to Hydrogen Embrittlement Testing
- 2.2 Military Standard:**⁴
- MIL-STD-1312** Fastener Tests, Methods (Test 12)

2.3 ISO Standard:⁵

ISO/TR 20491 Fundamentals of Hydrogen Embrittlement in Steel Fasteners

3. Terminology

3.1 Definitions:

3.1.1 Definitions of the terms used in this specification are in accordance with Terminology **B374**.

3.1.2 *passivate*—for the purpose of this specification, a conversion coating on zinc shall not contain hexavalent chromium.

4. Classification

4.1 Thickness—The coating shall be provided in one of the four thickness classes defined in **Table 1**.

TABLE 1 Thickness Classes for Coatings

Classification Number and Conversion Coating Suffix	Service Condition	Thickness, min μm
Fe/Zn 25	SC 4 (very severe)	25
Fe/Zn 12	SC 3 (severe)	12
Fe/Zn 8	SC 2 (moderate)	8
Fe/Zn 5	SC 1 (mild)	5

4.2 Finish—The coating shall have one of the finish types defined in **Table 2**.

TABLE 2 Finish Type and Corrosion Resistance Requirements

Type	Description	Minimum Salt Spray h
I	As-plated without supplementary treatments	
II	With colored chromate coatings	96
III	With colorless chromate conversion coatings	12
IV	With phosphate conversion coatings	
V	With colorless passivate	72
VI	With colored passivate	120

5. Ordering Information

5.1 When ordering the electroplating of articles, the purchaser shall state ASTM B633, the date of issue, service condition number, and the Type (see **4.1**, **4.2**, and **7.1**).

5.2 If necessary, the purchaser shall include on the part drawings or purchase order the following:

5.2.1 Basis metal alloy designation and ultimate tensile strength of the steel,

5.2.2 Whether the part underwent cold forming or cold straightening subsequent to heat treatment (see **Note 1**).

5.2.3 Thickness, if other than specified (**4.1**, **7.1**),

5.2.4 Location of significant surface (**7.1.1**, **7.1.2**),

5.2.5 Luster (**7.3**),

5.2.6 Exceptions to stress relief heat treatment prior to plating (**6.4**),

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://dodssp.daps.dla.mil>.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.