



Designation: B649 – 26

Standard Specification for Ni-Fe-Cr-Mo-Cu-N Low-Carbon Alloy and Cr-Ni-Fe-N Low-Carbon Alloy Bar and Wire, Ni-Cr-Fe-Mo-N Alloy Wire, and Ni-Fe-Cr-Mo-N Alloy Bar¹

This standard is issued under the fixed designation B649; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers nickel-iron-chromium-molybdenum-copper-nitrogen alloy and chromium-nickel-iron-nitrogen low-carbon alloy bar and wire, nickel-chromium-iron-molybdenum-nitrogen alloy wire, and nickel-iron-chromium-molybdenum-nitrogen alloy bar.

1.2 ASTM International has adopted definitions whereby some grades, such as UNS N08904,² previously in this specification were recognized as stainless steels, because those grades have iron as the largest element by mass percent. Such grades are under the oversight of ASTM Committee A01 and its subcommittees. The products of N08904 previously covered in this specification are now covered by Specifications [A479/A479M](#) and [A484/A484M](#).

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2026. Published April 2026. Originally approved in 1981. Last previous edition approved in 2021 as B649–21. DOI: 10.1520/B0649-26.

² New designation established in accordance with Practice [E527](#) and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

2. Referenced Documents

2.1 ASTM Standards:³

[A479/A479M](#) Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

[A484/A484M](#) Specification for General Requirements for Stainless Steel Bars, Billets, Shapes, and Forgings

[B880](#) Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

[B899](#) Terminology Relating to Non-ferrous Metals and Alloys

[E8/E8M](#) Test Methods for Tension Testing of Metallic Materials

[E29](#) Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

[E55](#) Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition

[E527](#) Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

[E1473](#) Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology [B899](#).

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bars, n*—hot-finished rounds, squares, octagons, and hexagons: ¼ in. (6.35 mm) and over in diameter or size; Hot-finished flats: ¼ in. to 10 in. (254 mm) inclusive in width, ⅛ in. (3.18 mm) and over in thickness; Cold-finished rounds, squares, octagons, hexagons, and shapes: over ½ in. (12.70 mm) in diameter or size; Cold-finished flats: ⅜ in. (9.52 mm) and over in width (see 3.2.1.1) and ⅛ in. and over in thickness (see 3.2.1.2).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

3.2.1.1 *Discussion*—Widths less than $\frac{3}{8}$ in. (9.52 mm) and thicknesses less than $\frac{3}{16}$ in. (4.76 mm) are described generally as flat wire.

3.2.1.2 *Discussion*—Thickness $\frac{1}{8}$ in. to under $\frac{3}{16}$ in. (3.18 mm to under 4.76 mm) can be cold-rolled strip as well as bar.

3.2.2 *wire, n*—cold-finished only: round, square, octagon, hexagon, and shape wire, $\frac{1}{2}$ in. (12.70 mm) and under in diameter or size. Cold-finished only: flat wire, $\frac{3}{16}$ in. to under $\frac{3}{8}$ in. (4.76 mm to under 9.52 mm) in width, 0.010 in. to under $\frac{3}{16}$ in. (0.25 mm to under 4.76 mm) in thickness.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Examples of such requirements include, but are not limited to, the following:

- 4.1.1 Quantity (weight or number of pieces),
- 4.1.2 Alloy name or UNS number,
- 4.1.3 Form (bar or wire),
- 4.1.4 Dimensions,
- 4.1.5 Finish (Section 9),
- 4.1.6 ASTM designation and year of issue,
- 4.1.7 Exceptions to the specification or special requirements.

5. Materials and Manufacture

5.1 *Heat Treatment*—With the exception of UNS N08936, the material shall be supplied in the solution-treated condition except as noted in 5.2. UNS N08936 shall be supplied in the cold drawn condition.

NOTE 1—The recommended heat treatment shall consist of heating to a temperature of 2010 °F to 2100 °F (1100 °C to 1150 °C) followed by water quenching for UNS N08925, UNS N08031, UNS N08034, 1975 °F to 2150 °F (1080 °C to 1180 °C) followed by water quenching or fast air cool for UNS N08354 and UNS N08926, 2010 °F to 2150 °F (1100 °C to 1180 °C) followed by water quenching or fast air cool for UNS R20033, or 1975 °F (1080 °C) minimum followed by water quenching or rapid cooling by other means for UNS N08935.

5.2 The heat treatment shall be waived for forging quality material.

6. Chemical Composition

6.1 The material sampled in accordance with 10.2 shall conform to the requirements as to chemical composition prescribed in Table 1.

6.2 *Product Analysis*—Product analysis may be made by the purchaser to verify the identity of the finished material representing each heat or lot. Such analysis may be made by any of the commonly accepted methods that will positively identify the material.

6.2.1 If a product analysis is made, the material shall conform to the product check analysis variation per Specification B880.

7. Mechanical and Other Requirements

7.1 *Tensile Requirements*—The material shall conform to the requirements as to the mechanical property prescribed in Table 2.

8. Dimensions, Weight, and Permissible Variations

8.1 *Bar*—The material referred to as bar shall conform to the variations in dimensions prescribed in Tables 3-11 inclusive, as applicable.

8.2 *Wire*—The material referred to as wire shall conform to the permissible variations in dimensions prescribed in Tables 12-16 inclusive, as applicable.

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and condition, smooth, commercially straight or flat, and free of injurious defects.

9.2 Bars in the hot-finished condition may be furnished with one of the following finishes:

- 9.2.1 Scale not removed,
- 9.2.2 Pickled or descaled, or
- 9.2.3 Turned (rounds only).

9.3 Bars in the cold-finished condition may be furnished with one of the following finishes:

- 9.3.1 Cold-drawn,
- 9.3.2 Centerless ground (rounds only), or
- 9.3.3 Polished (rounds only).

TABLE 1 Chemical Requirements^A

Element	UNS N08935	UNS N08936	UNS N08925	UNS N08031	UNS N08034	UNS N08354	UNS N08926	UNS R20033
Carbon	0.030	0.020	0.020	0.015	0.01	0.030	0.020	0.015
Manganese	1.2	4.00–6.00	1.00	2.0	1.0–4.0	1.00	2.00	2.0
Phosphorus	0.030	0.025	0.045	0.020	0.020	0.030	0.03	0.02
Sulfur	0.020	0.010	0.030	0.010	0.010	0.010	0.01	0.01
Silicon	0.5	0.50	0.50	0.3	0.1	1.00	0.5	0.50
Nickel	34.0–36.0	33.00–35.00	24.00–26.00	30.0–32.0	33.5–35.0	34.0–36.0	24.00–26.00	30.0–33.0
Chromium	26.0–28.0	26.00–28.00	19.00–21.00	26.0–28.0	26.0–27.0	22.0–24.0	19.00–21.00	31.0–35.0
Molybdenum	6.1–7.1	5.00–6.00	6.0–7.0	6.0–7.0	6.0–7.0	7.0–8.0	6.0–7.0	0.50–2.0
Copper	0.4	0.50	0.8–1.5	1.0–1.4	0.5–1.5	...	0.5–1.5	0.30–1.20
Nitrogen	0.25–0.36	0.30–0.50	0.1–0.2	0.15–0.25	0.10–0.25	0.17–0.24	0.15–0.25	0.35–0.60
Iron	balance	balance	balance	balance	balance	balance	balance	balance
Aluminum	...	...	...	...	0.3	...	...	...

^A Maximum %, unless range or minimum is indicated.