



Designation: B676 – 19 (Reapproved 2024)

Standard Specification for UNS N08367 Welded Tube¹

This standard is issued under the fixed designation B676; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers UNS N08367² welded tube for general corrosion applications.

1.2 This specification covers outside diameter and nominal wall tube.

1.2.1 The tube sizes covered by this specification are 1/8 in. to 5 in. (3.2 mm to 127 mm) in outside diameter and 0.015 in. to 0.320 in. (0.38 mm to 8.13 mm), inclusive, in wall thickness.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

A1016/A1016M Specification for General Requirements for Ferritic Alloy Steel, Austenitic Alloy Steel, and Stainless Steel Tubes

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved April 1, 2024. Published May 2024. Originally approved in 1980. Last previous edition approved in 2019 as B676 – 19. DOI: 10.1520/B0676-19R24.

² New designation established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

B751 Specification for General Requirements for Nickel and Nickel Alloy Welded Tube

B899 Terminology Relating to Non-ferrous Metals and Alloys

3. Terminology

3.1 Terms defined in Terminology **B899** shall apply unless otherwise defined in this standard.

4. General Requirement

4.1 Material furnished in accordance with this specification shall conform to the applicable requirements of Specification **B751** unless otherwise provided herein.

5. Classification

5.1 *Class 1*—Welded, cold worked, solution treated, and each piece of each lot subjected to one of the following four tests: hydrostatic, pneumatic (air underwater), eddy current, or ultrasonic.

5.2 *Class 2*—Welded, cold worked, solution treated, and each piece of each lot leak tested (hydrostatic or pneumatic) plus electric tested (eddy current or ultrasonic).

6. Ordering Information

6.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

6.1.1 Alloy name or UNS number,

6.1.2 ASTM designation and year of issue,

6.1.3 Dimensions:

6.1.3.1 Outside diameter and nominal wall thicknesses,

NOTE 1—Tube produced to outside diameter and minimum wall thickness may be furnished upon agreement between the manufacturer and the purchaser.

6.1.3.2 Length (specific or random),

6.1.4 Class (Section 5),

6.1.5 Quantity (feet or number of pieces),

6.1.6 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished, and

6.1.7 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.