



Designation: B766 – 23

Standard Specification for Electrodeposited Coatings of Cadmium¹

This standard is issued under the fixed designation B766; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the requirements for electrodeposited cadmium coatings on products of iron, steel, and other metals.

NOTE 1—Cadmium is deposited as a coating principally on iron and steel products. It can also be electrodeposited on aluminum, brass, beryllium copper, copper, nickel, and powder metallurgy parts.

1.2 The coating is provided in various thicknesses up to and including 25 μm either as electrodeposited or with supplementary finishes.

1.3 Cadmium coatings are used for corrosion resistance and for corrosion prevention of the basis metal part. The as-deposited coating (Type I) is useful for the lowest cost protection in a mild or noncorrosive environment where early formation of white corrosion products is not detrimental or harmful to the function of a component. The prime purpose of the supplementary chromate finishes (Types II and III) on the electroplated cadmium is to increase corrosion resistance. Chromating will retard or prevent the formation of white corrosion products on surfaces exposed to various environmental conditions as well as delay the appearance of corrosion from the basis metal.

1.4 Cadmium plating is used to minimize bi-metallic corrosion between high-strength steel fasteners and aluminum in the aerospace industry. Undercutting of threads on fastener parts is not necessary as the cadmium coating has a low coefficient of friction that reduces the tightening torque required and allows repetitive dismantling.

1.5 Cadmium-coated parts can easily be soldered without the use of corrosive fluxes. Cadmium-coated steel parts have a lower electrical contact resistance than zinc-coated steel. The lubricity of cadmium plating is used on springs for doors and latches and for weaving machinery operating in high humidity. Corrosion products formed on cadmium are tightly adherent. Unlike zinc, cadmium does not build up voluminous corrosion

products on the surface. This allows for proper functioning during corrosive exposure of moving parts, threaded assemblies, valves, and delicate mechanisms without jamming with debris.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following standards form a part of this document to the extent referenced herein.

2.2 *ASTM Standards:*²

A165 Specification for Electrodeposited Coatings of Cadmium on Steel (Withdrawn 1987)³

B117 Practice for Operating Salt Spray (Fog) Apparatus

B183 Practice for Preparation of Low-Carbon Steel for Electroplating

B201 Practice for Testing Chromate Coatings on Zinc and Cadmium Surfaces

B242 Guide for Preparation of High-Carbon Steel for Electroplating

B253 Guide for Preparation of Aluminum Alloys for Electroplating

B254 Practice for Preparation of and Electroplating on Stainless Steel

B281 Practice for Preparation of Copper and Copper-Base Alloys for Electroplating and Conversion Coatings

B320 Practice for Preparation of Iron Castings for Electroplating

B322 Guide for Cleaning Metals Prior to Electroplating

B343 Practice for Preparation of Nickel for Electroplating with Nickel

B374 Terminology Relating to Electroplating

¹ This specification is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.06 on Soft Metals.

Current edition approved May 1, 2023. Published May 2023. Originally approved in 1986. Last previous edition approved in 2015 as B766 – 86 (2015). DOI: 10.1520/B0766-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- B487** Test Method for Measurement of Metal and Oxide Coating Thickness by Microscopical Examination of Cross Section
- B499** Test Method for Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals
- B504** Test Method for Measurement of Thickness of Metallic Coatings by the Coulometric Method
- B507** Practice for Design of Articles to Be Electroplated on Racks
- B558** Practice for Preparation of Nickel Alloys for Electroplating
- B567** Test Method for Measurement of Coating Thickness by the Beta Backscatter Method
- B568** Test Method for Measurement of Coating Thickness by X-Ray Spectrometry
- B571** Practice for Qualitative Adhesion Testing of Metallic Coatings
- B602** Guide for Attribute Sampling of Metallic and Inorganic Coatings
- B697** Guide for Selection of Sampling Plans for Inspection of Electrodeposited Metallic and Inorganic Coatings
- B849** Specification for Pre-Treatments of Iron or Steel for Reducing Risk of Hydrogen Embrittlement
- B850** Guide for Post-Coating Treatments of Steel for Reducing the Risk of Hydrogen Embrittlement
- E8** Test Methods for Tension Testing of Metallic Materials [Metric] E0008_E0008M
- F519** Test Method for Mechanical Hydrogen Embrittlement Evaluation of Plating/Coating Processes and Service Environments
- 2.3 *Federal Standard:*
- QQ-P-416** Plating, Cadmium (Electrodeposited)⁴
- 2.4 *International Standard:*
- ISO 2082** Metallic Coatings—Electroplated Coatings of Cadmium on Iron or Steel⁵
- 2.5 *Military Standard:*
- MIL-STD-1312** Fasteners, Test Methods⁶

3. Terminology

3.1 *Definitions*—Definitions of terms used in this specification are in accordance with Terminology **B374**.

4. Classification

4.1 *Classes*—Electrodeposited cadmium coatings shall be classified on the basis of thickness as follows:

Class	Minimum Thickness, μm
25	25
12	12
8	8
5	5

NOTE 2—Cadmium coatings thicker than 12 μm are normally not economical.

⁴ Available from U.S. Government Printing Office, Washington DC 20402.

⁵ Available from American National Standards Institute, 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

4.2 *Types*—Electrodeposited cadmium coatings shall be identified by types on the basis of supplementary treatment required as follows:

4.2.1 *Type I*—As electrodeposited without supplementary treatment.

4.2.2 *Type II*—With supplementary colored chromate treatment.

4.2.3 *Type III*—With supplementary colorless chromate treatment.

NOTE 3—It is strongly recommended that production items be processed as either Type II or Type III.

5. Ordering Information

5.1 In order to make the application of this specification complete, the purchaser needs to supply the following information to the seller in the purchase order or other governing document:

5.1.1 The name, designation, and date of issue of this specification.

5.1.2 Deposit by class and type (4.1 and 4.2).

5.1.3 Composition, metallurgical condition, and tensile strength of the substrate to be coated. Application to high-strength steel parts (6.2), pretreatment (6.3) and post treatment (6.7).

5.1.4 Heat treatment for stress relief, whether it has been performed or is required (6.3).

5.1.5 Additional undercoat, if required (6.5).

5.1.6 Plating process variation, if required (6.6).

5.1.7 Exception to stress relief heat treatment prior to plating (6.3).

5.1.8 Baking requirements after plating, if any (6.7).

5.1.9 Desired color of the Type II film (6.8.2).

5.1.10 Location of significant surfaces (7.1.2).

5.1.11 Coating luster (7.5).

5.1.12 Whether non-destructive or destructive tests are to be used in cases of choice (Note 14).

5.1.13 Configuration, procedures, and tensile load for hydrogen embrittlement relief test (9.4, 10.6, Supplementary Requirements S2, and S3).

5.1.14 Whether certification is required (Section 12).

5.1.15 Whether supplementary requirements are applicable.

6. Materials and Manufacture

6.1 *Nature of Coating*—The coating shall be essentially pure cadmium produced by electrodeposition usually from an alkaline cyanide solution.

6.2 *High Tensile Strength Steel Parts*—Steel parts having an ultimate tensile strength greater than 1650 MPa (approximately 50 HRC) shall not be plated by electrodeposition unless authorized by the purchaser.

6.3 *Pretreatment of Iron or Steel for the Purpose of Reducing the Risk of Hydrogen Embrittlement*—Steel parts having an ultimate tensile strength greater than 1000 MPa (31 HRC) that contain tensile stresses caused by cold forming or cold straightening which have not been heat treated after the cold forming process, shall be heat treated for stress relief to reduce the risk of hydrogen embrittlement in the part before clean and electroplate processes. If these heat treatments are not required,