



Designation: B883 – 24

Standard Specification for Metal Injection Molded (MIM) Materials¹

This standard is issued under the fixed designation B883; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers ferrous metal injection molded materials fabricated by mixing elemental or pre-alloyed metal powders with binders, injecting into a mold, debinding, and sintering, with or without subsequent heat treatment.

1.2 This specification covers the following injection molded materials.

1.2.1 Compositions:

- 1.2.1.1 MIM-2200, low-alloy steel
- 1.2.1.2 MIM-2700, low-alloy steel
- 1.2.1.3 MIM-4605, low-alloy steel
- 1.2.1.4 MIM-4140, low-alloy steel
- 1.2.1.5 MIM-316L, austenitic stainless steel
- 1.2.1.6 MIM-17-4 PH, precipitation hardening stainless steel
- 1.2.1.7 MIM-420, martensitic stainless steel
- 1.2.1.8 MIM-430L, ferritic stainless steel
- 1.2.1.9 MIM-440, martensitic stainless steel
- 1.2.1.10 MIM-Cu, copper

1.3 Chemical composition limits are specified in [Table 1](#).

1.4 With the exception of the values for density and the mass used to determine density, for which the use of the gram per cubic centimetre (g/cm^3) and gram (g) units is the long-standing industry practice, the values in inch-pound units are to be regarded as standard. The values given in parentheses or in separate tables are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.11 on Near Full Density Powder Metallurgy Materials.

Current edition approved Feb. 1, 2024. Published February 2024. Originally approved in 1997. Last previous edition approved in 2019 as B883 – 19. DOI: 10.1520/B0883-24.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- B243 Terminology of Powder Metallurgy
- B311 Test Method for Density of Powder Metallurgy (PM) Materials Containing Less Than Two Percent Porosity
- B933 Test Method for Microindentation Hardness of Powder Metallurgy (PM) Materials
- B962 Test Methods for Density of Compacted or Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle
- E8 Test Methods for Tension Testing of Metallic Materials [Metric] E0008_E0008M
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer
- E350 Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
- E415 Test Method for Analysis of Carbon and Low-Alloy Steel by Spark Atomic Emission Spectrometry
- E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Inert Gas Fusion Techniques
- E1086 Test Method for Analysis of Austenitic Stainless Steel by Spark Atomic Emission Spectrometry
- E1461 Test Method for Thermal Diffusivity by the Flash Method

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

E1621 Guide for Elemental Analysis by Wavelength Dispersive X-Ray Fluorescence Spectrometry

F1089 Test Method for Corrosion of Surgical Instruments

2.2 *MPIF Standards*:³

MPIF Standard 35-MIM Materials Standards for Metal Injection Molded Parts

MPIF Standard 50 Method for Preparing and Evaluating Metal Injection Molded (MIM) Debound and Sintered/Heat Treated Tension Test Specimens

MPIF Standard 51 Method for Determination of Microindentation Hardness of Powder Metallurgy Materials

MPIF Standard 59 Method for Determination of Charpy Impact Energy of Unnotched Metal Injection Molded (MIM) Test Specimens

MPIF Standard 62 Method for Determination of the Corrosion Resistance of MIM Grades of Stainless Steel Immersed in 2 % Sulfuric Acid Solution

MPIF Standard 63 Method for Density Determination of Metal Injection Molded (MIM) Components (Gas Pycnometer)

3. Terminology

3.1 Definitions:

3.1.1 Definitions of powder metallurgy terms can be found in Terminology **B243**. Additional descriptive information is available in the Related Material Section of Vol. 02.05 of the Annual Book of ASTM Standards.

4. Ordering Information

4.1 Orders for parts conforming to this specification may include the following:

4.1.1 ASTM designation,

4.1.2 Alloy composition including carbon content (see **Table 1**),

4.1.3 Heat treatment condition and hardness (see **Tables 2-5**),

4.1.4 Functional or mechanical property testing (see **7.3 – 7.7** and **Tables 2-5**),

4.1.5 Corrosion resistance testing (see **8.1 – 8.1.4** and **Table 6**),

4.1.6 Thermal conductivity testing (see **9.1–9.2** and **Table 7** and **Table 8**),

4.1.7 Thermal expansion testing (see **10.1–10.2** and **Table 9** and **Table 10**),

4.1.8 Purchaser or purchaser's representative desire to witness the inspection and testing of material prior to shipment (see **12.2**),

4.1.9 Requirement for certification of material and a report of test results (see **14.1**),

4.1.10 Requirement for full or partial chemical analysis (see Section **6**), and

4.1.11 Other special requirements as mutually agreed.

5. Materials and Manufacture

5.1 Parts shall be made by injection molding mixtures of metal powder with binders, debinding, and sintering, with or

without subsequent heat treatment. The material shall conform to the designations in **1.2.1** and meet the chemical composition specified in **Table 1**.

6. Chemical Composition

6.1 Metal injection molded material shall conform to the chemical requirements prescribed in **Table 1**.

6.2 Chemical analysis for the elements copper, chromium, molybdenum, and nickel shall be determined in accordance with Test Methods **E415** (preferred method), **E350**, **E1086**, Guide **E1621**, Inductively Coupled Plasma–Atomic Emission Spectrometry (ICP–AES), Atomic Absorption (AA), or any such method as shall be agreed upon between buyer and seller. Analysis of the element carbon shall be determined in accordance with Test Methods **E1019**, via optical emission spectroscopy, or other method agreed upon between the purchaser and seller.

7. Mechanical and Physical Property Requirements

7.1 The preferred method of verifying the acceptable performance of a finished part is a qualification test to be performed on an actual part. The specific test should be determined following consideration of the function of the part, and should be agreed upon between manufacturer and purchaser.

7.2 Mandatory and typical mechanical properties of materials covered by this specification are shown in **Tables 2-10**.

7.3 Tensile Properties:

7.3.1 The tensile properties of MIM materials shall be measured using test specimens prepared and evaluated in accordance with MPIF Standard 50.

7.3.2 *Tensile Test Method*—When requested in the purchase order, tensile specimens shall be prepared and processed along with production parts. Tensile specimens shall be tested in accordance with Test Methods **E8**. Yield strength shall be determined by the 0.2 % offset method. MPIF Standard 50 governs the manufacture of the test bars, while Test Methods **E8** governs the testing procedure.

7.4 Impact Energy Properties:

7.4.1 Typical impact energy properties of materials covered by this specification are shown in **Tables 2-5**.

7.4.2 The impact energy properties of MIM materials shall be measured using test specimens prepared and evaluated in accordance with MPIF Standard 59.

7.4.3 *Impact Energy Test Method*—When requested in the purchase order, impact energy specimens shall be prepared and processed along with production parts.

7.5 Density:

7.5.1 The density of MIM materials shall be measured in accordance with Test Method **B311** or MPIF Standard 63. If a test specimen gains mass when immersed in water, it shall be tested in accordance with Test Methods **B962**.

7.6 *Apparent Hardness*—The apparent hardness of MIM materials shall be measured in accordance with Test Methods **E18**.

³ Available from Metal Powder Industries Federation (MPIF), 105 College Rd. East, Princeton, NJ 08540-6692, <http://www.mpif.org>.