



Designation: B886 – 24

Standard Test Method for Determination of Magnetic Saturation (Ms) of Cemented Carbides¹

This standard is issued under the fixed designation B886; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of magnetic saturation (Ms) of cemented carbide powder materials and sintered products using magnetic saturation induction test instrumentation.

1.2 The values stated in SI units are to be regarded as standard. An exception is the use of Gauss-cm³ per gram, which is a longstanding industry practice.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A340 Terminology of Symbols and Definitions Relating to Magnetic Testing](#)

[A977/A977M Test Method for Magnetic Properties of High-Coercivity Permanent Magnet Materials Using Hysteresisographs](#)

[B243 Terminology of Powder Metallurgy](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.06 on Cemented Carbides.

Current edition approved Feb. 1, 2024. Published February 2024. Originally approved in 1998. Last previous edition approved in 2019 as B886 – 19. DOI: 10.1520/B0886-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E1316 Terminology for Nondestructive Examinations](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definition of terms used in this procedure refer to Terminology [A340](#), Terminology [B243](#), and Terminology [E1316](#).

3.1.2 *dc*—direct current.

4. Summary of Test Method

4.1 *For Permanent Magnet Instrument*—A test specimen is statically positioned with the long axis perpendicular to the magnetic field generated by a permanent magnet and sensing coils of the test apparatus. The specimen is magnetized to induction saturation by the field and translated linearly that the intrinsic magnetic moment of the specimen's binder phase induces a dc current to flow in the sensing coils of the test apparatus. The induced current is proportional to the amount of magnetic binder phase present in the test specimen. Measurement of the induced current permits calculation of the intrinsic magnetic saturation of the test sample.

4.2 *For Electromagnet Instrument*—A test specimen is placed into a holder housing the Hall probe and sensing coils which has been positioned between the poles of the electromagnet. The magnetic field is increased while the sensing coils measure the magnetic flux of the specimen. The magnetic flux can be related to the intrinsic magnetic saturation of the test specimen.

5. Significance and Use

5.1 This test method allows the nondestructive measurement of the magnetic fraction of the binder phase in cemented carbide powder materials and sintered product, and may be used as an indirect measure of the carbon level in the material or product.

5.2 Measurement of magnetic saturation provides a comparison of the relative fraction of magnetic binder phase, that is, cobalt, nickel, or iron, present in the material and can be used for acceptance of product to specification.

5.3 Measurement of magnetic saturation can be used as a measure of the quality of powder material.

*A Summary of Changes section appears at the end of this standard