



Designation: B899 – 21

## Standard Terminology Relating to Non-ferrous Metals and Alloys<sup>1</sup>

This standard is issued under the fixed designation B899; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 To promote precise understanding and interpretation of standards, reports, and other technical writings promulgated by Committee B02.

1.2 To standardize the terminology used in these documents.

1.3 To explain the meanings of technical terms used within these documents for those not conversant with them.

1.4 Some definitions include a *discussion* section, which is a mandatory *part* of the definition and contains additional information that is relevant to the meaning of the defined term.

1.5 Definitions of terms specific to a particular standard will appear in that standard and will supersede any definitions of identical terms in this standard.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Significance and Use

2.1 The terms defined in this document are generic in respect to the standards under the jurisdiction of Committee B02 on Nonferrous Metals and Alloys. The same terms may have different definitions in other ASTM technical committees.

2.2 Some definitions may differ within the committee because of limitations on items such as weights or dimensions. In such cases the terms will be more precisely defined in the *Terminology* section of the standards in which these terms are used.

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.91 on Terminology.

Current edition approved Nov. 1, 2021. Published December 2021. Originally approved in 1999. Last previous edition approved in 2018 as B899 – 18. DOI: 10.1520/B0899-21.

### 3. Terminology

#### General Nonferrous Metals and Alloys

##### 3.1 Terms and Their Definitions:

**bar**, *n*—an elongated, forged or rolled metal product with uniform strength, length and section (such as rectangular, square, round, oval or hexagonal).

DISCUSSION—The term “bar” may have a similar definition, but with greater and more specific detail in the product standard.

**billet**, *n*—a formed shape that may be further worked, or a solid, semifinished, round, or rectangular product that has been hot-worked by forging, rolling, or extrusion.

**ellipsis**, *n*—in a tabular entry, three periods (...) that indicate that there is no requirement.

**heat**, *n*—refer to **melt**.

**ingot**, *n*—a casting of simple shape suitable for hot-working or remelting.

**liquidus**, *n*—the lowest temperature at which an alloy under equilibrium conditions begins to freeze on cooling or is completely melted on heating.

**lot**, *n*—a quantity of metal made under conditions that, for sampling purposes, are considered uniform.

**lot number**, *n*—a unique alphanumeric designation for a lot that is traceable to manufacturing records.

**melt**, *n*—all the metal that, while molten, was held at the same time in the same holding vessel.

**nonferrous material**, *n*—metals and alloys that do not contain iron as the principal component.

DISCUSSION—The iron content is not always stated in the specification and is not always determined by chemical analysis. The iron content may be taken to be 100 % minus the sum of the mean values permitted by the specification for all other elements having a specified range or a specified maximum. For conformance purposes, the mean value for iron, whether specified or calculated, is compared on an individual basis to the mean values permitted by the specification for each of the other elements having a specified range or a specified maximum. If an element other than iron is not specified, but is listed as remainder or balance, then, for conformance purposes the mean value for iron is compared to the calculated value for that other element.

**plate**, *n*—a flat-rolled metal product of same minimum thickness and width arbitrarily dependent on the type of metal.

\*A Summary of Changes section appears at the end of this standard

**producer**, *n*—the primary manufacturer of the material.

**sheet**, *n*—a flat-rolled metal product of some maximum thickness and minimum width arbitrarily dependent on the type of metal; it is thinner than plate.

**solidus**, *n*—the highest temperature at which under equilibrium conditions an alloy begins to melt on heating or is completely solid on cooling.

**sponge**, *n*—a form of metal characterized by a porous condition that is the result of decomposition or reduction of a compound without fusion.

**strip**, *n*—a flat-rolled metal product of some maximum thickness and width arbitrarily dependent on the type of metal, it is narrower than sheet.

**test report**, *n*—a document that presents the applicable qualitative or quantitative results obtained by applying one or more given test methods.

DISCUSSION—A single document, containing test report information and certificate of compliance information, may be used.

**wire**, *n*—a thin, flexible continuous length of metal, usually of uniform, round cross section.

## Refined Lead, Tin, Antimony, and Their Alloys

### 3.2 Terms and Their Definitions:

**pig**, *n*—an oblong or square mass of metal that has been cast while still molten into a mold that gives the metal its particular shape; most commonly used for lead and tin in weights that can be handled manually.

## Zinc and Cadmium

### 3.3 Terms and Their Definitions:

**alloy composition**, *n*—the composition is identified by a two or four-letter symbol and number. The letters typically indicate the chemical symbol for the critical element in the solder and the number indicates the nominal percentage, by weight, of the critical element in the solder.

**brightener bar**, *n*—brightener bar is a zinc alloy containing aluminum which is added to the galvanizing bath to adjust the aluminum content of the bath to: suppress the formation of iron-zinc alloy layers, increase the brightness and ductility of the galvanized coating, and improve the drainage of zinc from the work as it exits the bath; also called brightener.

**cathodic protection**, *n*—protection of a metal from corrosion by making it a cathode through the galvanic sacrifice of a less noble metal or through an impressed electric current.

**coiled sheet**, *n*—sheet in coils with slit edges.

**color code**, *n*—code to follow the quick identification of ingots.

**die casting**, *n*—a casting process in which molten metal is injected under high velocity and pressure into a metal die and solidified; also, a product produced by such a process; alternately known as pressure die casting.

**flat sheet**, *n*—sheet with sheared, silt, or sawed edges that has been flattened or leveled.

**foundry casting**, *n*—a casting process wherein a molten metal is poured by gravity into the cavity of a mold and solidified; also, a product of such a process.

**galvanic anode**, *n*—a metal electrode that sacrificially corrodes when coupled to a more noble metal in a conducting medium, thereby supplying a protective electric current to the more noble electrode.

**graphite permanent mold casting**, *n*—a metal object produced by introducing molten metal by gravity or low pressure into a graphite mold and allowing it to solidify.

**hardener**, *n*—an aluminum-base master alloy added to Special High Grade Zinc (SHG) to produce a zinc alloy for die casting.

**high fluidity alloy**, *n*—a zinc alloy by nature of its composition is capable of producing die castings with thinner wall sections compared to typical die cast alloys, often less than 0.012 in. (0.30 mm) in thickness.

**permanent mold casting**, *n*—a metal object produced by introducing molten metal by gravity or low pressure into a mold constructed of durable material, usually iron or steel, and allowing it to solidify. See also graphite permanent mold casting.

**pressure die-casting**, *n*—same as die casting.

**ribbon anode**, *n*—a long, continuous sacrificial anode shape, with a diamond, square, rectangular, oval, or other cross-section, most commonly made of zinc, magnesium or aluminum, having a core wire normally made of steel, that is, usually supplied in coils or reels of 100 to 3600 ft depending upon size and cross-section.

**saline electrolyte**, *n*—a solution customarily consisting of the chlorides of the alkali metals.

**shot**, *n*—small spherically shaped particles of metal.

**spin casting**, *n*—a casting process in which molten metal is poured into a rubber, polymer, graphite or metal mold and spun centrifugally until solidified, also a product produced by such a process.

**type 5**, *n*—95 % zinc-5 % aluminum.

**type 10**, *n*—90 % zinc-10 % aluminum.

**type 15**, *n*—85 % zinc-15 % aluminum.

### 3.4 Abbreviations:

**CGG**—continuous galvanizing grade zinc.

**HG**—High Grade Zinc.

**MM**—mischmetal.

**PW**—Prime Western Zinc.

**SHG**—Special High Grade Zinc.

**UNS**—Unified Numbering System.