



Designation: C1059/C1059M – 24

Standard Specification for Latex Agents for Bonding Fresh To Hardened Concrete¹

This standard is issued under the fixed designation C1059/C1059M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers latex bonding agents, suitable for brush, broom, or spray application, to bond fresh concrete to hardened concrete.

1.2 These latex bonding agents are intended for bonding new concrete to old concrete such as interior surfaces, floors, roadways, bridge decks, ramps, runways, walks, and curbs.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.4 The text of this specification refers to notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C125 Terminology Relating to Concrete and Concrete Aggregates

C882/C882M Test Method for Bond Strength of Bonding Systems Used With Concrete By Slant Shear

3. Terminology

3.1 Definitions:

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.25 on Organic Materials for Bonding.

Current edition approved Oct. 1, 2024. Published October 2024. Originally approved in 1986. Last previous edition approved in 2021 as C1059/C1059M – 21. DOI: 10.1520/C1059_C1059M-24.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 For definitions of terms used in this specification, refer to Terminology **C125**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bond strength, n*—a measure of the force required to separate surfaces that have been bonded together.

3.2.2 *bonding agent, n*—a couplant that physically attaches one material surface to another.

3.2.3 *latex, n*—a stable dispersion of polymeric substance in an essentially aqueous medium.

4. Classification

4.1 This specification provides for the classification of the latex bonding agents in accordance with use.

4.1.1 *Type I (Redispersable)*, is restricted for use in interior work not subject to water immersion or high humidity.

4.1.2 *Type II (Non-redispersable)*, may be used for areas subject to high humidity or immersion in water and is suitable for use in other areas.

5. Ordering Information

5.1 Purchase orders for these materials shall identify:

5.1.1 The number of this specification and the required type, and

5.1.2 Supplementary requirements if necessary.

6. Physical Properties

6.1 The material shall conform to the requirements of **Table 1** when tested in accordance with Test Method **C882/C882M**, for latex bonding agents, Type I (Redispersible) and Type II (Non-redispersible) materials.

7. Sampling

7.1 For sampling of bulk quantities, a batch or lot shall be considered a unit of manufacture as prepared for shipment or may consist of a blend of two or more production runs of material. A composite sample shall be taken and it shall provide a volume of at least 4 L [1 gal].

7.2 When the latex bonding agent to be sampled is in containers, the sample shall be obtained by taking a portion out of the containers that is equal in number to the next integer larger than the cube root of the total number of containers in the lot. Grab samples shall be taken from each container and they shall have a volume of at least 0.25 L [0.5 pt.].

*A Summary of Changes section appears at the end of this standard