



Designation: C1468 – 19a (Reapproved 2026)

Standard Test Method for Transthickness Tensile Strength of Continuous Fiber- Reinforced Advanced Ceramics at Ambient Temperature¹

This standard is issued under the fixed designation C1468; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of transthickness tensile strength (S_{Tl}^*) under monotonic uniaxial tensile loading of continuous fiber-reinforced ceramics (CFCC) at ambient temperature. This test method addresses, but is not restricted to, various suggested test specimen geometries, test fixtures, data collection, and reporting procedures. In general, round or square test specimens are tensile tested in the direction normal to the thickness by bonding appropriate hardware to the samples and performing the test. For a Cartesian coordinate system, the x -axis and the y -axis are in the plane of the test specimen. The transthickness direction is normal to the plane and is labeled the z -axis for this test method. For CFCCs, the plane of the test specimen normally contains the larger of the three dimensions and is parallel to the fiber layers for unidirectional, bidirectional, and woven composites. Note that transthickness tensile strength as used in this test method refers to the tensile strength obtained under monotonic uniaxial tensile loading, where “monotonic” refers to a continuous nonstop test rate with no reversals from test initiation to final fracture.

1.2 This test method is intended primarily for use with all advanced ceramic matrix composites with continuous fiber reinforcement: unidirectional (1D), bidirectional (2D), woven, and tridirectional (3D). In addition, this test method also may be used with glass (amorphous) matrix composites with 1D, 2D, and 3D continuous fiber reinforcement. This test method does not directly address discontinuous fiber-reinforced, whisker-reinforced, or particulate-reinforced ceramics, although the test methods detailed here may be equally applicable to these composites. It should be noted that 3D architectures with a high volume fraction of fibers in the “ z ” direction may be difficult to test successfully.

1.3 Values are in accordance with the International System of Units (SI) and [IEEE/ASTM SI 10](#).

¹ This test method is under the jurisdiction of ASTM Committee C28 on Advanced Ceramics and is the direct responsibility of Subcommittee C28.07 on Ceramic Matrix Composites.

Current edition approved June 1, 2026. Published June 2026. Originally approved in 2000. Last previous edition approved in 2019 as C1468 – 19a. DOI: 10.1520/C1468-19AR26.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Additional recommendations are provided in [6.7](#) and Section [7](#).

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C1145](#) Terminology of Advanced Ceramics

[C1239](#) Practice for Reporting Uniaxial Strength Data and Estimating Weibull Distribution Parameters for Advanced Ceramics

[C1275](#) Test Method for Monotonic Tensile Behavior of Continuous Fiber-Reinforced Advanced Ceramics with Solid Rectangular Cross-Section Test Specimens at Ambient Temperature

[C1468](#) Test Method for Transthickness Tensile Strength of Continuous Fiber-Reinforced Advanced Ceramics at Ambient Temperature

[D3878](#) Terminology for Composite Materials

[E4](#) Practices for Force Calibration and Verification of Testing Machines

[E6](#) Terminology Relating to Methods of Mechanical Testing

[E177](#) Practice for Use of the Terms Precision and Bias in ASTM Test Methods

[E337](#) Test Method for Measuring Humidity with a Psychrometer (the Measurement of Wet- and Dry-Bulb Temperatures)

[E691](#) Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E1012 Practice for Verification of Testing Frame and Specimen Alignment Under Tensile and Compressive Axial Force Application
IEEE/ASTM SI 10 American National Standard for Metric Practice

3. Terminology

3.1 Definitions:

3.1.1 The definitions of terms relating to tensile testing appearing in Terminology E6 apply to the terms used in this test method. The definitions of terms relating to advanced ceramics appearing in Terminology C1145 apply to the terms used in this test method. The definitions of terms relating to fiber-reinforced composites appearing in Terminology D3878 apply to the terms used in this test method. Pertinent definitions as listed in Practice E1012 and Terminologies C1145, D3878, and E6 are shown in the following with the appropriate source given in brackets. Terms used in conjunction with this test method are defined as follows:

3.1.2 *advanced ceramic*, *n*—a highly engineered, high-performance, predominately nonmetallic, inorganic, ceramic material having specific functional attributes. **C1145**

3.1.3 *bending strain* [LL^{-1}], *n*—the difference between the strain at the surface and the axial strain. **E1012**

3.1.4 *breaking force* [F], *n*—the force at which fracture occurs, P_{max} is the breaking force in units of N. **E6**

3.1.5 *ceramic matrix composite (CMC)*, *n*—a material consisting of two or more materials (insoluble in one another), in which the major, continuous component (matrix component) is a ceramic, while the secondary component(s) (reinforcing component) may be ceramic, glass-ceramic, glass, metal, or organic in nature. These components are combined on a macroscale to form a useful engineering material possessing certain properties or behavior not possessed by the individual constituents. **C1145**

3.1.6 *continuous fiber-reinforced ceramic matrix composite (CFCC)*, *n*—a ceramic matrix composite in which the reinforcing phase consists of continuous filaments, fibers, yarn, or knitted or woven fabrics. **C1145**

3.1.7 *gauge length* [L], *n*—the original length [L_{GL}] of that portion of the test specimen over which strain or change of length is determined. **E6**

3.1.8 *modulus of elasticity* [FL^{-2}], *n*—the ratio of stress to corresponding strain below the proportional limit. **E6**

3.1.9 *percent bending*, *n*—the bending strain times 100 divided by the axial strain. **E1012**

3.1.10 *tensile strength* [FL^{-2}], *n*—the maximum tensile stress which a material is capable of sustaining. Tensile strength is calculated from the maximum force during a tension test carried to rupture and the original cross-sectional area of the test specimen. **E6**

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *fixturing*, *n*—fixturing is referred to as the device(s) bonded to the test specimen. It is this device(s) that is actually gripped or pinned to the load train. The fixturing transmits the applied force to the test specimen.

3.2.2 *transthickness*, *n*—the direction parallel to the thickness, that is, out-of-plane dimension, as identified in 1.1, and also typically normal to the plies for 1D, 2D laminate, and woven cloth. For 3D laminates, this direction is typically taken to be normal to the thickness and associated with the “z” direction.

4. Significance and Use

4.1 This test method may be used for material development, material comparison, quality assurance, characterization, and design data generation.

4.2 Continuous fiber-reinforced ceramic matrix composites generally are characterized by glass or fine grain-sized (<50 μm) ceramic matrices and ceramic fiber reinforcements. CFCCs are candidate materials for high-temperature structural applications requiring high degrees of corrosion and oxidation resistance, wear and erosion resistance, and inherent damage tolerance, that is, toughness. In addition, continuous fiber-reinforced glass (amorphous) matrix composites are candidate materials for similar but possibly less demanding applications. Although shear test methods are used to evaluate shear interlaminar strength (τ_{ZX} , τ_{ZY}) in advanced ceramics, there is significant difficulty in test specimen machining and testing. Improperly prepared notches can produce nonuniform stress distribution in the shear test specimens and can lead to ambiguity of interpretation of strength results. In addition, these shear test specimens also rarely produce a gauge section that is in a state of pure shear. Uniaxially forced transthickness tensile strength tests measure the tensile interlaminar strength (S_{TL}^T), avoid the complications listed above, and provide information on mechanical behavior and strength for a uniformly stressed material. The ultimate strength value measured is not a direct measure of the matrix strength, but a combination of the strength of the matrix and the level of bonding between the fiber, fiber/matrix interphase, and the matrix.

4.3 CFCCs tested in a transthickness tensile test (TTT) may fail from a single dominant flaw or from a cumulative damage process; therefore, the volume of material subjected to a uniform tensile stress for a single uniaxially forced TTT may be a significant factor in determining the ultimate strength of CFCCs. The probabilistic nature of the strength distributions of the brittle matrices of CFCCs requires a sufficient number of test specimens at each testing condition for statistical analysis and design, with guidelines for test specimen size and sufficient numbers provided in this test method. Studies to determine the exact influence of test specimen volume on strength distributions for CFCCs have not been completed. It should be noted that strengths obtained using other recommended test specimens with different volumes and areas may vary due to these volume differences.

4.4 The results of TTTs of test specimens fabricated to standardized dimensions from a particular material, or selected portions of a part, or both, may not totally represent the strength and deformation properties of the entire full-size end product or its in-service behavior in different environments.

4.5 For quality control purposes, results derived from standardized TTT specimens may be considered indicative of the