



Designation: C1691 – 21

Standard Specification for Unreinforced Autoclaved Aerated Concrete (AAC) Masonry Units¹

This standard is issued under the fixed designation C1691; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers solid, unreinforced masonry units manufactured from autoclaved aerated concrete (AAC), a cementitious product. This specification addresses dimensional tolerances, maximum limits for drying shrinkage, and shipping and handling.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C1232 Terminology for Masonry

C1693 Specification for Autoclaved Aerated Concrete (AAC)

3. Terminology

3.1 **Definitions**—Terms defined in Terminology C1232 shall apply in this specification.

¹ This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.10 on Autoclaved Aerated Concrete Masonry Units.

Current edition approved Dec. 1, 2021. Published December 2021. Originally approved in 2009. Last previous edition approved in 2017 as C1391 – 11(2017). DOI: 10.1520/C1691-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Classification

4.1 AAC masonry units manufactured in accordance with this specification shall be classified according to their strength class as specified in Specification C1693—AAC2, AAC3, AAC4, AAC5, or AAC6.

NOTE 1—Typically, classes AAC2, AAC4, and AAC6 are predominantly used in masonry construction. Contact manufacturers for the availability of all classes.

5. Materials and Manufacture

5.1 AAC masonry units manufactured in accordance with this specification shall be composed entirely of AAC material conforming to Specification C1693.

6. Physical Requirements

6.1 **Compressive Strength**—The compressive strength of the units shall be determined according to Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are classified.

6.2 **Dry Bulk Density**—The dry bulk density shall be determined according to Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are classified.

6.3 **Drying Shrinkage**—The drying shrinkage shall be determined in accordance with Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are specified.

7. Dimensions and Permissible Variations

7.1 The specified dimensions of the units shall be established by the AAC unit manufacturer.

7.2 No overall unit dimension (width, height, or length) shall differ by more than 1/8 in. (3 mm) from the corresponding specified dimension

8. Visual Inspection

8.1 All units shall be sound and free of defects that would interfere with the proper placing of the unit or impair the strength or permanence of the construction. Minor imperfections incidental to the usual methods of manufacture, or

*A Summary of Changes section appears at the end of this standard