



Designation: C1846/C1846M – 19 (Reapproved 2024)

Standard Specification for Performance Based Manufacture of Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe¹

This standard is issued under the fixed designation C1846/C1846M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This performance based specification covers reinforced concrete pipe intended to be used for the conveyance of sewage, industrial wastes, and storm water, and for the construction of culverts.

1.2 It is not the intention of this standard to dictate the material quantities and properties required for a pipe to conform to this standard except those in Section 6. Specific product formulations shall be considered proprietary and allowed to remain confidential to the manufacturer.

NOTE 1—This specification is a manufacturing and purchase specification only, and does not include requirements for bedding, backfill, or the relationship between field load condition and the strength classification of pipe. However, experience has shown that the successful performance of this product depends upon the proper selection of the class of pipe, type of bedding and backfill, and care that installation conforms to the construction specifications. The owner of the reinforced concrete pipe specified herein is cautioned that he must correlate the field requirements with the class of pipe specified and provide inspection at the construction site.

NOTE 2—Attention is called to the specification for Reinforced Concrete D-load Culvert, Storm Drain, and Sewer Pipe (Specification C655). The distinction between this specification and C655 is in the D-Load specified and the practice for sampling pipe for conformance to the specification. This specification relies on standard classes of pipe (Class I-V), and sampling in accordance with Section 11.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:

- A36/A36M Specification for Carbon Structural Steel
- A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement
- A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete
- C33/C33M Specification for Concrete Aggregates
- C76 Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe
- C76M Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe (Metric)
- C150/C150M Specification for Portland Cement
- C260/C260M Specification for Air-Entraining Admixtures for Concrete
- C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete
- C443 Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets
- C494/C494M Specification for Chemical Admixtures for Concrete
- C497 Test Methods for Concrete Pipe, Concrete Box Sections, Manhole Sections, or Tile
- C595/C595M Specification for Blended Hydraulic Cements
- C618 Specification for Coal Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C655 Specification for Reinforced Concrete D-Load Culvert, Storm Drain, and Sewer Pipe
- C822 Terminology Relating to Concrete Pipe and Related Products
- C989/C989M Specification for Slag Cement for Use in Concrete and Mortars
- C990/C990M Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.02 on Reinforced Sewer and Culvert Pipe.

Current edition approved April 1, 2024. Published April 2024. Originally approved in 2017. Last previous edition approved in 2019 as C1846/C1846M – 19. DOI: 10.1520/C1846_C1846M-19R24.

C1017/C1017M Specification for Chemical Admixtures for Use in Producing Flowing Concrete (Withdrawn 2022)²
C1116/C1116M Specification for Fiber-Reinforced Concrete
C1157/C1157M Performance Specification for Hydraulic Cement
C1602/C1602M Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete
C1628 Specification for Joints for Concrete Gravity Flow Sewer Pipe, Using Rubber Gaskets
2.2 AASHTO Standards:
R073 Standard Practice for Evaluation of Precast Concrete Drainage Products

3. Terminology

3.1 Definitions—For definitions of terms relating to concrete pipe, see Terminology **C822**.

3.2 Definitions:

3.2.1 D_{design} n —the D-load test criteria required to reach the design strength as defined in Test Methods **C497**.

4. Classification

4.1 Pipe furnished under this specification shall be designated as Class I, II, III, IV, or V. The corresponding strength requirements are prescribed in **Table 1**. Special designs for pipe strengths not designated in **Table 1** are permitted provided all other requirements of this specification are met. For Pipe Classes of IV or less, the minimum ratio of the D_{Ult} to D_{design} in the three-edge-bearing test shall be 1.5 rounded to the nearest 50 lb/ft² [5 N/m²]. For Class V pipe, or higher, the minimum ratio of D_{Ult} to D_{design} in the three-edge-bearing test shall be 1.25. A linear interpolation may be performed to establish the D_{Ult} to D_{design} ratio for Pipe Classes between Class IV and V.

5. Basis of Acceptance

5.1 Acceptance on the Basis of Proof of Design Tests, Plant Load-Bearing Tests, Material Tests, and Inspection of Manufactured Pipe for Visual Defects and Imperfections—Acceptability of the pipe in all diameters and classes shall be determined by the results of the three-edge-bearing tests as defined in Section 11 and 12.3.1; by such material tests as are required in 6.2, 6.3, 6.5, 6.6, and 6.7; by an absorption test of the concrete from the wall of the pipe as required in 12.4; and by visual inspection of the finished pipe to determine its

conformance with the accepted design and its freedom from defects in accordance with Section 15.

5.2 Age for Acceptance—Pipe shall be considered ready for acceptance when it conforms to the requirements as indicated by the specified tests.

6. Materials

6.1 Reinforced Concrete—The reinforced concrete shall consist of cementitious materials; mineral aggregates; admixtures, if used; and water in which steel has been embedded in such a manner that the steel and concrete act together.

6.2 Cementitious Materials:

6.2.1 Cement—Cement shall conform to the requirements of Specification **C150/C150M** or **C1157/C1157M**, or shall be blended cement conforming to the requirements of Specification **C595/C595M**.

6.2.2 Slag Cement—Slag cement shall conform to the requirements of Grade 100 or 120 of Specification **C989/C989M**.

6.2.3 Fly Ash—Fly ash shall conform to the requirements of Class F or Class C of Specification **C618**.

6.2.4 Allowable Combinations of Cementitious Materials—Any combination of cementitious materials shall be acceptable for use in the concrete if the mix meets the testing requirements in this specification:

6.3 Aggregates—Aggregates shall conform to Specification **C33/C33M** except that the requirement for gradation shall not apply.

6.4 Admixtures—The following admixtures and blends are allowable:

6.4.1 Air-entraining admixture conforming to Specification **C260/C260M**;

6.4.2 Chemical admixture conforming to Specification **C494/C494M**;

6.4.3 Chemical admixture for use in producing flowing concrete conforming to Specification **C1017/C1017M**; and

6.4.4 Chemical admixture or blend approved by the owner.

6.5 Steel Reinforcement—Reinforcement shall consist of wire or welded wire conforming to Specification **A1064/A1064M**, or of bars conforming to Specification **A36/A36M**, Specification **A615/A615M**, Grade 40 or 60, or Specification **A706/A706M**, Grade 60. For helically wound cages only, weld shear tests are not required.

6.6 Fibers—Synthetic fibers and nonsynthetic fibers shall be allowed to be used, at the manufacturer's option, in concrete pipe as a nonstructural manufacturing material. Synthetic fibers (Type II and Type III) and nonsynthetic fiber (Type I) designed and manufactured specifically for use in concrete and conforming to the requirements of Specification **C1116/C1116M** shall be accepted.

6.7 Water—Water used in the production of concrete shall be potable or nonpotable water that meets the requirements of Specification **C1602/C1602M**.

7. Pipe Performance

7.1 The pipe shall be formulated sufficiently to pass the D_{Ult} and D_{design} requirements in **Table 1**.

² The last approved version of this historical standard is referenced on www.astm.org.

TABLE 1

Pipe Class	D_{design} (lbs/linear foot/foot of diameter) [N/linear m/mm of diameter]	D_{Ult} (lbs/linear foot/foot of diameter) [N/linear m/mm of diameter]
I	800 [40.0]	1200 [60.0]
II	1000 [50.0]	1500 [75.0]
III	1350 [65.0]	2000 [100.0]
IV	2000 [100.0]	3000 [150.0]
V	3000 [140.0]	3750 [175.0]