



Designation: C568/C568M – 22

Standard Specification for Limestone Dimension Stone¹

This standard is issued under the fixed designation C568/C568M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of limestone for general building and structural purposes. Refer to Guides [C1242](#) and [C1528](#) for the appropriate selection and use of limestone dimension stone.

1.2 Dimension limestone shall include stone that is sawed, cut, split, or otherwise finished or shaped and shall specifically exclude molded, cast, or otherwise artificially aggregated units of composed fragments, and also crushed and broken stone.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[C97/C97M](#) Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone

[C99/C99M](#) Test Method for Modulus of Rupture of Dimension Stone

[C119](#) Terminology Relating to Dimension Stone

[C170/C170M](#) Test Method for Compressive Strength of Dimension Stone

[C241/C241M](#) Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic

[C1242](#) Guide for Selection, Design, and Installation of Dimension Stone Attachment Systems

[C1353](#) Test Method for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic Using a Rotary Platform Abraser

[C1528](#) Guide for Selection of Dimension Stone

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology [C119](#).

4. Classification

4.1 Dimension limestone shall be classified into three categories, generally descriptive of those limestones having densities in approximate ranges, as follows:

4.1.1 *I (Low-Density)*—Limestone having a density ranging from 110 through 135 lb/ft³ [1760 through 2160 kg/m³].

4.1.2 *II (Medium-Density)*—Limestone having a density greater than 135 and not greater than 160 lb/ft³ [2160 through 2560 kg/m³].

4.1.3 *III (High-Density)*—Limestone having a density greater than 160 lb/ft³ [2560 kg/m³].

5. Physical Requirements

5.1 Limestone supplied under this specification shall conform to the physical requirements listed in [Table 1](#).

5.2 Limestone shall be sound, durable, and free of spalls, cracks, open seams, pits, or other defects that are likely to impair its structural integrity in its intended use.

5.3 The desired color and texture, with their permissible natural variations in material characteristics for all material to be produced for the project, shall be established by control samples. Select representative samples by viewing a sufficient number of physical samples prior to production that show the complete range of variations in color and texture of the limestone specified.

6. Sampling

6.1 Samples, if required, for testing to determine the characteristics and physical properties shall be representative of the limestone to be used.

¹ This specification is under the jurisdiction of ASTM Committee [C18](#) on Dimension Stone and is the direct responsibility of Subcommittee [C18.03](#) on Material Specifications.

Current edition approved Aug. 1, 2022. Published September 2022. Originally approved in 1965. Last previous edition approved in 2015 as C568/C568M – 15. DOI: 10.1520/C0568_C0586M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.