



Designation: C610 – 17 (Reapproved 2023)

Standard Specification for Molded Expanded Perlite Block and Pipe Thermal Insulation¹

This standard is issued under the fixed designation C610; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers molded expanded perlite block, fittings, and pipe thermal insulation intended for use on surfaces with temperatures between 80 to 1200°F (27 to 649°C).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- C165** Test Method for Measuring Compressive Properties of Thermal Insulations
- C168** Terminology Relating to Thermal Insulation
- C177** Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C203** Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation

- C302** Test Method for Density and Dimensions of Preformed Pipe-Covering-Type Thermal Insulation
- C303** Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation
- C335/C335M** Test Method for Steady-State Heat Transfer Properties of Pipe Insulation
- C356** Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat
- C390** Practice for Sampling and Acceptance of Thermal Insulation Lots
- C411** Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation
- C421** Test Method for Tumbling Friability of Preformed Block-Type and Preformed Pipe-Covering-Type Thermal Insulation
- C450** Practice for Fabrication of Thermal Insulating Fitting Covers for NPS Piping, and Vessel Lagging
- C518** Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- C585** Practice for Inner and Outer Diameters of Thermal Insulation for Nominal Sizes of Pipe and Tubing
- C795** Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel
- C1045** Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions
- C1058/C1058M** Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation
- C1616** Test Method for Determining the Moisture Content of Organic and Inorganic Insulation Materials by Weight
- C1617** Practice for Quantitative Accelerated Laboratory Evaluation of Extraction Solutions Containing Ions Leached from Thermal Insulation on Aqueous Corrosion of Metals
- C1763** Test Method for Water Absorption by Immersion of Thermal Insulation Materials
- E84** Test Method for Surface Burning Characteristics of Building Materials
- E136** Test Method for Assessing Combustibility of Materials Using a Vertical Tube Furnace at 750 °C

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.20 on Homogeneous Inorganic Thermal Insulations.

Current edition approved March 1, 2023. Published March 2023. Originally approved in 1967. Last previous edition approved in 2017 as C610 – 17. DOI: 10.1520/C0610-17R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions*—For definitions of general terms related to thermal insulation used in this specification, refer to Terminology **C168**.

4. Standard Shapes, Sizes, and Dimensions

4.1 Molded expanded perlite block, fitting, and pipe thermal insulation shall be as follows:

4.1.1 *Block*—Block shall be furnished in lengths of either 36 or 39.4 in. (914 or 1000 mm), widths of 6 in. (152 mm), 12 in. (305 mm), 18 in. (457 mm), or 24 in. (610 mm), and in thickness from 1½ to 6 in. (38 to 152 mm) in increments of ½ in. (13 mm).

4.1.2 *Pipe Insulation*—Molded expanded perlite pipe insulation shall be supplied either as hollow cylindrical shapes split in half lengthwise (in a plane including the cylindrical axis) or curved segments. The pipe insulation shall be furnished in sections or segments in lengths of either 36 or 39.4 in. (914 or 1000 mm) to fit standard sizes of pipe and tubing, and in nominal thickness from 1 to 4 in. (25 to 102 mm) in ½-in. (13-mm) increments. Inner and outer diameters of multilayer construction shall be specified. Inner and outer diameters shall be in accordance with those standard dimensions specified in Practice **C585**. Since outside diameter tolerances differ between individual manufacturing processes, it is acceptable to have pipe insulation furnished in two or more layers nested by the manufacturer. The purchaser shall consult the manufacturer for specific requirements.

4.1.3 *Fittings*—Molded (expanded insulation fittings shall conform to the inner and outer diameters in accordance with Practice **C585**. Mitered fittings shall be in accordance with Practice **C450**.

5. Description

5.1 *Composition*—molded expanded perlite block, fitting, and pipe thermal insulation shall be composed principally of expanded perlite and silicate binders may contain reinforcing fibers.

6. Dimensional Tolerances

6.1 *General*—The average tolerances for length, width, and thickness shall comply with the requirements shown in **Table 1**.

6.2 *Pipe Insulation*—The following additional tolerances apply to perlite pipe insulation supplied as half sections:

6.2.1 *Fit and Closure*—When fitted to the appropriate size pipe, the longitudinal seam of the pipe insulation shall close to within ¼ in. (1.6 mm) along the entire length of the section.

TABLE 1 Dimensional Tolerances

	Block	Pipe
Length	± ⅛ in. (3.2 mm)	± ⅛ in. (3.2 mm)
Width	± ⅛ in. (3.2 mm)	...
Thickness	± ⅛ in. (3.2 mm)	± ⅛ in. (3.2 mm)
Inner Diameter	...	in accordance with Practice C585
Outer Diameter	...	in accordance with Practice C585

6.2.2 *Concentricity*—The inner bore of the pipe insulation shall be concentric with the outer cylindrical surface. The deviation from concentricity shall not exceed ⅛ in. (3.2 mm) or 5 % of the wall thickness, whichever is greater.

6.2.3 *Half-Section Balance*—The plane formed by the split between half sections shall include the cylindrical axis. Deviation of the split plane from the cylinder axis over the 36 or 39.4-in. (914 or 1000-mm) length shall not exceed ⅛ in. (3.2 mm).

7. Workmanship, Finish, and Appearance

7.1 Since some requirements for this material are not easily defined by a numerical value, the insulation shall not have visible defects that will adversely affect its service qualities.

8. Physical Requirements

8.1 The insulation shall conform to the physical requirements in **Table 2**.

9. Sampling

9.1 The insulation shall be sampled in accordance with Practice **C390**. Specific provision for sampling shall be agreed upon between the purchaser and the supplier.

10. Qualification Requirements

10.1 The following requirements are generally employed for purpose of initial material or product qualification:

- 10.1.1 Flexural strength,
- 10.1.2 Compressive resistance,
- 10.1.3 Surface burning characteristics,
- 10.1.4 Linear shrinkage after soaking heat,
- 10.1.5 Water absorption after heat aging,
- 10.1.6 Apparent thermal conductivity,
- 10.1.7 Hot-surface performance,
- 10.1.8 Stress corrosion cracking of austenitic stainless steel,
- 10.1.9 Weight loss by tumbling,
- 10.1.10 Mass loss corrosion rate, and
- 10.1.11 Combustibility.

11. Acceptance Requirements

11.1 The following requirements are generally employed for purposes of acceptance sampling of lots or shipments of qualified products:

- 11.1.1 Density,
- 11.1.2 Dimensions,
- 11.1.3 Workmanship, and
- 11.1.4 Moisture content.

12. Test Methods

12.1 The properties enumerated in this specification shall be determined in accordance with the following test methods:

- 12.1.1 *Density*:
 - 12.1.1.1 *Block Insulation*—Test Method **C303**.
 - 12.1.1.2 *Pipe Insulation*—Test Method **C302**, Procedure A.
- 12.1.2 *Apparent Thermal Conductivity*:
 - 12.1.2.1 *Block Insulation*—Test Method **C177** per Practice **C1058/C1058M** large temperature difference method or Test Method **C518**, using 1½ ± ½-in. (38 ± 13-mm) thick specimens.