



Designation: C612 – 25

Standard Specification for Mineral Fiber Block and Board Thermal Insulation¹

This standard is issued under the fixed designation C612; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the classification, composition, dimension, and physical properties of mineral fiber (rock, slag, or glass) semi-rigid and rigid board intended for the use as thermal insulation on surfaces operating at temperatures between 0°F (-18°C) and 1800°F (982°C). For specific applications, the actual temperature limits shall be agreed upon between the supplier and the purchaser.

1.2 For satisfactory performance, properly installed protective vapor retarder or barriers shall be used on below ambient temperature applications to reduce movement of water through or around the insulation towards the colder surface. Failure to use a vapor retarder or barrier can lead to insulation and system damage. Refer to Guide C755 for consideration in the selection of water vapor retarders and Guide C1423 for specific guidance in selecting jacketing materials. Although vapor retarder properties are not part of this specification, properties required in Specification C1136 are pertinent to applications or performance.

1.3 The orientation of the fibers within the boards is primarily parallel to the principal surface (face). This specification does not cover fabricated pipe and tank wrap insulation where the insulation has been cut and fabricated to provide a fiber orientation that is perpendicular to the surface (face).

1.4 This standard does not purport to provide the performance requirements of hourly-rated fire systems. Consult the manufacturer for the appropriate system.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate*

safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C165 Test Method for Measuring Compressive Properties of Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation

C356 Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat

C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

C411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation

C447 Practice for Estimating the Maximum Use Temperature of Thermal Insulations

C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

C680 Practice for Estimate of the Heat Gain or Loss and the Surface Temperatures of Insulated Flat, Cylindrical, and Spherical Systems by Use of Computer Programs

C755 Guide for Selection of Water Vapor Retarders for Thermal Insulation

C795 Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.20 on Homogeneous Inorganic Thermal Insulations.

Current edition approved Nov. 15, 2025. Published December 2025. Originally approved in 1967. Last previous edition approved in 2019 as C612 – 14 (2019). DOI: 10.1520/C0612-25.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Physical Property Requirements^A

Properties	Type IA	Type IB	Type II	Type III	Type IVA	Type IVB	Type V Grade A and B
Maximum use temperature ^B °F (°C)	450 (232)	450 (232)	850 (454)	1000 (538)	1200 (649)	1200 (649)	1800 (982)
Apparent thermal conductivity, max, Btu in./h ft ² °F (W/m K)							
Mean temperatures °F (°C)							
25 (-4)	0.22 (0.032)	0.21 (0.030)	0.21 (0.030)	0.21 (0.030)	0.21 (0.030)	0.23 (0.033)	0.44 (0.063)
75 (24)	0.26 (0.037)	0.26 (0.037)	0.25 (0.036)	0.25 (0.036)	0.25 (0.036)	0.24 (0.035)	0.45 (0.064)
100 (38)	0.28 (0.040)	0.27 (0.039)	0.27 (0.039)	0.27 (0.039)	0.27 (0.039)	0.25 (0.036)	0.45 (0.064)
200 (93)	0.36 (0.052)	0.34 (0.049)	0.35 (0.050)	0.35 (0.050)	0.34 (0.049)	0.30 (0.043)	0.47 (0.068)
300 (149)	0.46 (0.066)	0.42 (0.060)	0.44 (0.063)	0.44 (0.063)	0.44 (0.063)	0.36 (0.052)	0.49 (0.071)
400 (204)			0.55 (0.079)	0.55 (0.079)	0.55 (0.079)	0.42 (0.061)	0.52 (0.075)
500 (260)			0.70 (0.101)	0.70 (0.101)	0.70 (0.101)	0.53 (0.076)	0.55 (0.080)
600 (316)				0.90 (0.130)	0.85 (0.123)	0.63 (0.091)	0.59 (0.085)
700 (371)					1.00 (0.144)	0.75 (0.108)	0.63 (0.091)
800 (427)							0.67 (0.097)
Minimum Compressive resistance at 10 % deformation, min, lb/ft ² (kPa)							
Category I			no compressive resistance requirement				
Category 2	N. A. ^C	25 (1.2)	25 (1.2)	12 (0.6)	50 (2.4)	50 (2.4)	1000 (48)
Linear shrinkage, at maximum use temperature, %	2.0	2.0	2.0	2.0	2.0	2.0	4.0
Water vapor sorption, max, %	5.0	5.0	5.0	5.0	5.0	5.0	5.0
Surface burning characteristics:							
Flame spread index, max	25	25	25	25	25	25	25
Smoke developed, max	50	50	50	50	50	50	50

^A Refer to Section 7 for additional physical property requirements.

^B See **Warning** in 6.2.1.

^C N. A. indicates not applicable.

C1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions

C1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation

C1101/C1101M Test Methods for Classifying the Flexibility or Rigidity of Mineral Fiber Blanket and Board Insulation

C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation

C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus

C1136 Specification for Flexible, Low Permeance Vapor Retarders for Thermal Insulation

C1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials

C1335 Test Method for Measuring Non-Fibrous Content of Man-Made Rock and Slag Mineral Fiber Insulation

C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings

C1423 Guide for Selecting Jacketing Materials for Thermal Insulation

C1617 Test Method for Quantitative Accelerated Laboratory Evaluation of Extraction Solutions Containing Ions Leached from Thermal Insulation on Aqueous Corrosion of Carbon Steel

C1936 Test Method for Corrosiveness of Mineral-Fiber or Cellulosic-Fiber Insulation by Comparison to Control

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E84 Test Method for Surface Burning Characteristics of Building Materials

2.2 Other Referenced Document:

CAN/ULC-S102 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies³

3. Terminology

3.1 *Definitions*—For definitions used in this specification, refer to Terminology **C168**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *delivered thickness*—the actual thickness of the product shipped by the manufacturer or the seller and received by the purchaser.

3.2.2 *mean temperature*—the sum of the cold surface temperature and the hot surface temperature divided by two.

3.2.3 *shot*—is defined, for the purposes of this specification, as that material which cannot be brushed or mechanically shaken through No. 100 (150-µm) sieve.

4. Classification

4.1 Mineral fiber board insulation covered by this specification shall be classified into seven types with two grades for Type V and two categories, shown in **Table 1**. This classification is based upon the maximum use temperature, maximum apparent thermal conductivity, minimum compressive resistance, maximum linear shrinkage, maximum water vapor sorption, and maximum surface burning characteristics for the insulations.

³ Available from Underwriters Laboratories of Canada, 7 Crouse Road, Scarborough, Ontario, Canada M1R 3A9.