



Designation: C665 – 23

Standard Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing¹

This standard is issued under the fixed designation C665; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers the composition and physical properties of mineral-fiber blanket insulation used to thermally or acoustically insulate ceilings, floors, and walls in light frame construction and manufactured housing. The requirements cover fibrous blankets and facings. Values for water-vapor permeance of facings are suggested for information that will be helpful to designers and installers.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- B152/B152M** Specification for Copper Sheet, Strip, Plate, and Rolled Bar
- C167** Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations
- C168** Terminology Relating to Thermal Insulation

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1970. Last previous edition approved in 2017 as C665 – 17. DOI: 10.1520/C0665-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C177** Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C390** Practice for Sampling and Acceptance of Thermal Insulation Lots
- C518** Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- C653** Guide for Determination of the Thermal Resistance of Low-Density Blanket-Type Mineral Fiber Insulation
- C1104/C1104M** Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
- C1304** Test Method for Assessing the Odor Emission of Thermal Insulation Materials
- C1338** Test Method for Determining Fungi Resistance of Insulation Materials and Facings
- C1617** Practice for Quantitative Accelerated Laboratory Evaluation of Extraction Solutions Containing Ions Leached from Thermal Insulation on Aqueous Corrosion of Metals
- E84** Test Method for Surface Burning Characteristics of Building Materials
- E96/E96M** Test Methods for Gravimetric Determination of Water Vapor Transmission Rate of Materials
- E970** Test Method for Critical Radiant Flux of Exposed Attic Floor Insulation Using a Radiant Heat Energy Source
- G1** Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminology **C168**.

4. Classification

4.1 Typical mineral-fiber thermal insulation is classified into the following types, classes, and categories:

4.1.1 *Type I*—Blankets without facings.

4.1.2 *Type II*—Blankets with nonreflective facings.

4.1.2.1 *Class A*—Facing with a flame spread index of 25 or less.

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.1.2.2 *Class B*—Facing with a flame propagation resistance; critical radiant flux of 0.12 W/cm^2 ($.11 \text{ Btu/ft}^2\cdot\text{s}$) or greater.

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.1.2.3 *Class C*—Facing not rated for flame propagation resistance (for use in nonexposed applications only).

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.1.3 *Type III*—Blankets with reflective facings:

4.1.3.1 *Class A*—Facing with a flame spread index of 25 or less.

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.1.3.2 *Class B*—Facing with a flame propagation resistance; critical radiant flux of 0.12 W/cm^2 ($.11 \text{ Btu/ft}^2\cdot\text{s}$) or greater.

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.1.3.3 *Class C*—Facing not rated for flame propagation resistance (for use in nonexposed applications only).

(1) *Category 1*—Facing is a vapor retarder.

(2) *Category 2*—Facing is not a vapor retarder.

4.2 Mechanically attached field installed facing shall be classified into *Type/Class/Category* as follows:

(1) *Type I* insulation used in conjunction with a field installed non-reflective facing having a 25 flame spread or less on both sides is considered functionally equivalent to a *Type II/Class A/Category 1* insulation composite.

(2) *Type I* insulation used in conjunction with a field-installed perforated, or vapor breathable, nonreflective facing having a 25 flame spread or less on both sides is considered functionally equivalent to *Type II/Class A/Category 2* insulation composite.

(3) *Type I* insulation used in conjunction with a field-installed reflective facing (reflective side exposed) having a 25 flame spread or less on both sides is considered equivalent to a *Type III/Class A/Category 1* insulation composite.

(4) *Type I* insulation used in conjunction with a field-installed perforated, or vapor breathable, reflective facing (reflective side exposed) having a 25 flame spread or less on both sides is considered functionally equivalent to a *Type III/Class A/Category 2* insulation composite.

5. Ordering Information

5.1 For specific installations, thermal resistance, length, width, and facing suited to the intended use shall be specified by the purchaser.

6. Materials and Manufacture

6.1 *Basic Material*—The basic material shall be fibers made from mineral substances such as rock, slag, or glass processed from the molten state into a fibrous form.

6.2 *Manufacture*—Insulation blankets shall consist of flexible units composed of felted, bonded, or unbonded fibers formed into rolls or flat cut pieces (batts), with or without various adhered facings, and with or without a means for attachment of the blanket to applicable constructions.

7. Physical Properties

7.1 *Thermal Resistance*—The standard thermal resistance values in $^{\circ}\text{F} \cdot \text{h} \cdot \text{ft}^2/\text{Btu}$ ($\text{K} \cdot \text{m}^2/\text{W}$) are: 4, 7, 11, 13, 19, 22, 30, and 38 (0.7, 1.2, 1.9, 2.3, 3.3, 3.9, 5.3, and 6.7). *R* values other than those listed shall be agreed upon between the supplier and the purchaser. The product must be produced to the label *R* value. The thermal resistance, *R*, for the average of any four randomly selected samples shall not be more than 5 % below the listed *R* value when tested in accordance with 13.2, nor shall any single specimen be more than 10 % below the listed *R* value.

7.2 Surface Burning Characteristics:

7.2.1 Insulation blankets exclusive of facing, when tested in accordance with Test Method E84, shall have a flame spread index no greater than 25, and a smoke developed index no greater than 50.

7.2.2 Insulation blankets with facings intended for exposed application, when tested in accordance with Test Method E84, shall have a flame spread index no greater than 25, and a smoke developed index no greater than 50.

7.3 *Critical Radiant Flux*—Insulation blankets, when tested in accordance with 13.4, shall have a critical radiant flux-flame propagation resistance $\geq 0.12 \text{ W/cm}^2$ ($0.11 \text{ Btu/ft}^2\cdot\text{s}$). Blankets with facing on both surfaces, shall be tested on the surface to be left exposed and shall be marked on either surface.

7.4 *Water-Vapor Permeance*—When tested in accordance with 13.5, vapor retardant facings shall have a vapor permeance of no more than 1 perm ($5.7 \times 10^{-11} \text{ kg} \cdot \text{Pa}^{-1} \cdot \text{s}^{-1} \cdot \text{m}^{-2}$) and vapor-permeable facing shall have a vapor permeance of no less than 5 perm ($2.9 \times 10^{-10} \text{ kg} \cdot \text{Pa}^{-1} \cdot \text{s}^{-1} \cdot \text{m}^{-2}$).

7.5 *Water Vapor Sorption*—The water vapor sorption of the insulation without facing shall be not more than 5 % by weight, when tested in accordance with 13.6.

7.6 *Odor Emission*—A detectable odor of strong objectionable nature recorded by more than two of the five panel members shall constitute rejection of the material when tested in accordance with 13.7.

7.7 Corrosiveness:

7.7.1 When tested in accordance with 13.8, the metal plates in contact with the insulation shall show no corrosion greater than that observed on the comparative plates in contact with sterile cotton.

7.7.2 *Alternative test – Steel only*—When tested in accordance with 13.9, the mass loss corrosion rate of the unfaced insulation extract shall not exceed that of the 5-ppm chloride solution.

NOTE 1—The use of alternative metals such as copper and aluminum have been evaluated using Practice C1617. The task group will continue to investigate the potential for using Practice C1617 as an alternative to 7.7.1 for these metals.

NOTE 2—The pass/fail criteria established in section 7.7.2 is for materials which claim compliance with Specification C665. The corrosion procedure as detailed in 7.7.1 is referenced in multiple Mineral Fiber material standards. The use of the alternative procedure and the establishment of pass/fail criteria using section 7.7.2 should be addressed by each specific material standard.