



Designation: C871 – 18 (Reapproved 2023)

Standard Test Methods for Chemical Analysis of Thermal Insulation Materials for Leachable Chloride, Fluoride, Silicate, and Sodium Ions¹

This standard is issued under the fixed designation C871; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover laboratory procedures for the determination of water-leachable chloride, fluoride, silicate, and sodium ions in thermal insulation materials in the parts per million range.

1.2 Selection of one of the test methods listed for each of the ionic determinations required shall be made on the basis of laboratory capability and availability of the required equipment and appropriateness to the concentration of the ion and any possible ion interferences in the extraction solution.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C168 Terminology Relating to Thermal Insulation

C692 Test Method for Evaluating the Influence of Thermal Insulations on External Stress Corrosion Cracking Tendency of Austenitic Stainless Steel

¹ These test methods are under the jurisdiction of ASTM Committee C16 on Thermal Insulation and are the direct responsibility of Subcommittee C16.31 on Chemical and Physical Properties.

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1977. Last previous edition approved in 2018 as C871 – 18. DOI: 10.1520/C0871-18R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C795 Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel

C871 Test Methods for Chemical Analysis of Thermal Insulation Materials for Leachable Chloride, Fluoride, Silicate, and Sodium Ions

D1428 Test Method for Test for Sodium and Potassium In Water and Water-Formed Deposits by Flame Photometry (Withdrawn 1989)³

2.2 *AWWA Standards:*

4500-Si D Molybdosilicate Method for Silica⁴

4500-Si E Heteropoly Blue Method for Silica⁴

3. Terminology

3.1 *Definitions*—Refer to Terminology C168 for definitions relating to insulation.

4. Summary of Test Methods

4.1 Insulation specimens are leached for 30 min in boiling water. Tests to determine quantitatively chloride, fluoride, silicate, and sodium ions are performed on aliquots of the filtered leachate solution.

4.2 *Analysis for Chloride:*

4.2.1 Amperometric-coulometric titration test method.

4.2.2 Titrimetric test method. This method is no longer recommended as requested by ASTM International due to use of a specific hazardous substance.

4.2.3 Specific ion electrode test method.

4.3 *Analysis for Fluoride:*

4.3.1 Specific ion electrode test method.

4.3.2 SPADNS colorimetric test method.

4.4 *Analysis for Silicate:*

4.4.1 Atomic absorption spectrophotometry test method.

4.4.2 Colorimetric test methods—AWWA Methods 4500-Si D and 4500-Si E.

4.5 *Analysis for Sodium:*

4.5.1 Flame photometric test method

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ *Standard Methods for the Examination of Water and Wastewater*, 17th Edition, American Public Health Association, Washington, DC, 1989.

Test Methods **D1428**.

4.5.2 Atomic absorption spectrophotometry test method.

4.5.3 Sodium Ion-Selective electrode.

5. Significance and Use

5.1 Research has demonstrated that in addition to the halide ion chloride; fluoride ions, when deposited and concentrated on the surface of austenitic stainless steel, can contribute to external stress corrosion cracking (ESCC) in the absence of inhibiting ions.⁵ Two widely used insulation specifications that are specific to ESCC allow the use of the same Test Methods **C692** and **C871** for evaluation of insulation materials. Both specifications require fluoride ions to be included with chloride ions when evaluating the extractable ions.

5.2 Chlorides (and fluorides) can be constituents of the insulating material or of the environment, or both. Moisture in the insulation or from the environment can cause chlorides (and fluorides) to migrate through the insulation and concentrate at the hot stainless steel surface.

5.3 The presence of sodium and silicate ions in the insulation has been found to inhibit external stress corrosion cracking caused by chloride (and fluoride) ions, whether such ions come from the insulation itself or from external sources. Furthermore, if the ratio of sodium and silicate ions to chloride (and fluoride) ions is in a certain proportion in the insulation, external stress corrosion cracking as a result of the presence of chloride (and fluoride) in the insulation will be prevented or at least mitigated (see also Specification **C795**).

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁶ Use other grades only if it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Distilled or deionized water (DI), having maximum conductivity of 2.5 $\mu\text{S}/\text{cm}$ and containing less than 0.1 ppm of chloride ions shall be used in all tests.

7. Sampling

7.1 With low-chloride insulating materials, wear clean polyethylene gloves while taking and handling the sample to avoid chloride contamination from perspiration. Do not use gloves made from chloride-containing compounds such as neoprene

or saran, or materials with metallic chlorides in their formulations. Prior to use, rinse gloves twice, drain, and air-dry in a clean, halide-free environment. Store clean gloves in a closed container or envelope.

7.2 It is suitable to handle materials with more than 25 ppm chloride with clean, dry hands with no significant contamination.

8. Test Specimen

8.1 Apparatus and tools used for special preparation and leaching shall be clean and free of chlorides, fluorides, silicates, sodium, and acidic or alkaline materials that might affect the chemical test. Distilled water must be used in all tests unless deionized water has been shown to be adequate.

8.1.1 For molded insulation, use a band saw or equivalent, making several cuts through the entire cross section of each piece of insulation to be tested. Each specimen shall be representative of the entire cross section of the piece, except that metal screen, or expanded metal used as a supportive facing shall not be included. It is recommended that thin wafers of material be cut between $\frac{1}{16}$ in. and $\frac{1}{8}$ in. (1.6 mm and 3.2 mm) thick. Cut enough material for two 20 g samples.

8.1.2 Blanket fibrous materials are cut into strips across the entire width of the blanket using clean, dry scissors.

8.1.3 Samples containing moisture are placed in a suitable container, protected from contamination, and oven dried at $230^\circ\text{F} \pm 10^\circ\text{F}$ ($100^\circ\text{C} \pm 5^\circ\text{C}$) (or manufacturers recommended temperature) to a constant weight (± 0.1 g) or overnight.

9. Extraction Technique

9.1 *Apparatus*:

9.1.1 *Electronic Balance*, capable of weighing to 2000 g with readability to the nearest 0.1 g.

9.1.2 *Blender*, with jar-top thread preferred.

9.1.3 *Beaker*, 1 L stainless or borosilicate.

9.1.4 *Filter*, Buchner with suitable filter paper.

9.2 Using a closed-top blender, such as a 1 qt Mason jar with blender blades, blend exactly 20.0 g of sample (or other weight if necessary) in approximately 400 mL of DI or distilled water for 30 s. While most materials blend to a homogeneous mixture in 30 s, some very hard materials require 60 s or more.

9.3 Quantitatively transfer the mixture to a tared 1 L stainless steel or borosilicate beaker, rinsing with distilled or DI water.

9.4 Bring to boiling and maintain at the boiling point for $30 \text{ min} \pm 5 \text{ min}$.

9.5 Remove from heat, and cool in a cold water bath to ambient temperature.

9.6 Remove water from the outside of the beaker and place on a balance. Add DI (or distilled) water to bring amount of water up to exactly 500.0 mL (g) (or other weight if necessary).

9.7 Stir mixture until it is uniform and filter through filter paper to get a clear filtrate. If not clear after the first filtration, refilter through a finer filter paper. The first small portion of filtrate is used to rinse the receiving flask and Solution A bottle.

⁵ Whorlow, Kenneth M., Woolridge, Edward and Hutto, Francis B., Jr., "Effect of Halogens and Inhibitors on the External Stress Corrosion Cracking of Type 304 Austenitic Stainless Steel"; STP 1320 *Insulation Materials: Testing and Applications*, Third Volume, Ronald S. Graves and Robert R. Zarr, editors, ASTM West Conshohocken, PA, 1997, page 485.

⁶ *ACS Reagent Chemicals, Specifications and Procedures for Reagents and Standard-Grade Reference Materials*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.