



Designation: D1025 – 23

Standard Test Method for Nonvolatile Residue of Polymerization-Grade Butadiene^{1,2}

This standard is issued under the fixed designation D1025; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of nonvolatile material in polymerization-grade butadiene.

1.2 **WARNING**—Mercury has been designated by many regulatory agencies as a hazardous substance that can cause serious medical issues. Mercury, or its vapor, has been demonstrated to be hazardous to health and corrosive to materials. Use Caution when handling mercury and mercury-containing products. See the applicable product Safety Data Sheet (SDS) for additional information. The potential exists that selling mercury or mercury-containing products, or both, is prohibited by local or national law. Users must determine legality of sales in their location.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and to determine the applicability of regulatory limitations prior to use.*

1.4.1 *The user is advised to obtain LPG safety training for the safe operation of this test method procedure and related activities.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.D0.04 on C4 and C5 Hydrocarbons.

Current edition approved March 1, 2023. Published June 2023. Originally approved in 1949. Last previous edition approved in 2021 as D1025 – 10 (2021). DOI: 10.1520/D1025-23.

² This test method is an adaptation of one developed and cooperatively tested by the Butadiene Producer's Committee on Specifications and Methods of Analysis of the Office of Rubber Reserve. It appears in the Butadiene Laboratory Manual, Office of Rubber Reserve, as Method No. 2.1.56.2.

2. Referenced Documents

2.1 *ASTM Standards*:³

E1 Specification for ASTM Liquid-in-Glass Thermometers

3. Summary of Test Method

3.1 A measured volume of liquid butadiene is allowed to evaporate at room temperature from a small glass evaporating dish until only residue remains. The evaporation is then completed by heating the dish to a constant weight.

4. Significance and Use

4.1 This test method is used to determine if there is any heavy material in the butadiene. It is possible that these materials could be deleterious to a polymerization reaction.

5. Apparatus

5.1 *Balance, Analytical*, capable of weighing to the nearest 0.1 mg.

5.2 *Evaporating Dish*, glass, 80 mm in diameter and 45 mm in height.

5.3 *Graduated Cylinder*, capacity of 25 mL, graduated in 0.2 mL subdivisions.

5.4 *Oven*, capable of maintaining a temperature of 105 °C $\pm$ 5 °C.

5.5 *Cooling Vessel*, tightly covered, such as a glass desiccator, for cooling the evaporating dish before weighing.

5.6 *Thermometer*, range from –40 °C to 50 °C, graduated in 1 °C intervals, conforming to the requirements for ASTM Thermometer 1C as prescribed in Specification **E1** is satisfactory. Temperature measuring devices that cover the temperature range of interest, such as the ASTM 1C thermometer, or liquid-in-glass thermometers, thermocouples, or platinum resistance thermometers that provide equivalent or better accuracy and precision may be used.

6. Preparation of Apparatus

6.1 Clean the evaporating dishes with a chromic-acid solution or other suitable cleaning agent before each test.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard