



Designation: D1792 – 17 (Reapproved 2023)

Standard Test Method for Long-Term Removability Properties of Emulsion Floor Polishes¹

This standard is issued under the fixed designation D1792; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the relative ease of removal of dried films of water-emulsion floor polishes from common flooring substrates under accelerated conditions, which correspond to extended service aging.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1436 Test Methods for Application of Emulsion Floor Polishes to Substrates for Testing Purposes

3. Summary of Test Method

3.1 The dried films are conditioned at 37.8 °C (100 °F) in order to simulate service aging. This method utilizes the Gardner straight-line washability apparatus as a means for controlled removal of the dried films. A heavily weighted pad is employed as a means of arriving at a scrubbing force similar to that of hand scrubbing. In order to distinguish between the

relative removal properties of different polishes, the number of oscillations required for complete removal is taken as a measure of removability.

4. Significance and Use

4.1 This test method is used to predict removability of floor polish after a treatment period that simulates aging in the field. It allows for uniform mechanical and detergent action leaving the only variable the actual removability of the polish.

5. Apparatus

5.1 *Volumetric Pipet*, 1 mL, graduated in 0.2 mL units.

5.2 *Applicator*—Doctor blade 51 mm (2 in.) wide by 25 mm (1 in.) deep and having 0.203 mm (0.008 in.) clearance along the 51 mm (2 in.) length.

5.3 *Test Flooring Substrate*—Official Vinyl Composition Tile (OVCT),³ shall be used in the test.

5.4 *Oven*, capable of maintaining a temperature of 37.8 °C $\pm$ 1.1 °C (100 °F $\pm$ 2 °F).

5.5 *Washability Apparatus*—The Gardner straight-line washability machine.

5.6 *Abrading Surface Nylon Polishing Floor Pad*,⁴ attached to a wood block of dimensions 89 mm by 38 mm (3½ in. by 1½ in.). Presoaked in stripper solution.

5.7 *Weight*—The boat containing the pad is fitted to achieve a total weight of 1 kg (2½ lb $\pm$ ¼ lb). The weight should be properly mounted for uniform load distribution.

¹ This test method is under the jurisdiction of Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.04 on Performance Tests.

Current edition approved September 1, 2023. Published September 2023. Originally approved in 1960 as D1792 – 60 T. Last previous edition approved in 2017 as D1792 – 17. DOI: 10.1520/D1792-17R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ OVCT tile may be obtained through Armstrong Flooring from various home improvement stores. The following Armstrong tile substrates have been found to perform adequately for this test method: Armstrong Excelon Feature Tile: Black (56790), http://www.armstrong.com/commflooringna/product_details_toolbox_magnify.jsp?item_id=47394.

⁴ The sole source of supply of the apparatus known to the committee at this time is 3M Co., 3M Center, St. Paul, MN 55101. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend.