



Designation: D1912 – 00 (Reapproved 2023)

Standard Test Method for Cold-Crack Resistance of Upholstery Leather¹

This standard is issued under the fixed designation D1912; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method² covers the measurement of the cold-crack resistance on all types of upholstery leathers, but especially in the field of automotive upholstery.³ This test method does not apply to wet blue.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Adjuncts:

Greuel rotary cold-fold test machine (14 drawings, 1 list)⁴

3. Summary of Test Method

3.1 In this test method, the cold-crack resistance of upholstery leather is measured by means of a mechanically-applied

pressure to a cone-shaped specimen of leather after both the specimen and the pressure-device have been conditioned in a carefully controlled cold cabinet. Both the specimen and the machine remain in the cold cabinet during testing.

4. Significance and Use

4.1 The results are reproducible⁵ and correlate with the cold impact test⁶ and also correlate with actual practice conditions.⁷ A comparison of the significance of this test method with other test methods has also been made.⁵

5. Apparatus

5.1 *Greuel Rotary Cold-Fold Test Machine*,^{4,8} as shown in Fig. 1 and consisting of two tangential knurled rollers driven by a chain drive.

5.2 *Steel Die or Other Shearing Device.*

5.3 *Cold Cabinet*, capable of maintaining temperatures from -50°F to $+20^{\circ}\text{F}$ (-45°C to -6°C) within $\pm 1^{\circ}\text{F}$ (0.5°C) and flexible enough so that temperatures can be adjusted easily and quickly in 5° increments.

5.4 *Specimen Racks*, constructed so that the specimens may be suspended in the air by attachment at point C with a paper clip (see Fig. 2).

5.5 *Pliers-Type Stapler.*

5.6 *Temperature Indicator*, with a range from -50°F to $+20^{\circ}\text{F}$ (-45°C to -6°C) and an accuracy of $\pm 1^{\circ}\text{F}$ (0.5°C) for measuring the temperature of the area adjacent to the specimens in the cabinet.

6. Test Specimen

6.1 The specimen shall be cut with a die or other shearing device to a size shown in Fig. 2(a). The specimen may be cut from any area on the hide.

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.05 on Upholstery. This standard was developed in cooperation with the American Leather Chemists Assn.

Current edition approved Jan. 1, 2023. Published January 2023. Originally approved in 1961. Last previous edition approved in 2016 as D1912-00 (2016) ϵ^1 . DOI: 10.1520/D1912-00R23.

² Sometimes referred to as the Greuel Cold-Fold Test in Upholstery Group literature.

³ In the past, cold-crack resistance has been measured by various methods which were evaluated by the Upholstery Group Technical Committee in April 1957, and the Cold-Fold Test was adopted as a standard test in the industry. The method has been adopted by the following groups:

The Upholstery Leather Group, Tanners' Council of America.

Fisher Body Division of General Motors Corp., Specification No. 29.1, dated April 12, 1957.

⁴ Detailed drawings of this machine are available at a nominal cost from: ASTM International Headquarters. Order Adjunct No. ADJD1912-E-PDF. Original adjunct produced in 1957. Adjunct updated in 2021 to digital format.

⁵ Good reproducibility is evidenced by correlation tests conducted by the Upholstery Leather Group Technical Committee in April 1956 and reported by Fopma, R. J., "Study of Cold-Crack Test for Upholstery Leathers," *The Journal of the American Leather Chemists' Association*, Vol LIV, No. 4, April 1959, p. 194.

⁶ ALCA Test Method E42, Provisional, April 1953.

⁷ Upholstery Group Technical Committee, Tanners' Council of America files, "Correlation of Cold-Fold versus Cold Impact Tests versus Actual Cushion Testing."

⁸ The sole source of supply of the test machine known to the committee at this time is Aim Tool and Die, 14324 172nd St., Grand Haven, MI 49417. If you are aware of alternative suppliers, please provide this information to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.