



Designation: D1929 – 23

Standard Test Method for Determining Ignition Temperature of Plastics¹

This standard is issued under the fixed designation D1929; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This fire test response test method² covers a laboratory determination of the flash ignition temperature and spontaneous ignition temperature of plastics using a hot-air furnace.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *Caution*—During the course of combustion, gases or vapors, or both, are evolved that have the potential to be hazardous to personnel.

1.4 *This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of the materials, products, or assemblies under actual fire conditions.*

1.5 *Fire testing is inherently hazardous. Adequate safeguards for personnel and property shall be employed in conducting these tests.*

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in 1.3 and 1.4.*

NOTE 1—This test method and ISO 871-2022 (Option 1) are similar in all technical details.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.30 on Thermal Properties.30.03).

Current edition approved May 1, 2023. Published June 2023. Originally approved in 1962. Last previous edition approved in 2020 as D1929 – 20. DOI:10.1520/D1929-23.

In 1996, this test method was totally revised to be technically equal to ISO 871-1996, and a specific air velocity is specified, which eliminates the need for approximations.

² The following reference may be of interest in connection with this test method: Stetchkin, N. P., “A Method and Apparatus for Determining the Ignition Characteristics of Plastics,” *Journal of Research*, National Institute of Standards and Technology, Vol 43, No. 6, December 1949 (RP 2052), p. 591.

Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:³

D618 Practice for Conditioning Plastics for Testing

D883 Terminology Relating to Plastics

E176 Terminology of Fire Standards

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E2653 Practice for Conducting an Interlaboratory Study to Determine Precision Estimates for a Test Method with Fewer Than Six Participating Laboratories

E2935 Practice for Evaluating Equivalence of Two Testing Processes

2.2 International Standards:^{4,5}

ISO 871-2022 Plastics—Determination of Ignition Temperature Using a Hot-Air Furnace

ISO 5725-2 (2019) Accuracy (trueness and precision) of Measurement Methods and Results—Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method

ISO 13943:2017 Fire Safety—Vocabulary

IEC 60584-2 (1982) Thermocouples—Part 2: Tolerances

IEC 60584-3 (2013) Thermocouples—Part 1: EMF specifications and tolerances

3. Terminology

3.1 For definitions of terms relating to plastics, the definitions in this test method are in accordance with Terminology D883. For terms relating to fire, the definitions in this test method are in accordance with Terminology E176 and

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Available from International Organization for Standardization (ISO), ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.

*A Summary of Changes section appears at the end of this standard

ISO 13943. In case of conflict, the definitions given in Terminology E176 shall prevail. For terms relating to precision and bias and associated issues, the terms used in this test method are in accordance with the definitions in Terminology E456.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *flash ignition temperature (FIT)*—the minimum temperature at which, under specified test conditions, sufficient flammable gases are emitted to ignite momentarily upon application of a small external pilot flame.

3.2.2 *glowing combustion*—combustion of a material in the solid phase without flame but with emission of light from the combustion zone, caused by slow decomposition and carbonization at various points in the specimen, without general ignition occurring.

3.2.3 *spontaneous ignition temperature or self-ignition temperature (SIT)*—the minimum temperature at which the self-heating properties of the specimen lead to ignition or ignition occurs of itself, under specified test conditions, in the absence of any additional flame ignition source.

4. Significance and Use

4.1 Tests made under conditions herein prescribed can be of considerable value in comparing the relative ignition characteristics of different materials. Values obtained represent the lowest ambient air temperature that will cause ignition of the material under the conditions of this test. Test values are expected to rank materials according to ignition susceptibility under actual use conditions.

4.2 This test is not intended to be the sole criterion for fire hazard. In addition to ignition temperatures, fire hazards include other factors such as burning rate or flame spread, intensity of burning, fuel contribution, products of combustion, and others.

5. Apparatus

5.1 *Hot-Air Ignition Furnace*—A furnace similar to that shown in Fig. 1, consisting primarily of an electrical heating unit and specimen holder.

5.2 *Furnace Tube*—A vertical tube with an inside diameter of 100 ± 5 mm and a length of 230 ± 20 mm, made of a ceramic that will withstand at least 750°C . The vertical tube stands on the furnace floor, fitted with a plug for the removal of accumulated residue.

5.3 *Inner Ceramic Tube*—A ceramic tube that will withstand at least 750°C , with an inside diameter of 75 ± 5 mm, length of 230 ± 20 mm, and thickness of approximately 3 mm, placed inside the furnace tube and positioned 20 ± 2 mm above the furnace floor on three small spacer blocks. The top is covered by a disk of heat-resistant material with a 25 ± 2 -mm diameter opening in the center that is used for observation and passage of smoke and gases. The pilot flame is located immediately above the opening.

NOTE 2—Fire resistant materials such as silica glass and stainless steel have also been found suitable for this application.

5.4 *Air Source*—An outside air source to supply clean air near the top of the annular space between the ceramic tubes,

through a copper tube at a steady and controllable rate. Air shall be heated and circulated in the space between the two tubes and enter the inner furnace tube at the bottom. Air shall be metered by a rotameter or other suitable device.

5.5 *Electrical Heating Unit*, contained within the mineral fiber sleeve and constructed of 50 turns of 1.3 ± 0.1 mm Nichrome V alloy wire, wound around the furnace tube and embedded in heat-resistant cement.

NOTE 3—Other constructions such as finely coiled wire embedded in molded ceramic fiber have also been found to be acceptable.

5.6 *Insulation*, consisting of a layer of mineral fiber, approximately 60-mm thick, and covered by a metal jacket.

5.7 *Pilot Igniter*, consisting of a nominal 1.8 ± 0.3 -mm inside diameter (ID) copper tubing attached to a gas supply of 94 % minimum purity propane and placed horizontally 5 ± 1 mm above the top surface of the disk cover. The pilot flame shall be adjusted to 20 ± 2 mm in length and centered above the opening in the disk cover.

5.8 *Specimen Support and Holder*—The specimen pan consists of a metal container of approximately 0.5-mm thick steel measuring 40 ± 2 mm in diameter by 15 ± 2 mm in depth. It is held in a ring of approximately 2.0-mm diameter stainless steel welding rod. The ring is welded to a length of the same type of rod extending through the cover of the furnace, as shown in Fig. 1. The bottom of the specimen pan shall be located 185 ± 5 mm down from the top of the inner furnace tube.

5.9 *Thermocouples*, 0.5-mm diameter, Chromel-Alumel (Type K) or Iron-Constantan (Type J), for temperature measurement connected to a calibrated recording instrument with a tolerance not exceeding $\pm 2^\circ\text{C}$. The thermocouple tolerance shall be in accordance with IEC 60584-2 (1982), Table 1, Class 2, or IEC 60584-3 (2013), Table 12, Class 2, or better.

5.10 *Heating Control*—A suitable variable transformer or an automatic controller connected in series with the heating coils.

5.11 *Timing Device*, having an accuracy of at least 1 s.

6. Location of Thermocouples

6.1 Thermocouple TC_1 measures the temperature, T_1 , of the specimen. It is located as close as possible to the center of the upper surface of the specimen when the specimen is in place within the furnace. The thermocouple wire is attached to the specimen support rod.

6.2 Thermocouple TC_2 gives some indication of the temperature, T_2 , of the air traveling past the specimen. It is located 10 ± 2 mm below the center of the specimen pan. The thermocouple wire is attached to the specimen support rod.

6.2.1 It is acceptable to install thermocouple TC_2 through a hole drilled adjacent to the inspection plug below the specimen pan, instead of introducing it from the top, as shown in Fig. 1.

6.3 Thermocouple TC_3 measures the temperature, T_3 , of the heating coil. It is located adjacent to the furnace heating coil and is used as a reference for temperature adjustment purposes. A metallic sheathed thermocouple with a diameter not greater