



Designation: D2086 – 22

Standard Test Method for Acidity in Vinyl Acetate and Acetaldehyde¹

This standard is issued under the fixed designation D2086; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of total acidity as acetic acid in refined vinyl acetate and acetaldehyde.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 For purposes of determining conformance of an observed value or a calculated value using this test method to relevant specifications, test result(s) shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.4 For hazard information and guidance, see the supplier’s Material Safety Data Sheet.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 8.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Jan. 1, 2022. Published January 2022. Originally approved in 1962. Last previous edition approved in 2012 as D2086 – 08 (2012) which was withdrawn January 2021 and reinstated in January 2022. DOI: 10.1520/D2086-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

E200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis

3. Summary of Test Method

3.1 The specimen is mixed with either an equal volume of chilled water or an equal volume of ethyl alcohol and titrated at reduced temperature with aqueous sodium hydroxide solution to a phenolphthalein end point.

4. Significance and Use

4.1 This test method provides a measurement of total acidity in vinyl acetate and acetaldehyde. The results of these measurements can be used for specification acceptance.

5. Interferences

5.1 Any material or contaminant that will react with NaOH under the test conditions will affect the results.

5.2 Vinyl acetate will decompose on storage, typically by way of hydrolysis, to form acetic acid.

5.3 Acetaldehyde will react with oxygen, either dissolved or in a storage container, to form acetic acid.

5.4 Various acids or other acidic materials may be present. Common practice, including the method used here, calculates these as acetic acid. The actual weight percent of acidic materials may be different.

6. Apparatus

6.1 *Buret*, 10-mL, graduated in 0.05-mL subdivisions.

6.2 *Erlenmeyer Flask*, 250-mL capacity.

6.3 *Graduated Cylinder*, 50 or 100-mL capacity.

6.4 *Cold Bath*, maintained at 0 °C or below.

7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society,