



Designation: D2347 – 00 (Reapproved 2021)

Standard Test Method for Measuring Area of Leather Test Specimens¹

This standard is issued under the fixed designation D2347; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the measurement of the surface area of leather test specimens. Unless otherwise specified, the surface to be measured shall be the grain surface or the surface most closely adjacent to the grain surface. This test method does not apply to wet blue.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1610 Practice for Conditioning Leather and Leather Products for Testing

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *area of a circular specimen*—the average diameter squared and multiplied by $\frac{\pi}{4}$ and reported to the nearest 1 mm².

3.1.2 *area of a rectangular specimen*—the product of the average distance across the width of the grain surface multiplied by the average distance across the length of the grain surface of the leather specimen to the nearest 1 mm².

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.07 on Physical Properties.

Current edition approved Sept. 1, 2021. Published October 2021. Originally approved in 1965. Last previous edition approved in 2015 as D2347 – 00 (2015). DOI: 10.1520/D2347-00R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 This test method is designed to measure the area of specimens before and after they are subjected to various tests that may effect surface area. Two test procedures wherein such measurements could be used are for the apparent density of leather and the resistance of leather to synthetic perspiration solution.

5. Apparatus

5.1 *Die*, of appropriate size for round or rectangular leather specimens, having uniform dimensions in the 50 to 80 mm range. When rigid and thick leathers, such as sole leathers, are being measured, a knife may be used to produce the test specimen provided straight edges are obtained.

5.2 *Mallet or Clicking Machine*.

5.3 *Rule or Steel Tape*, graduated to 1.0 mm.

5.4 *Caliper*, graduated to 1.0 mm (recommended for sole leather).

6. Test Specimen

6.1 The specimen shall be a circular or rectangular piece of leather cut from leather sides or skins that have been conditioned in accordance with Practice D1610 for 48 h in an atmosphere maintained at 73.4 ± 1.8 °F (23 ± 1 °C) and 50 ± 4 % relative humidity.

6.2 The specimens used in this test method generally range in area from 1500 to 10 000 mm².

6.3 Do not die out or cut specimens from areas that show surface defects such as indentations, creases, or cuts.

7. Procedure

7.1 Place the specimen with the grain side up on a flat surface and spread it out without pulling or stretching. Using a rule or steel tape for flexible leathers and a caliper for sole leathers, make three measurements equally spaced along the width and three measurements along the length of the specimen to the nearest 1.0 mm.

7.2 Measure the diameter of the specimen by placing a rule or steel tape across its widest girth and note the length on the rule or tape extending over the specimen. Repeat this measurement four times at radii approximately 45° to each other and average the results to obtain the diameter.