



Designation: D2834 – 95 (Reapproved 2022)

Standard Test Method for Nonvolatile Matter (Total Solids) in Water-Emulsion Floor Polishes, Solvent-Based Floor Polishes, and Polymer- Emulsion Floor Polishes¹

This standard is issued under the fixed designation D2834; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of nonvolatile matter (total solids) in a water-emulsion, organic solvent-based liquid and paste floor polishes, and polymer-emulsion-type floor polishes.

1.2 This test method recognizes that the products may contain material that will slowly volatilize or change chemically with a resulting change in weight of the nonvolatile matter. Therefore, since drying to constant weight is impractical, specific drying times have been selected.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Significance and Use

2.1 Nonvolatile matter determination is useful as a quality control test, when used in conjunction with other tests, to assure specification compliance.

3. Apparatus

3.1 Flat-Bottom Dishes:

¹ This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.03 on Chemical and Physical Testing. This test method is a consolidation of Methods D1289 and D2046.

Current edition approved Dec. 1, 2022. Published December 2022. Originally approved in 1969. Last previous edition approved in 2015 as D2834 – 95 (2015). DOI: 10.1520/D2834-95R22.

3.1.1 For water-emulsion floor polishes and polymer-emulsion-type floor polishes, use aluminum dishes 1.5 cm deep and 6 cm in diameter.

3.1.2 For solvent-based floor polishes, use glass dishes 4.5 cm deep and 6 cm in diameter, with covers.

3.2 *Analytical Balance*, with a sensitivity of 0.1 mg.

3.2.1 *Drying Oven, Convection-Type*, capable of maintaining a temperature of $105.0^{\circ}\text{C} \pm 2.5^{\circ}\text{C}$ ($221.0^{\circ}\text{F} \pm 4.5^{\circ}\text{F}$). If many determinations of solvent-based floor polishes are being made at the same time, an explosion-proof oven should be used.

4. Sampling

4.1 The sample shall be thoroughly representative of the material in question, and the test specimen shall be thoroughly representative of the sample itself.

5. Procedure

5.1 Bring the material to be tested to equilibrium temperature at $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$ ($73.4^{\circ}\text{F} \pm 3.6^{\circ}\text{F}$).

5.2 Making the determination in duplicate, place approximately 2 g of water-emulsion floor polish, or solvent-based floor polish specimen, or 1 g of polymer-emulsion-type floor polish specimen into a tared, dried, flat-bottom aluminum dish of the previously specified size. Weigh rapidly, and place in the oven maintained at 102.5°C to 107.5°C . The starting time in the oven is the point at which the oven has returned to temperature after loading. After heating for 4 h for water-emulsion floor polish, 16 h for solvent-based floor polish, or 2 h for polymer-emulsion-type floor polishes. Cool in a desiccator. Weigh to the nearest 0.1 mg.

5.3 Do not overload the oven, and provide space at least equal to the diameter of the dishes between dishes in the oven.

6. Calculation

6.1 Multiply the weight of total solids by 100 and divide by the weight of the sample to obtain the percentage of nonvolatile matter.