



Designation: D3128 – 07 (Reapproved 2021)

## Standard Specification for 2-Methoxyethanol<sup>1</sup>

This standard is issued under the fixed designation D3128; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This specification covers 2-methoxyethanol.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.4 For hazard information and guidance, see the supplier’s Material Safety Data Sheet for materials listed in this specification.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related

Coatings and Material (Withdrawn 2021)<sup>3</sup>

D1078 Test Method for Distillation Range of Volatile Organic Liquids

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method) (Withdrawn 2021)<sup>3</sup>

D1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products

D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E300 Practice for Sampling Industrial Chemicals

2.2 U.S. Federal Standard:

PPP-C-2020 Specification for Packaging of Chemicals, Liquid, Dry, and Paste<sup>4</sup>

### 3. Properties

3.1 2-Methoxyethanol shall conform to the following requirements:

|                                                   |                                                          |
|---------------------------------------------------|----------------------------------------------------------|
| Apparent specific gravity:                        |                                                          |
| 20/20 °C                                          | 0.963 to 0.967                                           |
|                                                   | or                                                       |
| 25/25 °C                                          | 0.960 to 0.964                                           |
| Color, Pt-Co scale, max (Note 1)                  | 15                                                       |
| Distillation range:                               |                                                          |
| Initial boiling point, °C, min                    | 123                                                      |
| Dry point, °C, max                                | 126                                                      |
| Water, weight, % max                              | 0.2                                                      |
| Acidity (free acid as acetic acid), weight, % max | 0.01, equivalent to 0.093 mg of KOH per gram of material |

NOTE 1—Instrumental Pt-Co color determined by Test Method D5386 has been shown to have no statistically significant difference from Pt-Co color determined by Test Method D1209. However, it is not known whether 2-methoxyethanol was part of the sample set included in the interlaboratory study.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved July 1, 2021. Published August 2021. Originally approved in 1972. Last previous edition approved in 2013 as D3128 – 07 (2013). DOI: 10.1520/D3128-07R21.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.