



Designation: D3816/D3816M – 96 (Reapproved 2020)

Standard Test Method for Water Penetration Rate of Pressure-Sensitive Tapes¹

This standard is issued under the fixed designation D3816/D3816M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method provides one procedure for measuring the water penetration rate of 2-in. or wider pressure-sensitive tape.

1.2 The values stated in either SI or inch-pound units are to be regarded separately as standard. The values stated in each system may not be equivalent; therefore, each system must be used independently, without combining values in any way.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D996 Terminology of Packaging and Distribution Environments

D3715/D3715M Practice for Quality Assurance of Pressure-Sensitive Tapes

D4332 Practice for Conditioning Containers, Packages, or Packaging Components for Testing

E122 Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process

¹ This test method is under the jurisdiction of ASTM Committee D10 on Packaging and is the direct responsibility of Subcommittee D10.14 on Tape and Labels.

Current edition approved Oct. 1, 2020. Published October 2020. Originally approved in 1979. Last previous edition approved in 2012 as D3816/D3816M – 96 (2012). DOI: 10.1520/D3816_D3816M-96R20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions*— General terms in this test method are defined in Terminology **D996**.

4. Summary of Test Method

4.1 The pressure-sensitive tape to be tested is secured by its adhesive to a test cup containing a desiccant. The assembly is weighed, then reweighed following submersion under a specified head of water for a specified period of time. The gain in weight is used to calculate the water penetration rate.

5. Significance and Use

5.1 The results of this test method will indicate the relative permeability by water of the tape through its smallest dimension (generally normal to the tape's backing).

5.1.1 The pathway for the water parallel to the adhesive-cup interface is great compared to the tape's thickness and the latter is usually the nearly exclusive source of transmitted water.

5.1.2 Some tape types allow a relatively free path in a direction normal to the backing or along backing pathways parallel to the adhesive-cup interface, allowing the adhesive to become the principal barrier.

5.2 If the adhesive does not continue to adhere to the cup flange during the exposure periods, allowing unintended pathways for water to occur, the measurement should be considered as not having been made. Consequently, the tape might be considered as being inappropriate for use on surfaces like the cup flange under moisture conditions approximating those of the test.

NOTE 1—It may be that the interest is simply in the tape material as a water barrier. In this case how well the tape adheres to the cup flange may be of little consequence and steps to prevent any edge effects are in order. These are referred to in Section 10.

6. Apparatus

6.1 *Test Cups*,³ made from materials that are nonhygroscopic. The cup shall have a *zero* water vapor transmission rate

³ The sole source of supply of the apparatus known to the committee at this time is Chemsultants International, 9349 Hamilton Dr., Mentor, OH 44061-1118. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.