



Designation: D3861 – 22

Standard Test Method for Quantity of Water-Extractable Matter in Membrane Filters¹

This standard is issued under the fixed designation D3861; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the gravimetric determination of the water-extractable material present in membrane filters and is applicable over the complete concentration range of extractables.

1.2 The analyst should be aware that collaborative data for a bias statement as required by Practice D2777 is not provided. See Section 11 for details.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1129 Terminology Relating to Water

D1193 Specification for Reagent Water

D2777 Practice for Determination of Precision and Bias of Applicable Test Methods of Committee D19 on Water

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee D19 on Water and is the direct responsibility of Subcommittee D19.08 on Membranes and Ion Exchange Materials.

Current edition approved Nov. 1, 2022. Published December 2022. Originally approved in 1979. Last previous edition approved in 2011 as D3861 – 91 (2011) which was withdrawn July 2020 and reinstated in November 2022. DOI: 10.1520/D3861-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 For definitions of terms used in this test method, refer to Terminology D1129.

4. Summary of Test Method

4.1 The quantity of water-soluble extractables present in membrane filters is determined by immersing the preweighed membrane in boiling reagent grade water for an extended time, then drying and reweighing the membrane. A control membrane is employed to eliminate weighing errors caused by balance changes or changing moisture content of the membrane in the weighing procedures. Weight changes of the control membrane are applied as a correction factor to the weight change of the test membrane filters.

5. Significance and Use

5.1 The presence of water-soluble extractables in membrane filters can create errors in test procedures employing membrane filters. However, these errors can be eliminated or significantly reduced if the quantity of water-soluble extractables of the specific membrane is previously determined. Certain membrane filter uses require specifications of maximum water-soluble extractable levels. This test method is intended to be a rapid test to determine the loss of water-soluble compounds such as plasticizers or wetting agents from filtration membranes. This test method is not designed to predetermine the performance of a filter, but is significant in determining the percent extractables of membranes from different sources and lot variations from a single source.

6. Apparatus

6.1 *Beaker*, borosilicate glass, 300 mL capacity.

6.2 *Forceps*, stainless steel, unserrated tips.

6.3 *Desiccator*.

6.4 *Drying Oven*, with thermostatic control.

6.5 *Analytical Balance*, sensitivity 0.01 mg.

6.6 *α -Emitting Polonium Source*³ (to discharge static charge in balance).

6.7 *Humidity-Controlled Room or Hood*, for balance.

³ The "Staticmaster," available from Nuclear Products Inc., El Monte, CA, has been found suitable for this purpose.