



Designation: D4402/D4402M – 23

Standard Test Method for Viscosity Determination of Asphalt at Elevated Temperatures Using a Rotational Viscometer¹

This standard is issued under the fixed designation D4402/D4402M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method outlines a procedure for measuring the apparent viscosity of asphalt from 40 to 260 °C [100 to 500 °F] using a rotational viscometer and a temperature-controlled thermal chamber for maintaining the test temperature.

1.2 The values stated in either SI units or cgs and inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. See 10.6 for specific precautionary information.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

E644 Test Methods for Testing Industrial Resistance Thermometers

E1137/E1137M Specification for Industrial Platinum Resistance Thermometers

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-up Roofing.

Current edition approved Feb. 15, 2023. Published February 2023. Originally approved in 1984. Last previous edition approved in 2022 as D4402/D4402M – 15 (2022). DOI: 10.1520/D4402_D4402M-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E2975 Test Method for Calibration or Calibration Verification of Concentric Cylinder Rotational Viscometers

3. Terminology

3.1 Definitions:

3.1.1 *apparent viscosity, n*—the ratio of shear stress to shear rate for a Newtonian or non-Newtonian liquid.

3.1.2 *filled asphalt, n*—an asphalt blend that contains finely dispersed insoluble mineral matter.

3.1.3 *Newtonian liquid, n*—a liquid for which the rate of shear is proportional to the shearing stress.

3.1.3.1 *Discussion*—The constant ratio of the shearing stress to the rate of shear is the viscosity of the liquid. The viscosity of a Newtonian liquid is therefore not dependent on its shear rate. If the ratio is not constant, the liquid is non-Newtonian. Many liquids exhibit both Newtonian and non-Newtonian behavior, depending on the shear rate or temperature, or both.

3.1.4 *shear rate, n*—the measure of the speed in reciprocal seconds (sec^{-1}) at which the intermediate layers of the liquid move with respect to each other.

3.1.5 *shear stress, n*—the force per unit area in pascals (Pa) for SI or dynes/cm² for cgs required to produce the shearing action.

3.1.6 *viscosity, n*—the ratio between the applied shear stress and the rate of shear is called the coefficient of viscosity.

3.1.6.1 *Discussion*—This coefficient is a measure of the resistance to flow of the liquid. The SI unit of viscosity is the pascal second (Pa·s). The centimetre gram second (cgs) unit of viscosity is the poise (dyne·s/cm²) and is equivalent to 0.1 Pa·s. Frequently, centipoise (cP)—equal to one millipascal second (mPa·s)—is used as the viscosity unit.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *apparatus-measuring geometry, n*—the part of the equipment that is immersed in the asphalt sample, the dimensions of which are used, in conjunction with the rotational resisting torque, to calculate the apparent viscosity referred to by the equipment manufacturer as a spindle, bob, inner concentric cylinder, vane, and so forth.

4. Summary of Test Method

4.1 A rotational viscometer, as described in this test method, is used to measure the apparent viscosity of asphalt at elevated temperatures. The torque on the apparatus-measuring geometry, rotating in a thermostatically controlled sample holder containing a sample of asphalt, is used to measure the relative resistance to rotation. The torque and speed are used to determine the viscosity of the asphalt in pascal seconds, millipascal seconds, or centipoise.

5. Significance and Use

5.1 This test method is used to measure the apparent viscosity of asphalts at handling, mixing, or application temperatures.

5.2 Some asphalts may exhibit non-Newtonian behavior under the conditions of this test method, or at temperatures within the range of this test method. Since non-Newtonian viscosity values are not absolute properties, but reflect the behavior of the fluid within the particular measurement system, it should be recognized that measurements made by this test method may not always predict field performance under the conditions of use.

5.3 Comparisons between non-Newtonian viscosity values should be made only for measurements made with similar conditions of temperature, shear rate, and shear history.

6. Apparatus

6.1 *Rotational Viscometer*, capable of measuring the torque required to rotate the selected apparatus-measuring geometry at a selected constant speed while submerged in asphalt at constant desired test temperature, and with the capability to convert the torque measurement to viscosity in pascal seconds, millipascal seconds, or centipoise. This calculation may need to be done manually for some instruments.

NOTE 1—A dynamic shear rheometer meeting the requirements of 6.1 is also acceptable.

6.2 *Apparatus-Measuring Geometry*, of various shapes and sizes, for measurement of various viscosities of asphalt.

6.3 *Temperature-Controlled Thermal Chamber Heater*, for maintaining the sample of asphalt at the test temperature.

6.4 *Sample Chambers*, reusable or disposable.

6.5 *Temperature Controller*, capable of maintaining the specimen temperatures to $\pm 1.0^\circ\text{C}$ [$\pm 2.0^\circ\text{F}$] for test temperatures between 38 and 150 $^\circ\text{C}$ [100 to 300 $^\circ\text{F}$] and to $\pm 2.0^\circ\text{C}$ [$\pm 4.0^\circ\text{F}$] for test temperatures between 150 and 260 $^\circ\text{C}$ [300 to 500 $^\circ\text{F}$].

6.6 *Balance*, readable to 0.1 g, for determining the mass of asphalt sample.

6.7 *Platinum Resistance Thermometer (PRT)*, with a probe which conforms to the requirements of Specification E1137/E1137M, for measuring the temperature of the thermal chamber. The PRT shall have a three- or four-wire connection configuration and overall sheath length shall be at least 50 mm

[2 in.] greater than the immersion depth. Calibrate the PRT system (probe and readout) in accordance with Test Methods E644.

7. Reagents and Materials

7.1 Solvents for cleaning sample chamber, apparatus-measuring geometry, and accessories.

8. Preparation of Apparatus

8.1 The rotational viscometer and thermal chamber heater shall be leveled and prepared as recommended by the instrument manufacturer.

9. Calibration and Standardization

9.1 The viscometer shall be zeroed before use, or as needed, or both, according to the manufacturer's instructions.

9.2 The accuracy of the viscometer shall be checked at least annually using a certified reference fluid of known viscosity at various temperatures, using the procedure described in Test Method E2975. The reference fluid shall be certified to be Newtonian in behavior over the full range of expected test temperatures and shear rates. The reference fluid shall be certified at a temperature within 50 $^\circ\text{C}$ [90 $^\circ\text{F}$] of the temperature(s) to be used during the test. The viscosity measured shall be within $\pm 2\%$ of the certified value, or else a calibration constant (viscosity of the calibration fluid/viscosity indicated by the apparatus) must be determined and applied.

9.3 The accuracy of the temperature reading and the temperature stability of the temperature controller are to be checked at least every six months by placing an asphalt sample or high flash point oil in the test chamber, and equilibrating to a temperature within 50 $^\circ\text{C}$ [90 $^\circ\text{F}$] of the temperature(s) to be used during the test. The sample temperature shall then be measured to within $\pm 0.1^\circ\text{C}$ [$\pm 0.2^\circ\text{F}$] by using a NIST-traceable measuring device, as described in Test Methods E644. If any temperature differential is indicated, the set point of the temperature controller shall be offset accordingly.

10. Procedure

10.1 Follow the manufacturer's instructions for the operation of the instrument.

10.2 Allow the instrument electronics to warm up for at least 5 min before conducting any calibrations or analyses.

10.3 Set the temperature controller to the desired test temperature, taking into account any offset determined in 9.3.

10.4 Select an apparatus-measuring geometry that will develop a resisting torque between 10 and 98 % of the instrument capacity at the selected speed. Generally, measurements will be more accurate at higher torque readings.

10.5 Preferably, preheat the sample chamber and the selected apparatus-measuring geometry until temperature equilibrium has been obtained for at least 15 min. If filled asphalts are being measured, this step is mandatory.

10.6 Add the volume of sample specified by the manufacturer for the apparatus-measuring geometry to be used to the sample chamber. A convenient way for measuring the volume