



Designation: D5071 – 06 (Reapproved 2021)

Standard Practice for Exposure of Photodegradable Plastics in a Xenon Arc Apparatus¹

This standard is issued under the fixed designation D5071; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers specific procedures and test conditions that are applicable for xenon arc exposure of photodegradable plastics conducted in accordance with Practices **G151** and **G155**. This practice also covers the preparation of test specimens, the test conditions best suited for photodegradable plastics, and the evaluation of test results.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This practice is technically equivalent to ISO 4892-2 and Practice **D2565** which cover xenon arc exposures of plastics intended for long term use in outdoor applications.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D882** Test Method for Tensile Properties of Thin Plastic Sheeting
- D883** Terminology Relating to Plastics
- D1293** Test Methods for pH of Water
- D2565** Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
- D3593** Test Method for Molecular Weight Averages/ Distribution of Certain Polymers by Liquid Size-Exclusion Chromatography (Gel Permeation Chromatography GPC)

¹ This practice is under the jurisdiction of ASTM Committee **D20** on Plastics and is the direct responsibility of Subcommittee **D20.50** on Durability of Plastics.

Current edition approved Dec. 1, 2021. Published December 2021. Originally approved in 1991. Last previous edition approved in 2013 as D5071 - 06(2013). DOI: 10.1520/D5071-06R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Using Universal Calibration (Withdrawn 1993)³

D3826 Practice for Determining Degradation End Point in Degradable Polyethylene and Polypropylene Using a Tensile Test

D3890 Practice for Number of Strokes to Prime a Mechanical Pump Dispenser

D5870 Practice for Calculating Property Retention Index of Plastics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

G141 Guide for Addressing Variability in Exposure Testing of Nonmetallic Materials

G147 Practice for Conditioning and Handling of Nonmetallic Materials for Natural and Artificial Weathering Tests

G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

G155 Practice for Operating Xenon Arc Lamp Apparatus for Exposure of Materials

G169 Guide for Application of Basic Statistical Methods to Weathering Tests

2.2 Other Standards:

ISO 4892-2 Plastics—Method of Exposure to Laboratory Light Sources—Part 2, Xenon Arc Sources⁴

Publication C.I.E. No. 85 (1989)⁵

DIN 53384 Testing of Plastics: Artificial Weathering or Exposure in Laboratory Exposure Weathering or Exposure in Laboratory Exposure Apparatus to UV Radiation⁴

3. Terminology

3.1 *Definitions*—The definitions given in Terminologies **D883** and **G113** are applicable to this practice.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁵ Publication No. CIE 85, 1st Ed., 1989 Technical Report, "Solar Spectral Irradiance," available from U.S. National Committee CIE, Mr. Thomas M. Lemons, TLA-Lighting Consultants, Inc., 72 Loring Ave., Salem, MA 01970.

*A Summary of Changes section appears at the end of this standard

4. Significance and Use

4.1 Materials made from photodegradable plastics are intended to deteriorate rapidly when exposed to solar radiation, oxygen, heat, moisture and other degrading elements of the weather. This practice is used for evaluating the photodegradability of plastics when exposed in an apparatus that produces simulated daylight (1,2)⁶ and controlled temperature and moisture. The exposure used in this practice is not intended to simulate the deterioration caused by localized weather phenomena such as atmospheric pollution, biological attack, and salt water exposure. There can be no positive correlation of exposure results between this and other laboratory weathering devices.

4.2 Variations in results can be expected when operating conditions are varied within the accepted limits of this practice. Therefore, all test results using this practice must be accompanied by the specific operating conditions required in Section 9. Refer to Practice G151 for detailed information on the caveats applicable to use of results obtained in accordance with this practice.

4.3 The results of laboratory exposure cannot be directly extrapolated to estimate absolute rate of deterioration by the environment because the acceleration factor is material dependent and can be significantly different for each material and for different formulations of the same material. However, exposure of a similar material of known outdoor performance, a control, at the same time as the test specimens allows comparison of the durability relative to that of the control under the test conditions. Evaluation in terms of relative durabilities also greatly improves the agreement in test results among different laboratories (3).

4.4 Test results will depend on the care that is taken to operate the equipment in accordance with Practice G155. Significant factors include regulation of line voltage, freedom from salt or other deposits from water, temperature and humidity control and condition and age of the burners and filters.

NOTE 2—Additional information on sources of variability and on strategies for addressing variability in the design, execution and data analysis of laboratory accelerated exposure tests is found in Guide G141.

4.5 Before proceeding with this practice, it is common practice to reference the specifications of the material being tested. Any test specimen preparation, conditioning, dimensions, or testing parameters, or combination thereof, covered in the material specification shall take precedence over those mentioned in this practice. If there are no material specifications, then the default conditions apply.

5. Apparatus

5.1 The exposure apparatus employed shall use as the source of radiation a xenon arc lamp and apparatus which conforms to the requirements defined in Practices G151 and G155.

5.1.1 Unless otherwise specified, the spectral power distribution (SPD) of the xenon lamp shall conform to the requirements of Table 1 in Practice G155 for a xenon lamp with daylight filters.

6. Test Specimens

6.1 The size and shape of specimens to be exposed will be determined by the specifications of the particular test method used to evaluate the effects of the exposure on the specimens; the test method shall be determined by the parties concerned. Where practical, it is recommended that specimens be sized to fit specimen holders and racks supplied with the exposure apparatus. Unless supplied with a specific backing as an integral part of the test, specimens shall be mounted so that only the minimum specimen area required for support by the holder is covered. This unexposed surface must not be used as part of the test area. To provide rigidity, flexible specimens are typically attached to, or backed by, a panel made of aluminum, 0.025-in. (0.64-mm) thick.

6.2 Unless otherwise specified, prepare at least three replicate specimens of each test and control material to be exposed.

6.3 Retain a supply of unexposed file specimens of all materials evaluated.

6.3.1 When destructive tests are used, it is recommended that a sufficient number of file specimens be retained so that the property of interest can be determined on the file specimens each time the exposed materials are evaluated.

6.4 Follow the procedures described in Practice G147 for identification and conditioning and handling of specimens of test, control, and reference materials prior to, during, and after exposure.

6.5 Do not mask the face of a specimen for the purpose of showing on one panel the effects of various exposure times. Accurate results are not guaranteed since the masked portion of the specimen is still exposed to temperature and humidity cycles that, in many cases, will affect results.

6.6 In some materials, specimen thickness markedly affects the test results. Thickness of test and control specimens shall be within $\pm 10\%$ of the nominal dimensions.

NOTE 3—Thickness of a specimen is especially important when mechanical properties are being investigated.

7. Procedure

7.1 It is recommended that a control material be exposed simultaneously with experimental materials for determination of relative performance, if performance comparisons are not being made between the test materials themselves. All concerned parties must agree on the control material used.

7.1.1 Identification of any control specimen used shall accompany the report.

7.2 Mount the test specimens in the specimen exposure area with the test surfaces facing the lamp. When the test specimens do not completely fill the exposure area, fill the empty spaces with blank metal panels to maintain the test conditions within the chamber.

⁶ The boldface numbers in parentheses refer to a list of references at the end of this standard.