



Designation: D5263 – 23

Standard Test Method for Determining the Relative Degree of Oxidation in Bituminous Coal by Alkali Extraction¹

This standard is issued under the fixed designation D5263; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This colorimetric test method describes the determination of the relative degree of oxidation by alkali extraction of coals that are high volatile A bituminous to low volatile bituminous in rank.

1.2 This test cannot be sensitive to thermally oxidized coal. It is intended for coals that may be oxidized as a result of weathering.

1.3 *Units*—The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

D7448 Practice for Establishing the Competence of Laboratories Using ASTM Procedures in the Sampling and Analysis of Coal and Coke

3. Terminology

3.1 There are no terms in this standard that require new or other than dictionary definitions.

¹ This test method is under the jurisdiction of ASTM Committee **D05** on Coal and Coke and is the direct responsibility of Subcommittee **D05.15** on Metallurgical Properties of Coal and Coke.

Current edition approved March 1, 2023. Published May 2023. Originally approved in 1992. Last previous edition approved in 2021 as D5263 – 21. DOI: 10.1520/D5263-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 Humic acids, which are present in oxidized coals, are extracted from the coal with sodium hydroxide solution. The degree of oxidation is determined by colorimetrically measuring the transmittance of the alkali extract solution at 520 nm. The intensity of the color produced by the humic acids is a function of the degree of oxidation.

5. Significance and Use

5.1 This test method is a relative measure of the degree of oxidation present in coal. It does not determine the quantitative amount of oxidized coal present. It is only intended to serve as a guide to the supplier, buyer, and user for selecting coals for metallurgical use.

NOTE 1—Lower rank bituminous coals are more easily extracted than higher rank coal.

6. Apparatus

6.1 *Transmission Spectrophotometer*—Single-beam, grating spectrophotometer having a wavelength range of 340 nm to 900 nm.

6.2 *Glass Test Tubes/Cuvettes*, with light paths ranging from 10 mm to 17 mm may be used. Test tubes with an inside diameter of 17 mm $\pm$ 0.3 mm are commonly used.

6.3 *Analytical Balance*, sensitive to 0.001 g.

6.4 *Hot Plate*, capable of bringing aqueous solutions to a boil.

6.5 *Thermometer*, capable of measuring up to 100 °C with a sensitivity of $\pm$ 0.5 °C.

6.6 *Filter Papers*, Type II, Class F and G.

6.7 *Timer*, capable of measuring 30 min to the nearest second.

6.8 *Graduated Cylinder*, 100 mL capacity.

6.9 *Beakers*, 400 mL capacity.

7. Reagents

7.1 *Sodium Hydroxide Solution* (certified 1N).

7.2 *Octylphenoxypolyethoxyethanol Nonionic Surfactant*—Wetting agent.