



Designation: D5336 – 22

Standard Classification System and Basis for Specification for Polyphthalamide (PPA) Injection Molding Materials¹

This standard is issued under the fixed designation D5336; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This classification system covers polyphthalamide (PPA) materials suitable for injection molding.

1.2 The properties included in this classification system are those required to identify the compositions covered. Other requirements necessary to identify particular characteristics important to specialized applications are to be specified by using suffixes as given in Section 5.

1.3 This classification system allows for the use of recycled materials provided that all specification requirements are met.

1.4 This classification system is intended to be a means of calling out plastics materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection can be made by those having expertise in the plastics field only after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this classification system.

1.5 The values stated in SI units are to be regarded as the standard (see [IEEE/ASTM SI-10](#)). The values given in parentheses are for information only.

1.6 The following precautionary caveat pertains only to the test methods portion, Section 11, of this classification system: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in 11.7.1.

NOTE 1—There is no known ISO equivalent to this standard. ISO 16396-1/-2 for polyamides may also be used to describe and classify these PPA materials, but the technical content is significantly different.

NOTE 2—ASTM Standard [D6779](#) on polyamide materials also includes PPA materials in its coverage of various polyamide chemistries. This standard gives additional information for classification and specification

for PPA compositions classified as Group 10 (PA6T/66), Group 12 (PA6T/6I/66) and Group 13 (PA6T/6I) in ASTM Standard [D6779](#) and includes provisions for other PPA compositions to utilize the classification presented.

1.7 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

- [D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics](#)
- [D618 Practice for Conditioning Plastics for Testing](#)
- [D638 Test Method for Tensile Properties of Plastics](#)
- [D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position](#)
- [D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials](#)
- [D792 Test Methods for Density and Specific Gravity \(Relative Density\) of Plastics by Displacement](#)
- [D883 Terminology Relating to Plastics](#)
- [D1600 Terminology for Abbreviated Terms Relating to Plastics](#)
- [D2857 Practice for Dilute Solution Viscosity of Polymers](#)
- [D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry](#)
- [D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials](#)
- [D3892 Practice for Packaging/Packing of Plastics](#)
- [D4000 Classification System for Specifying Plastic Materials](#)
- [D5225 Test Method for Measuring Solution Viscosity of Polymers with a Differential Viscometer](#)

¹ This standard is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.15](#) on Thermoplastic Materials (Section D20.15.09).

Current edition approved Sept. 1, 2022. Published September 2022. Originally approved in 1992. Last previous edition approved in 2021 as D5336 - 21. DOI: 10.1520/D5336-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

D5630 Test Method for Ash Content in Plastics (Withdrawn 2022)³

D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)

D6869 Test Method for Coulometric and Volumetric Determination of Moisture in Plastics Using the Karl Fischer Reaction (the Reaction of Iodine with Water)

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products (Withdrawn 2015)³

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): The Modern Metric System

2.2 *Underwriters Laboratories Standard:*

UL94 Standard for Tests for Flammability of Plastic Materials⁴

2.3 *ISO Standards:*⁵

ISO 75-1 Determination of Temperature of Deflection Under Load—Part 1: General Test Methods

ISO 75-2 Determination of Temperature of Deflection Under Load—Part 2: Plastics and Ebonite

ISO 179-1 Determination of Charpy Impact Strength—Part 1: Non-Instrumented Impact Test

ISO 294-1 Injection Moulding of Test Specimens of Thermoplastic Materials—Part 1: General Principles, Multipurpose-Test Specimens and Bars

ISO 307 Plastics—Polyamides—Determination of Viscosity Number

ISO 527-1 Determination of Tensile Properties—Part 1: General Principles

ISO 527-2 Determination of Tensile Properties—Part 2: Testing Conditions

ISO 3451-1 Determination of Ash General Methods

ISO 3451-4 Determination of Ash, Polyamides

ISO 15512 Determination of Water Content

ISO 16396-1/-2 Plastics — Polyamide (PA) moulding and extrusion materials

3. Terminology

3.1 *Definitions*—The terminology used in this classification system is in accordance with Terminologies **D883** and **D1600**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *polyphthalamide, PPA, n*—a polyamide in which residues of terephthalic acid or isophthalic acid or a combination of the two comprise at least 55 molar percentage of the dicarboxylic acid portion of the repeating structural units in the polymer chain.

4. Classification

4.1 The polyphthalamide materials are designated “PPA,” as specified in Terminology **D1600**.

4.2 Unreinforced polyphthalamide materials are classified into groups according to crystallinity. These groups are subdivided into classes and grades as shown in Table PPA.

NOTE 3—An example of this classification system is as follows:

The designation PPA0121 would indicate from Table PPA:

PPA	= Polyphthalamide as found in Terminology D1600
01 (Group)	= Semicrystalline PPA
2 (Class)	= Low-temperature molding material
1 (Grade)	= With the corresponding requirements shown in Table PPA

4.2.1 To facilitate the incorporation of future or special materials, the “other/unspecified” category (00) for group, (0) for class, and (0) for grade is shown. The basic properties of the material can be obtained from Table A as they apply.

4.3 Reinforced and lubricated versions of the polyphthalamide materials are classified in accordance with Tables PPA and A, where Table PPA specifies the unreinforced material and Table A the properties after the addition of reinforcements or lubricants at the nominal level indicated (see 4.3.1).

NOTE 4—This part of the classification system uses the percent of reinforcements or additives, or both, in the callout of the modified basic material. The types and percentages of reinforcements and additives is sometimes shown on the supplier’s technical data sheet. If necessary additional callout of these reinforcements and additives can be accomplished by use of the suffix of the system (see Section 5).

NOTE 5—Materials containing reinforcements or fillers, or both, at nominal levels not in multiples of five are included in the nearest grade designation. For example, a material with a nominal glass fiber level of 33 % is included with Grade G35.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Underwriters Laboratories (UL), 333 Pfingsten Rd., Northbrook, IL 60062-2096, <http://www.ul.com>.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.