



Designation: D5467/D5467M – 97 (Reapproved 2025)

Standard Test Method for Compressive Properties of Unidirectional Polymer Matrix Composite Materials Using a Sandwich Beam¹

This standard is issued under the fixed designation D5467/D5467M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the in-plane compressive properties of polymer matrix composite materials reinforced by high-modulus fibers in a sandwich beam configuration. The composite material forms are limited to continuous-fiber composites of unidirectional orientation. This test procedure introduces compressive load into a thin skin bonded to a thick honeycomb core with the compressive load transmitted into the sample by subjecting the beam to four-point bending.

1.2 This procedure is applicable primarily to laminates made from prepreg or similar product forms. Other product forms may require deviations from the test method.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3.1 Within the text the inch-pound units are shown in brackets.

NOTE 1—Additional procedures for determining compressive properties of polymer matrix composites may be found in Test Methods [D3410/D3410M](#) and [D695](#).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee [D30](#) on Composite Materials and is the direct responsibility of Subcommittee [D30.04](#) on Lamina and Laminate Test Methods.

Current edition approved Nov. 1, 2025. Published December 2025. Originally approved in 1993. Last previous edition approved in 2017 as D5467/D5467M – 97 (2017). DOI: 10.1520/D5467_D5467M-97R25.

2. Referenced Documents

2.1 *ASTM Standards:*²

[D695](#) Test Method for Compressive Properties of Rigid Plastics

[D792](#) Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

[D883](#) Terminology Relating to Plastics

[D2584](#) Test Method for Ignition Loss of Cured Reinforced Resins

[D2734](#) Test Methods for Void Content of Reinforced Plastics

[D3171](#) Test Methods for Constituent Content of Composite Materials

[D3410/D3410M](#) Test Method for Compressive Properties of Polymer Matrix Composite Materials with Unsupported Gage Section by Shear Loading

[D3878](#) Terminology for Composite Materials

[D5229/D5229M](#) Test Method for Moisture Absorption Properties and Equilibrium Conditioning of Polymer Matrix Composite Materials

[E4](#) Practices for Force Calibration and Verification of Testing Machines

[E6](#) Terminology Relating to Methods of Mechanical Testing

[E111](#) Test Method for Young's Modulus, Tangent Modulus, and Chord Modulus

[E122](#) Practice for Calculating Sample Size to Estimate, With Specified Precision, the Average for a Characteristic of a Lot or Process

[E177](#) Practice for Use of the Terms Precision and Bias in ASTM Test Methods

[E251](#) Test Methods for Performance Characteristics of Metallic Bonded Resistance Strain Gages

[E456](#) Terminology Relating to Quality and Statistics

[E1237](#) Guide for Installing Bonded Resistance Strain Gages

[E1309](#) Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases (Withdrawn 2015)³

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

E1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases (Withdrawn 2015)³

E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases (Withdrawn 2015)³

3. Terminology

3.1 *Definitions*—Terminology D3878 defines terms relating to high-modulus fibers and their composites. Terminology D883 defines terms relating to plastics. Terminology E6 defines terms relating to mechanical testing. Terminology E456 and Practice E177 define terms relating to statistics. In the event of a conflict between terms, Terminology D3878 shall have precedence over the other terminology standards.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *nominal value, n* —a value, existing in name only, assigned to a measurable property for the purpose of convenient designation. Tolerances may be applied to a nominal value to define an acceptable range for the property.

3.2.2 *orthotropic material, n* —a material with a property of interest that, at a given point, possesses three mutually perpendicular planes of symmetry defining the principal material coordinate system for that property.

3.2.3 *principal material coordinate system, n* —a coordinate system with axes that are normal to the planes of symmetry that exist within the material.

3.2.4 *reference coordinate system, n* —a coordinate system for laminated composites used to define ply orientations. One of the reference coordinate system axes (normally the Cartesian x -axis) is designated the reference axis, assigned a position, and the ply principal axis of each ply in the laminate is referenced relative to the reference axis to define the ply orientation for that ply.

3.2.5 *specially orthotropic, adj* —a description of an orthotropic material as viewed in its principal material coordinate system. In laminated composites, a specially orthotropic laminate is a balanced and symmetric laminate of the $(0_i/90_j)_n$ family as viewed from the reference coordinate system, such that the membrane-bending coupling terms of the stress-strain relation are zero.

3.2.6 *transition strain, $\epsilon^{transition}$, n* —the strain value at the mid-range of the transition region between the two essentially linear portions of a bilinear stress-strain or strain-strain curve (a transverse strain-longitudinal strain curve as used for determining Poisson's ratio).

3.3 *Symbols:*

3.3.1 a —distance between neutral axes of test and opposite facesheets.

3.3.2 A —cross-sectional area of test facesheet.

3.3.3 CV —sample coefficient of variation, in percent.

3.3.4 E_o —modulus of elasticity of the opposite facesheet in the test direction.

3.3.5 E_f —modulus of elasticity of the test facesheet in the test direction.

3.3.6 F^{cu} —ultimate compressive strength.

3.3.7 G_{xz} —through-thickness shear modulus of elasticity.

3.3.8 h_c —thickness of core.

3.3.9 σ^c —compressive normal stress.

4. Summary of Test Method

4.1 A sandwich beam composed of two facesheets separated by a relatively deep honeycomb core, as shown in Fig. 1, is loaded in four-point bending. The main component of the compression test specimen is the face sheet that is loaded in compression during flexure, with the material direction of interest oriented along the length of the beam. The other facesheet is of a material and size carefully selected to preclude its influence on the test results. The ultimate compressive strength of the material is determined from the load at which the test facesheet of the sandwich beam fails in an acceptable compression failure mode. If the specimen strain is monitored with strain or deflection transducers then the stress-strain response of the material can be determined, from which can be derived the compressive modulus of elasticity for this configuration.

5. Significance and Use

5.1 This test method is designed to produce membrane compressive property data for material specifications, research and development, quality assurance, and structural design and analysis. Factors that influence the compressive response and should therefore be reported include the following: material, methods of material and specimen preparation, specimen conditioning, environment of testing, specimen alignment, speed of testing, time at reinforcement. Properties, in the test direction, that may be obtained from this test method include:

5.1.1 Ultimate compressive strength,

5.1.2 Ultimate compressive strain,

5.1.3 Compressive (linear or chord) modulus of elasticity, and

5.1.4 Transition strain.

6. Interferences

6.1 *Test Method Sensitivities*—Compressive strength for a single material system has been shown to differ when determined by different test methods. Such differences can be attributed to specimen alignment effects, specimen geometry effects, and fixture effects even though efforts have been made to minimize these effects.

6.2 *Material and Specimen Preparation*—Compressive modulus, and especially compressive strength, are sensitive to poor material fabrication practices, damage induced by improper coupon machining, and lack of control of fiber alignment. Fiber alignment relative to the specimen coordinate axis should be maintained as carefully as possible, although no standard procedure to insure this alignment exists. Procedures found satisfactory include the following: fracturing a cured unidirectional laminate near one edge parallel to the fiber direction to establish the [0] direction or laying in small filament count tows of contrasting color fiber (aramid in carbon laminates and carbon in aramid or glass laminates) parallel to the [0] direction either as part of the prepreg production or as part of panel fabrication.