



Designation: D5890 – 25

Standard Test Method for Swell Index of Clay Mineral Component of Geosynthetic Clay Liners¹

This standard is issued under the fixed designation D5890; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers an index method that enables the evaluation of swelling properties of a clay mineral in reagent water for estimation of its usefulness in geosynthetic clay liners (GCLs). This test method is not applicable for clays with polymers.

1.2 It is adapted from United States Pharmacopeia (USP-NF-XVII) test method for bentonite.

1.3 Powdered clay mineral is tested after drying to constant weight at $105 \pm 5^\circ\text{C}$; granular clay mineral should be ground to 100 % passing a $150\ \mu\text{m}$ (No. 100) U.S. Standard Sieve with a minimum of 65 % passing a $75\ \mu\text{m}$ (No. 200) U.S. Standard Sieve. The bentonite passing the $150\ \mu\text{m}$ U.S. Standard Sieve is used for testing after drying to constant weight at $105 \pm 5^\circ\text{C}$.

1.4 The values stated in SI units are to be regarded as standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in Section 8.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D4643 Test Method for Determination of Water Content of Soil and Rock by Microwave Oven Heating

D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing

E1 Specification for ASTM Liquid-in-Glass Thermometers

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E725 Test Method for Sampling Granular Carriers and Granular Pesticides

2.2 *United States Pharmacopeia Standard:*³

USP-NF-XVII Bentonite

3. Terminology

3.1 *Definitions:*

3.1.1 *oven-dried, adj*—the condition of a material that has been heated under prescribed conditions of temperature and humidity until there is no further significant change in its mass.

4. Significance and Use

4.1 Clay mineral is a major functional component of GCL systems that reduces the hydraulic conductivity of industrial, waste, or ground water through the liner.

4.2 Clay mineral quality can vary significantly and affect the hydraulic conductivity of the GCL composite. This test method evaluates a significant property of clay mineral that relates to performance.

5. Atmosphere Conditions

5.1 *Atmospheric Conditions*—The atmospheric conditions of the laboratory performing swell index of clay mineral

¹ This test method is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.04 on Geosynthetic Clay Liners.

Current edition approved Jan. 1, 2025. Published January 2025. Originally approved in 1995. Last previous edition approved in 2019 as D5890 – 19. DOI: 10.1520/D5890-25.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at www.astm.org/contact. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from U.S. Pharmacopeia (USP), 12601 Twinbrook Pkwy., Rockville, MD 20852.

component of geosynthetic clay liners shall be: relative humidity between 50 to 70 % and a temperature of $21 \pm 2^\circ\text{C}$ ($70 \pm 4^\circ\text{F}$).

6. Apparatus

6.1 *Mortar and Pestle or Laboratory Hammer Mill*, for grinding clay mineral to required particle sizing.

6.2 *U.S. Standard Sieve*, 150 μm (No. 100), 75 μm (No. 200).

6.3 *Drying Oven*, thermostatically controlled, preferably forced-draft type, meeting requirements of Specification **E145**, and capable of maintaining a uniform temperature of $105 \pm 5^\circ\text{C}$ throughout the drying chamber.

6.4 *Desiccator*, of suitable size, containing indicator silica gel. It is preferable to use desiccant which changes color to indicate when it needs reconstitution.

6.5 *Laboratory Balance*, 100 g capacity, ± 0.01 g accuracy and precision.

6.6 *Weighing Paper*, or small weighing dish.

6.7 *Glass Cylinder*, graduated TC (to contain), Class A volumetrically calibrated, with 1 mL subdivisions and ground glass stopper, high form with approximately 180 mm height from inside base to 100 mL mark.

6.8 *Wash Bottle*, for dispensing reagent water.

6.9 *Spatula*, flat-blade, to dispense clay mineral powder into cylinder; vibrating spatula should not be used, since the delivery quantity may not be adequately controlled.

6.10 *Mechanical Ten-Minute Timer*.

6.11 *ASTM Calibration Immersion Thermometer*, (Specification **E1**).

6.12 *Microwave Oven*—A microwave oven, preferably with a vented chamber, is suitable. The required size and power rating of the oven is dependent on its intended use. Ovens with variable power controls and input power ratings of about 700 W have been found to be adequate for this use. Variable power controls are important and reduce the potential for overheating the test specimen.

NOTE 1—Microwave ovens equipped with built-in scales and computer controls have been developed for use in drying soils. Their use is compatible with this test method.

6.13 *Balances*—All balances must meet the requirements of Guide **D4753** and this section. A Class GP1 balance of 0.01 g readability is required for samples having a mass of up to 200 g (excluding mass of sample container).

6.14 *Sample Containers*—Suitable containers made of material resistant to corrosion and change in mass upon repeated heating, cooling, exposure to materials of varying pH, and cleaning. Microwave sample containers should be microwave safe.

6.15 *Container Handling Apparatus*—Gloves, tongs, or suitable holder for moving and handling hot containers after drying.

7. Reagents

7.1 *Purity of Reagents*—Unless otherwise indicated, references to water shall be understood to mean reagent water with an electric conductivity of $\leq 1.0 \mu\text{S}/\text{cm}$. Such water is best prepared by distillation or the passage of tap water through an ion exchange resin.

8. Hazards

8.1 Handle hot containers with a container holder.

8.2 Safety precautions supplied by the manufacturer of the microwave/oven should be observed.

8.3 Do not use metallic containers in a microwave oven (if used).

9. Samples, Specimens, and Test Units

9.1 For testing from a large bulk (for example, >1 t) before the GCL production, carry out sampling in accordance with Test Method **E725**.

10. Procedure

10.1 Grind the clay mineral sample to 100 % passing a 150 μm (No. 100) U.S. Standard Sieve and a minimum of 65 % passing a 75 μm (No. 200) U.S. Standard Sieve with a mortar and pestle or laboratory hammer mill, as required. The total mass of the test specimen shall be a minimum of 100 g.

10.2 The container to be used for drying should be oven dried thoroughly and subsequently placed into a desiccator until ready for use so that the tare weight of the container will be recorded.

10.3 Determine and record the tare of the specimen container.

10.4 Place the test specimen in the individual container. Determine the mass of the container and clay specimen as delivered, using a balance selected on the basis of the sample mass. Record the value of the clay specimen.

NOTE 2—To prevent mixing of samples and yielding of incorrect results, all containers should be numbered and the container numbers shall be recorded on the laboratory data sheets.

10.5 Place the container with the clay specimen in the drying oven. Dry the clay specimen to a constant mass. Maintain the drying oven at $105 \pm 5^\circ\text{C}$. The time required to obtain constant mass will vary depending on the type of material, oven type and capacity, and other factors.

NOTE 3—In most cases, drying a test sample overnight (about 12 to 16 h) is sufficient for conventional ovens. In cases where there is doubt concerning the adequacy of drying, drying should be continued until the change in mass after two successive periods (greater than 1 h) of drying is less than 0.1 %. In this case, it should be verified that excessive drying does not influence the swelling performance of the clay. This can be done by comparing the swelling values after the first drying period (about 12 to 16 h) and the swelling values of bentonite being dried for a longer time period.

NOTE 4—If a microwave oven is used to dry the test specimen(s), the user of this test method should follow the drying procedures as stated in Test Method **D4643**. It is further recommended to run a comparison test between the microwave oven and the drying oven to demonstrate that the microwave oven gives similar values as the drying oven and that excessive drying does not change the swelling performance of the clay.

NOTE 5—Since some dry materials may absorb moisture from moist