



Designation: D6546 – 23

Standard Test Methods for and Suggested Limits for Determining Compatibility of Elastomer Seals for Industrial Hydraulic Fluid Applications¹

This standard is issued under the fixed designation D6546; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 These test methods cover the procedure for measuring physical properties of elastomer seals in the form of O-rings after exposure to industrial hydraulic fluids and thermal aging. The measured properties are then compared to the physical properties of elastomer seals that have not been exposed to the industrial hydraulic fluids and thermal aging. The changes in these properties form a basis for assessing compatibility when these changes are compared against the suggested limits in [Table 1](#).

1.2 While these test methods involve the use of O-rings, they can also be used to evaluate the compatibility of the elastomeric compounds of specialty seals with industrial hydraulic fluids and their resistance to thermal aging. The compounds can be molded into O-rings for evaluation purposes.

1.3 These test methods provide procedures for exposing O-ring test specimens to industrial hydraulic fluids under definite conditions of temperature and time. The resulting deterioration of the O-ring material is determined by comparing the changes in work function, hardness, physical properties, compression set, and seal volume after immersion in the test fluid to the pre-immersion values.

1.4 The values stated in SI units are to be regarded as the standard.

1.4.1 *Exception*—The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

[D395 Test Methods for Rubber Property—Compression Set](#)

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

[D471 Test Method for Rubber Property—Effect of Liquids](#)

[D1414 Test Methods for Rubber O-Rings](#)

[D2000 Classification System for Rubber Products in Automotive Applications](#)

[D2240 Test Method for Rubber Property—Durometer Hardness](#)

[D3677 Test Methods for Rubber—Identification by Infrared Spectrophotometry](#)

[D3767 Practice for Rubber—Measurement of Dimensions](#)

[D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants](#)

[D5028 Test Method for Curing Properties of Pultrusion Resins by Thermal Analysis](#)

[E1131 Test Method for Compositional Analysis by Thermogravimetry](#)

2.2 SAE Standard:³

[AS568A O-ring Sizes](#)

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *batch, n*—all the O-rings molded from the same lot of material and presented for inspection at one time.

3.2.2 *compound, n*—a fully formulated elastomer material containing all fillers and cross-linking agents.

¹ These test methods are under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.N0 on Hydraulic Fluids.

Current edition approved July 1, 2023. Published July 2023. Originally approved in 2000. Last previous edition approved in 2015 as D6546 – 15. DOI: 10.1520/D6546-23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Property Change Limits

Time, h	Maximum Volume Swell, %	Maximum Volume Shrinkage, %	Hardness Change, Shore A Points	Maximum Tensile Strength Change, %	Maximum Elongation Change, %	Maximum Work Function Change, %	Maximum Compression Set, %
24	15	–3	±7	–20	–20	±12	...
70	15	–3	±7	–20	–20	±12	20
100	15	–3	±8	–20	–20	±12	20
250	15	–4	±8	–20	–20	±12	25
500	20	–4	±10	–25	–25	±17	30
1000	20	–5	±10	–30	–30	±20	35

3.2.3 *fluid saturation effect, n*—the absorption of fluid by the elastomer until an equilibrium swell value is reached at a particular temperature.

3.2.4 *O-ring, n*—a rubber seal of homogeneous composition molded in one piece to the configuration of a torus with circular cross section.

3.2.4.1 *Discussion*—O-rings are used as both dynamic and static seals. The size of the O-ring is normally designated by a dash number corresponding to the size tables listed in AS568A. The dimensions for the O-rings used in these test methods are listed in [Annex A2](#).

3.2.5 *ultimate elongation, n*—the amount of stretch that the O-ring is exposed to before breaking.

3.2.6 *work function, n*—work done on a test specimen to cause 20 % deformation.

4. Significance and Use

4.1 When more than one elastomer seal material is tested, the test methods yield comparative data on which to base judgements as to expected service quality. Suggested in-service property change limits are provided. Property changes beyond these limits will indicate limited service life of the elastomer seal.

4.2 These test methods attempt to simulate service conditions through controlled aging and evaluation of property changes but may not give any direct correlations with actual part performance since actual service conditions vary widely. These test methods yield comparative data and indications of property changes of the elastomeric seal material under ideal service conditions. These test methods can be used for quality control purposes, for engineering assessments, for service evaluation, and for manufacturing control. The information from these test methods can be used to anticipate expected service quality.

5. General Test Methods

5.1 Except as otherwise specified, the test methods for rubber O-rings referred to in [5.1.1 – 5.1.6](#), which are applicable in general to vulcanized rubber, shall be complied with as required and are hereby made a part of these test methods.

5.1.1 *Tension Test*—Test Methods [D412](#) and [D1414](#).

5.1.2 *Compression Set*—Test Methods [D395](#) and [D1414](#).

5.1.3 *Fluid Aging*—Test Method [D471](#) and Test Methods [D1414](#).

5.1.4 *Hardness*—Test Method [D2240](#).

5.1.5 *Compositional Analysis*—Test Methods [D3677](#) and Test Method [E1131](#).

5.1.6 *Degree of Cure*—Test Method [D5028](#).

5.2 In case of conflict between the provisions of the ASTM test methods referenced in [5.1.1 – 5.1.6](#) and the detailed provisions of the test methods in Test Methods D6546, the latter shall take precedence.

6. Test Conditions

6.1 *Temperature*—The test temperature shall be the maximum sustained temperature anticipated in service.

6.2 *Immersion Periods*—The following immersion periods are recommended: 24 h, 72 h, 100 h, 250 h, 500 h, and 1000 h. The final immersion period will depend upon the results of the previous immersion period. If the changes in the physical properties have deteriorated beyond the suggested limits, then further testing is not required. The tolerance for any immersion period shall be ±1 % of the immersion period.

7. Test Fluids

7.1 For reliable compatibility assessments, it is desirable to use the fluid with which the elastomer will come in contact in actual service. For comparative tests, samples of fluid from the same drum or shipment shall be used.

8. Test Specimen

8.1 The test specimens shall be O-rings molded from the same compound batch from which the actual seals will be molded. The test samples should approximate the cross section of the actual seal to be used so that the fluid saturation effect is properly considered. The test samples should be either -021, -120, -214, or -320 O-rings, in accordance with AS568A. These have an approximate inside diameter of 25.4 mm (1 in.) and represent the most popular cross sections of seals used in industrial systems. The actual dimensions of each O-ring size are listed in [Annex A2](#).

8.2 Test specimens shall be wiped clean of external contaminants prior to testing by using a clean dry wipe.

9. Suggested Compatibility Test Limits

9.1 For a critical seal application, property change limits, as described in [Table 1](#), should be observed.

9.2 All values are in reference to soak time in the operational fluid at the operating temperature of the application.