



Designation: D6901 – 15 (Reapproved 2021)

Standard Specification for Artists' Colored Pencils¹

This standard is issued under the fixed designation D6901; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification establishes requirements for composition, performance, and labeling of artists' colored pencils.

1.2 This specification covers vehicles and additives. Requirements are included for identification, lightfastness, and consistency.

1.3 Colored pencil specimens are exposed to both natural daylight through window glass and simulated window glass-filtered daylight radiation to determine the lightfastness rating for each pencil.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

D4236 Practice for Labeling Art Materials for Chronic Health Hazards

D4303 Test Methods for Lightfastness of Colorants Used in Artists' Materials

E284 Terminology of Appearance

G24 Practice for Conducting Exposures to Daylight Filtered Through Glass

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.57 on Artist Paints and Related Materials.

Current edition approved Nov. 1, 2021. Published November 2021. Originally approved in 2003. Last previous edition approved in 2015 as D6901 – 15. DOI: 10.1520/D6901-15R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

G155 Practice for Operating Xenon Arc Lamp Apparatus for Exposure of Materials

3. Terminology

3.1 *Definitions*—Refer to Terminology **E284** for appearance terms used in this specification and to Terminology **G113** for terms relating to natural and artificial lightfastness tests.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bloom*, *n*—a cloudy exudation on the surface of colored pencil due to wax migration.

3.2.2 *burnish*, *v*—to firmly rub the surface of the sample following application of the colored pencil until the binder breaks down and the color is forced into the texture of the substrate to improve coverage.

3.2.3 *colored pencil*, *n*—a core of extenders, binders, pigments and additives, such as wax/oil and thickeners surrounded by a casing.

3.2.4 *color stick*, *n*—a core of extenders, binders, pigments and additives, such as wax/oil and thickeners without a casing but sometimes with a paper sleeve.

3.2.5 *substrate*, *n*—white, uncoated, neutral pH, buffered paper, or board, without optical brighteners, to which color is applied.

3.2.6 *watercolor pencil*, *n*—a colored pencil with a water-dispersible core.

3.2.7 *water-soluble color stick*, *n*—a water-dispersible color stick.

4. Significance and Use

4.1 This specification establishes quality requirements and provides a basis for common understanding among producers, distributors, and users.

4.2 It is not intended that all pencils meeting the requirements be identical nor of uniform excellence in all respects. Variations in manufacture, not covered by this specification, may cause some artists to prefer one brand over another, either of which may be acceptable under this specification.

4.3 Variation in test results can result from differences in pigment manufacture from time to time in a company, different varieties of a pigment from company to company, different combinations of pigments and other ingredients, specimen preparation, different instruments and instrumental readings, variations in the surface of the specimen, and the conditions of exposure. Allowance for these variations is made by establishing lightfastness categories, each of which covers a defined range of color loss.

4.4 Since a specific colored pencil may be unusually sensitive to some aspect of a particular method of accelerated lightfastness testing and show a change in color that would not occur in a normal home or gallery environment, two types of exposure are required.

4.5 Some variation in test results is to be expected even when the same type of exposure is repeated; therefore, after triplicate specimens are exposed in each type of exposure, any outlier is discarded and the mean of the specimens is calculated for each exposure type to determine the lightfastness category for each. If the two types of exposures place colored pencil in the same lightfastness category, it is the category for that pencil. Instead of testing a third time if the two types of exposures place the colored pencil in different lightfastness categories, producers may elect to use the poorer of the two relevant lightfastness categories.

4.6 Variations in specimen preparation and measurement may result in as much as 4 units of CIE 1976 $L^*a^*b^*$ (CIELAB) color difference ΔE^* , calculated using the equation given in Practice D2244, between the measurements of a test specimen before and after exposure; therefore, only color differences greater than 4 ΔE^* are considered color loss.

5. Labeling Requirements

5.1 *Provide on the Pencil:*

5.1.1 Company or brand name.

5.1.2 Company assigned identification number for the pencil, or company assigned color name for the pencil, or both; however, pigment names shall not be used as pencil names unless the pencil contains only that pigment, or a variant of that pigment, or that pigment and white; otherwise the word “Hue” must be added to the name.

5.1.3 Country of origin.

5.1.4 The Colour Index Names of the pigments used in the pencil if space permits.

5.1.5 *Lightfastness*—Lightfastness Category indicated by the symbols I, II, III, IV or V. Only colored pencils in Lightfastness Categories I and II conform with this Specification.

5.2 *Provide in Literature Included in Packaging Container and at Points of Purchase:*

5.2.1 Identification of the type of pencil: colored, watercolor, color stick, water-soluble color stick.

5.2.2 Name and address of manufacturer, importer or supplier.

5.2.3 The Colour Index name and Constitution Number of every pigment in each pencil.

5.3 *Toxicity*—All products and labeling must conform to the Federal Hazardous Substances Act and to ASTM Practice D4236.

5.4 *Statement of Conformance*—Provide Statement of Conformance in literature and on packaging container if all pencils in the container are Lightfastness I or II: “Conforms to ASTM Specification D6901,” or “Conforms to ASTM D6901.” This statement may be combined with other conformance statements, such as, “Conforms to the quality and health requirements of ASTM Specification D6901 and Practice D4236.”

6. Quality Assurance for Artists’ Colored Pencils

6.1 *Conditions Not Covered in This Specification that Affect Colored Pencils:*

6.1.1 *Substrate*—The effective pH of the paper used will affect the long-term color appearance of the applied color.

6.2 *Additives*—Thickeners, preservatives, surfactants, wax, oil, and humectants may be used to achieve consistency, prevent microbial deterioration, and control application results.

6.3 Pencils shall be capable of being applied in a smooth, uniform coating of color without scratch marks.

6.4 The colored lead shall not crumble or break excessively when used with pressure sufficient to apply the color smoothly.

7. Specimen Preparation and Exposure

7.1 *Materials:*

7.1.1 *Colored Pencils, Watercolor Pencils, Color Sticks or Water-soluble Color Sticks*—Materials to be tested.

7.1.2 *Substrate*—White paper or board. To avoid substrate discoloration during the testing procedures, the substrate shall be 100 % cotton, acid free, buffered, uncoated, and contain no optical brighteners.

7.2 *Preparation of Test Specimens:*

7.2.1 Prepare ten specimens of each pencil or stick to be tested. Cut the paper substrate into a size that fits the holder to be used for exposure. Draw a specimen square 28 by 28 mm (1 1/8 by 1 1/8 in.) in the center of each paper substrate. Leave enough white substrate around each specimen so that the colored portion will not be damaged by handling or instrument mounting hardware. Using constant pressure, color each specimen substrate evenly and firmly with the colored pencils, watercolor pencils, color sticks, or water-soluble color sticks. Repeat as necessary to completely cover the square drawn on the substrate. In the case of a metallic color, finish with parallel strokes in whichever direction results in an even metallic sheen. Burnish each sample to make coverage as complete and uniform as possible.

NOTE 1—It is difficult to achieve an even coating of the color with complete hiding of the substrate. If the substrate is not completely covered, measurement will vary from spot to spot. If the coating has varying thicknesses, the specimen will fade unevenly. In these cases the complete surface of the substrate in the colored area may have to be measured to get a repeatable and reproducible measurement that represents the average color of the specimen. If a 25 mm (1 in.) diameter instrument measuring port is used, the whole colored surface of the specimen is measured; if a smaller measuring port is used, additional measurements of different portions of the colored surface of the specimen