



Designation: D6913/D6913M – 17 (Reapproved 2025)

Standard Test Methods for Particle-Size Distribution (Gradation) of Soils Using Sieve Analysis¹

This standard is issued under the fixed designation D6913/D6913M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Although this test method has been used for many years, there are vast testing variations due to soil types and conditions. The test is more complicated and complex than would be expected. Multiple procedures are being presented along with new terminology. Although these procedures are not new, they will now be defined and explained. Some examples of these new terms are composite sieving, designated separating sieve and subspecimen. This test method outlines the majority of conditions and procedures but does not cover every conceivable variation or contingency. The table of contents in the Scope section is added to enable the user to easily find a specific topic or requirement. Only sections/subsections with titles are presented. Therefore, numbered subsections will not be continuous in some cases, as indicated in the Scope section.

1. Scope*

1.1 Soils consist of particles with various shapes and sizes. This test method is used to separate particles into size ranges and to determine quantitatively the mass of particles in each range. These data are combined to determine the particle-size distribution (gradation). This test method uses a square opening sieve criterion in determining the gradation of soil between the 3-in. (75-mm) and No. 200 (75- μ m) sieves.

1.2 The terms, soils and material, are used interchangeably throughout the standard.

1.3 In cases where the gradation of particles larger than 3 in. (75 mm) sieve is needed, Test Method **D5519** may be used.

1.4 In cases where the gradation of particles smaller than No. 200 (75- μ m) sieve is needed, Test Method **D7928** may be used.

1.5 Typically, if the maximum particle size is equal to or less than 4.75 mm (No. 4 sieve), then single-set sieving is applicable. Furthermore, if the maximum particle size is greater than 4.75 mm (No. 4 sieve) and equal to or less than 9.5 mm ($\frac{3}{8}$ -in sieve), then either single-set sieving or composite sieving is applicable. Finally, if the maximum particle size is equal to or greater than 19.0 mm ($\frac{3}{4}$ -in sieve), composite sieving is applicable. For special conditions see **10.3**.

¹ This test method is under the jurisdiction of ASTM Committee **D18** on Soil and Rock and is the direct responsibility of Subcommittee **D18.03** on Texture, Plasticity, and Density Characteristics of Soils.

Current edition approved Oct. 1, 2025. Published October 2025. Originally approved in 2004. Last previous edition approved in 2017 as D6913/D6913M – 17. DOI: 10.1520/D6913_D6913M-17R25.

1.6 Two test methods are provided in this standard. The methods differ in the significant digits recorded and the size of the specimen (mass) required. The method to be used may be specified by the requesting authority; otherwise Method A shall be performed.

1.6.1 *Method A*—The percentage (by mass) passing each sieve size is recorded to the nearest 1 %. This method must be used when performing composite sieving. For cases of disputes, Method A is the referee method.

1.6.2 *Method B*—The percentage (by mass) passing each sieve size is recorded to the nearest 0.1 %. This method is only applicable for single sieve-set sieving and when the maximum particle size is equal to or less than the No. 4 (4.75-mm) sieve.

1.7 This test method does not cover, in any detail, procurement of the sample. It is assumed that the sample is obtained using appropriate methods and is representative.

1.8 *Sample Processing*—Three procedures (moist, air dry, and oven dry) are provided to process the sample to obtain a specimen. The procedure selected will depend on the type of sample, the maximum particle-size in the sample, the range of particle sizes, the initial conditions of the material, the plasticity of the material, the efficiency, and the need for other testing on the sample. The procedure may be specified by the requesting authority; otherwise the guidance given in Section **10** shall be followed.

1.9 This test method typically requires two or three days to complete, depending on the type and size of the sample and soil type.

*A Summary of Changes section appears at the end of this standard

1.10 This test method is **not** applicable for the following soils:

1.10.1 Soils containing fibrous peat that will change in particle size during the drying, washing, or sieving procedure.

1.10.2 Soils containing extraneous matter, such as organic solvents, oil, asphalt, wood fragments, or similar items. Such extraneous matter can affect the washing and sieving procedures.

1.10.3 Materials that contain cementitious components, such as cement, fly ash, lime, or other stabilization admixtures.

1.11 This test method may not produce consistent test results within and between laboratories for the following soils and the precision statement does not apply to them.

1.11.1 Friable soils in which the sieving processes change the gradation of the soil. Typical examples of these soils are some residual soils, most weathered shales and some weakly cemented soils such as hardpan, caliche or coquina.

1.11.2 Soils that will not readily disperse such as glauconitic clays or some dried plastic clays.

1.11.3 To test these soils, this test method must be adapted, or altered, and these alterations documented. Depending on the design considerations, a specialized gradation-testing program could be performed. The alterations could require the washing and sieving procedures to be standardized such that each specimen would be processed in a similar manner.

1.12 Some materials that are not soils, but are made up of particles may be tested using this method. However, the applicable sections above should be used in applying this standard.

1.13 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice **D6026**, unless superseded by this test method.

1.13.1 The procedures used to specify how data are collected/recorded and calculated in this standard are regarded as the industry standard. In addition, they are representative of the significant digits that generally should be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of these test methods to consider significant digits used in analysis methods for engineering design.

1.14 **Units**—The dimensional values stated in either SI units or inch-pound units are to be regarded as standard, such as 200-mm or 8-in. diameter sieve. Except, the sieve designations are typically identified using the “alternative” system in accordance with Practice **E11**, such as 3 in. and No. 200, instead of the “standard” system of 75 mm and 75 μ m, respectively. Only the SI units are used for mass determinations, calculations, and reported results. However, the use of balances or scales recording pounds of mass (lbm) shall not be regarded as nonconformance with this standard.

1.15 A summary of the symbols used in this test method is given in **Annex A1**.

1.16 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.

1.17 **Table of Contents**—All tables and figures appear at the end of this standard.

	Section
Scope	1
Method A	1.6.1
Method B	1.6.2
Sample Processing	1.8
Units	1.14
Referenced Documents	2
ASTM Standards	2.1
Terminology	3
General	3.1
Definitions	3.2
Definitions of Terms Specific to This Standard	3.3
Summary of Test Method	4
Significance and Use	5
Apparatus	6
Sieves	6.1
Standard Sieve Set	6.1.1
Washing Sieve, No. 200 (75- μ m)	6.1.2
Designated Separating Sieve	6.1.3
Washing Sink with Spray Nozzle	6.2
Mechanical Sieve Shaker	6.3
Balances	6.4
Drying Oven	6.5
Sieving Containers	6.6
Specimen Containers	6.6.1
Collection/Transfer Device	6.6.2
Cumulative Mass Container	6.6.3
Sieve Brushes	6.7
Miscellaneous Items	6.8
Splitter or Riffle Box (optional)	6.9
Quartering Accessories (optional)	6.10
Mortar and Rubber-Covered Pestle (optional)	6.11
Low Temperature Drying Oven (optional)	6.12
Ultrasonic Water Bath (optional)	6.13
Dispersion Shaker (optional)	6.14
Reagents	7
Sodium Hexametaphosphate	7.1
Dry Addition	7.1.1.1
Solution	7.1.1.2
Preparation of Apparatus	8
Verification of Sieves	8.1
Verification Interval	8.1.1
Verification of Mechanical Sieve Shaker and	8.2
Standard Shaking Period	8.2.1
Large Mechanical Sieve Shaker	8.2.2
Verification Interval	8.2.3
Hand Sieve Shaking Procedure	9
Sampling	9
General	9.1
Sample Sources	9.2
Bulk Samples	9.2.1
Jar and Small Bag Samples	9.2.2
Intact Tube Samples	9.2.3
Samples from Prior Testing	9.2.4
Specimen	10
General	10.1
Minimum Mass Requirement	10.2
Selection of Sieving Procedure	10.3
Single Sieve-Set Sieving	10.3.1
Composite Sieving	10.3.2
Specimen Procurement	10.4
Moist Procedure	10.4.1
Air-Dried Procedure	10.4.2
Oven-Dried Procedure	10.4.3
Discussion on Segregating Soils	10.4.4
Specimen Procurement and Processing Requirements	10.5