



Designation: D7530/D7530M – 17 (Reapproved 2023)

Standard Specification for Self-Adhesive Glass Fiber Fabric Reinforced Polymer- Modified Asphalt Steep Slope Roll Roofing Surfaced with Mineral Granules¹

This standard is issued under the fixed designation D7530/D7530M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers prefabricated, self-adhesive, glass fiber fabric reinforced, polymer-modified asphalt roll roofing, with granule surfacing, designed for steep slope applications. These products use polymer modifiers in their top and bottom coatings. These products have an adhesive bottom layer which is exposed by removal of a peel-away protective release paper or film sheet.

1.2 The specified tests and property limits used to characterize the sheet materials are intended to establish minimum or maximum properties. In-place roof system design criteria such as fire resistance, field strength, impact/puncture resistance, material compatibility, uplift resistance, and others, are factors beyond the scope of this material specification. Factors regarding the suitability of specific roof constructions or application techniques are beyond this scope.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Steep Roofing Products and Assemblies.

Current edition approved May 1, 2023. Published May 2023. Originally approved in 2010. Last previous edition approved in 2017 as D7530/D7530M – 17. DOI:10.1520/D7530_D7530M-17R23.

2. Referenced Documents

2.1 *ASTM Standards:*²

D903 Test Method for Peel or Stripping Strength of Adhesive Bonds

D1079 Terminology Relating to Roofing and Waterproofing
D4977/D4977M Test Method for Granule Adhesion to Mineral-Surfaced Roofing by Abrasion

D5147/D5147M Test Methods for Sampling and Testing Modified Bituminous Sheet Material

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this specification, refer to Terminology D1079.

3.1.2 *ultimate elongation, n*—the elongation measured on the load-elongation curve at which point the load has dropped to 5 % of its maximum value, after the peak load has been reached.

4. Materials and Manufacture

4.1 In the process of manufacture, the reinforcing mat is impregnated and coated on its top and bottom sides with polymer-modified asphalt coatings. The polymer-modified asphalt coatings are permitted to be compounded with a mineral stabilizer. The coating on the bottom side shall feature self-adhesive properties.

4.2 The sheet is surfaced on the weather side with mineral granules, except for any selvage.

5. Physical Properties

5.1 The sheet shall conform to the minimum physical properties prescribed in Table 1.

5.2 The finished product shall not crack nor be so sticky as to cause tearing or other material damage upon being unrolled at any product temperature between 4 and 60 °C [40 and

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Physical Properties of Self-Adhesive Glass Fiber Fabric Reinforced Polymer-Modified Asphalt Steep Slope Roll Roofing Surfaced with Mineral Granules^{A,B}

Property	SI [inch-pound]
Thickness, min, mm [mils]	3 [120]
Peak Load at $-18 \pm 2^\circ\text{C}$ [$0 \pm 4^\circ\text{F}$], MD and XMD, min, before and after heat conditioning, kN/m [lbf/in.]	10 [57]
Elongation at $-18 \pm 2^\circ\text{C}$ [$0 \pm 4^\circ\text{F}$], MD and XMD, min, at Peak Load, before and after heat conditioning, %	1
Peak Load at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$], MD and XMD, min, before and after heat conditioning, kN/m [lbf/in.]	4.4 [25]
Elongation at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$], MD and XMD, min, at Peak Load, before and after heat conditioning, %	2
Ultimate Elongation at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$], MD and XMD, min, before and after heat conditioning, %	3
Tear strength at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$], min, N [lbf]	89 [20]
Low temperature flexibility, max, before and after heat conditioning, $^\circ\text{C}$ [$^\circ\text{F}$]	0 [32]
Adhesion to plywood, at $4 \pm 1^\circ\text{C}$ [$40 \pm 2^\circ\text{F}$], min, N/m, [lbf/ft]	30 [2]
Adhesion to plywood, at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$], min, N/m, [lbf/ft]	180 [12]
Side Lap Integrity (Head of Water Test)	Pass
Dimensional stability, max, %	0.5
Thermal stability at 70°C [158°F], max, mm [in.]	3 [0.1]
Granule loss, max, g	2.0

^A The properties in this table are “as manufactured” unless otherwise noted.

^B See [Appendix X1](#).

140 °F] or at a lower temperature if the manufacturer allows application at such lower temperature.

5.3 The release paper or film sheet shall not tear during removal.

6. Dimensions and Permissible Variations

6.1 The width and area of the finished product shall conform to the following:

6.1.1 The width of the roll shall be as agreed between the purchaser and the seller and shall not vary more than 1 %.

6.1.2 The area of the roll shall be no less than as agreed between the purchaser and the seller.

7. Workmanship, Finish, and Appearance

7.1 The reinforcement shall be coated completely in a continuous, unbroken film and shall be free of such defects as holes, tears, cracks, wrinkles or permanent deformations, blisters, ragged or untrue edges, and areas of uncoated reinforcement.

7.2 The surface of the weather side, exclusive of any selvage, shall be uniform in finish and texture.

7.3 The mineral granules shall be distributed in a uniform layer over the entire surface, excluding any selvage, and shall be embedded firmly in the polymer-modified asphalt coating. The line of demarcation between the granule-surfaced portion of the weather side and any selvage shall be straight and parallel to the edges of the sheet.

7.4 When unrolled on a smooth plane, the sheet shall be straight and true so that the lap shall completely cover the selvage width without wrinkles, buckles, or fishmouths and without allowing any asphalt to show through.

8. Sampling and Test Methods

8.1 Sample the material and determine the properties described in this specification in accordance with Test Methods [D5147/D5147M](#), unless otherwise indicated.

8.2 *Conditioning*—Unless otherwise specified, condition test specimens for at least 4 h at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$] and $50 \pm 10\%$ relative humidity prior to testing.

8.3 *Ultimate Elongation*—Sample the material and determine the ultimate elongation at $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$] in accordance with Test Methods [D5147/D5147M](#) (Section 7) and as defined in [3.1.2](#).

8.4 *Adhesion to Plywood*—This test method covers the determination of the adhesive properties of the product sheets to plywood as set forth in Test Method [D903](#), except as noted below.

8.4.1 *Conditioning*—Testing is to be performed at two temperatures, $23 \pm 2^\circ\text{C}$ [$73 \pm 4^\circ\text{F}$] and $4 \pm 1^\circ\text{C}$ [$40 \pm 2^\circ\text{F}$]. Materials used to construct test specimens, including the plywood and the roller, must be conditioned at the test temperature for at least 4 h prior to assembly. Similarly, the test assembly (specimen adhered to plywood) must be conditioned at the test temperature for at least 1 h prior to testing.

8.4.2 Specimen Preparation:

8.4.2.1 The test specimen shall consist of one piece of product sheet, 75 ± 2 by 200 ± 2 mm [3 ± 0.125 by 8 ± 0.125 in.], overlapped and bonded to an area of 9400 mm^2 [15 in.^2], 75 by 125 mm [3 by 5 in.], of the top surface of a piece of plywood, 75 by 150 mm [3 by 6 in.] so that the last inch of the plywood (a strip 25 by 75 mm [1 by 3 in.]) is exposed for subsequent gripping in the test machine, and 75 mm [3 in.] of the product is available for gripping in the test machine. The plywood shall be 6 mm [$1/4$ in.] minimum thickness, APA Grade, Exposure 1, and the product shall be adhered to the surface intended for exposure. The plywood must not be reused for testing.

8.4.2.2 Roll test specimen three times back and forth with a roller which has a mass of 12 kg [26 lb] $\pm 0.5\%$, diameter of 125 mm [5 in.] $\pm 5\%$, and width of 125 mm [5 in.] $\pm 5\%$. Roll at a rate of 2 to 3 s per back and forth cycle.

8.4.2.3 At least five specimens shall be tested for each test temperature.

8.4.2.4 The specimens shall be assembled individually. Cutting specimens to size after assembly may influence the test results.

NOTE 1—Adhesion to other potential wood deck materials and substrates may also be determined by this test method.