



Designation: D7548 – 22

Standard Test Method for Determination of Accelerated Iron Corrosion in Petroleum Products¹

This standard is issued under the fixed designation D7548; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers an accelerated laboratory and field procedure for the determination of corrosion of iron, in the presence of water, on samples such as gasoline and gasoline blended with 10 % ethanol, E10 (Specification [D4814](#)); gasoline-blend components (except butane); diesel fuel and biodiesel B5, except Grade No. 4-D (Specification [D975](#)); biodiesel B6 to B20 (Specification [D7467](#)); diesel-blend component such as light cycle-oil; No. 1 fuel oil, No. 2 fuel oil (Specification [D396](#)); aviation turbine fuel (Specification [D1655](#)).

1.2 The values stated in SI units are to be regarded as the standard.

1.2.1 *Exception*—Values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A108](#) Specification for Steel Bar, Carbon and Alloy, Cold-Finished
[D97](#) Test Method for Pour Point of Petroleum Products

¹ This test method is under the jurisdiction of ASTM Committee [D02](#) on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee [D02.14](#) on Stability, Cleanliness and Compatibility of Liquid Fuels. Current edition approved May 1, 2022. Published May 2022. Originally approved in 2009. Last previous edition approved in 2022 as D7548 – 16a (2022) ^{ϵ 1}. DOI: 10.1520/D7548-22

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D396](#) Specification for Fuel Oils

[D665](#) Test Method for Rust-Preventing Characteristics of Inhibited Mineral Oil in the Presence of Water

[D975](#) Specification for Diesel Fuel

[D1193](#) Specification for Reagent Water

[D1655](#) Specification for Aviation Turbine Fuels

[D4175](#) Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants

[D4814](#) Specification for Automotive Spark-Ignition Engine Fuel

[D7467](#) Specification for Diesel Fuel Oil, Biodiesel Blend (B6 to B20)

[G15](#) Terminology Relating to Corrosion and Corrosion Testing (Withdrawn 2010)³

2.2 *Other Standards:*

British Standard [BS970–1:070M20](#)⁴ or European Steel C22E Number 1.1151—Carbon and Carbon Manganese Steels including Free Cutting Steels

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this test method, refer to Terminology [D4175](#).

3.1.2 *corrosion*, *n*—chemical or electrochemical reaction between a material, usually a metal, and its environment that produces a deterioration of the material and its properties. **G15**

3.1.3 *rust*, *n*—corrosion product consisting primarily of hydrated iron oxide.

3.1.3.1 *Discussion*—Rust is a term properly applied only to ferrous alloys. **G15**

3.2 *Acronyms:*

3.2.1 *TP*—temperature probe.

4. Summary of Test Method

4.1 A polished iron corrosion test-rod is immersed in 50 mL of the sample being tested and heated to 37.8 °C (100 °F), at

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ *Annual Book of IP Standard Methods for Analysis and Testing of Petroleum and Related Products*, Vol 2. Available from Energy Institute, 61 New Cavendish St., London, W1G 7AR, U.K., <http://www.energyinst.org>.

*A Summary of Changes section appears at the end of this standard

which point 5 mL of reagent water, Type III or better, is added to the sample. Sample temperature is maintained between 37 °C to 39 °C (98 °F to 102 °F), with the target being 37.8 °C (100 °F), for 1 h. At the end of the heating period, test-rod is removed, rinsed, and examined for the degree/category of corrosion against the “ASTM Iron Corrosion Rating Chart—Test Method D7548.”

5. Significance and Use

5.1 In general, wherever the possibility exists of water getting mixed with products/material (covered under 1.1) the results obtained by this test method will indicate the degree to which corrosion of iron components can be expected.

5.2 Test also determines the antirust properties of products/material (covered under 1.1) in preparation for the various stages through which the tested product may pass prior to or during its transport through a pipeline.

5.3 Test results are also meant to show whether or not the dosage levels and type of iron corrosion inhibitor added to a product/material (covered under 1.1) is sufficient for achieving the desired protection of affected assets such as storage tanks, process lines, and shipment systems.

6. Apparatus

6.1 *Stirring Hotplate*,^{5,6} Single or multi-position (see Appendix X1), ceramic top, capable of accommodating Accelerated Iron Corrosion Test (AICT) apparatus specified in A1.1. Stirrer should be capable of stirring at a rate of 900 r/min ± 100 r/min.

6.2 *Water Bath*—Beaker, 150 mL to 200 mL capacity, borosilicate glass, containing 100 mL of distilled water, or other type of water bath capable of accommodating Accelerated Iron Corrosion Test (AICT) apparatus specified in A1.1.

6.3 *Test Jar*—Cylindrical, clear glass, 90 mL capacity, flat bottom, 115 mm to 125 mm (4.53 in. to 4.92 in.) in height, 33.2 mm to 34.8 mm (1.31 in. to 1.37 in.) outside diameter, 30.0 mm to 32.4 mm (1.18 in. to 1.28 in.) inside diameter, 1.6 mm (0.06 in.) maximum wall thickness.

NOTE 1—The pour point test jar specified in Test Method D97 meets this requirement. A test jar meeting requirements of 6.3 and graduated at 50 mL is more suitable.

NOTE 2—Optionally, to prevent accidental breakage of the test jar, a rubber O-ring, 32 mm (1.25 in.) inside diameter, and 3 mm (0.12 in.) thick, could be slipped over the test jar up to about 25 mm (1.0 in.) below its rim.

6.4 *Cover*,^{7,6} Test Jar—Plastic, such as high density polyethylene (HDPE), with three holes, meeting dimensions and features seen and outlined in A1.2.

6.5 *Corrosion Test Rod*,^{8,6} with a plastic or polytetrafluoroethylene (PTFE) holder and nominal dimensions according to Fig. A1.3; round, threaded steel rod, tapered at one end; 81.0 mm (3.19 in.) long, including the 12.7 mm (0.5 in.) long threaded portion, and 12.7 mm (0.5 in.) in diameter. See Fig. A1.3. Test rod should be made of steel conforming to Grade 1015, 1018, 1020, or 1025 of Specification A108, or to European Steel C22E number 1.1151, or to British Standard BS970–1 as per Table 1. If these steels are unavailable, other equivalent steels may be used, provided they are satisfactory according to comparative tests using this test method.

6.5.1 *Holder*,^{8,6} ethanol-resistant plastic or PTFE with nominal dimensions according to Fig. A1.3. Total length: 63.5 mm (2.5 in.), with a 2-step handle at top that is disc-type, 22.2 mm ± 0.1 mm (0.875 in. ± 0.004 in.) in diameter by 15.9 mm (0.625 in.) thick. Below this is a circular step or rim which is 17.1 mm (0.63 in.) diameter by 6.4 mm (0.25 in.) thick. The stem portion of the holder is 41.2 mm (1.622 in.) long by 12.7 mm (0.5 in.) in diameter, with a 6.4 mm (0.25 in.) female-threaded hole in the bottom to accept the male-threaded test rod.

6.6 *Temperature Probe*, Digital, calibrated, with stem about 200 mm (8 in.) long by 3.0 mm (0.125 in.) in diameter and covering a temperature range of about 20 °C (68 °F) to at least 60 °C (140 °F).

NOTE 3—Calibrated, digital temperature probe, or equivalent calibrated temperature measurement device, covering a range of –50 °C (–58 °F) to +300 °C (+572 °F) will be suitable. Alternatively, calibrated thermocouples may be used.

6.7 *Stirring Bar*—Magnetic, PTFE (polytetrafluoroethylene)-coated, 25.4 mm ± 2.54 mm (1.0 in. ± 0.1 in.) long by 8 mm ± 0.8 mm (0.31 in. ± 0.03 in.) in diameter.

⁵ The sole source of supply of the apparatus “Super-Nuova” Multi position stirring hot plate, Model No. SP135935Q known to the committee at this time is Thermo Fisher Scientific, 2000 Park Lane Dr., Pittsburgh, PA 15275-9952.

⁶ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁷ The sole source of supply of the test jar cover known to the committee at this time is K & C Manufacturing, 210 S. Main, Newkirk, OK 74647.

⁸ The sole source of supply of the apparatus, with complete set of test accessories, known to the committee at this time is Koehler Instruments Co., 1595 Sycamore Ave, Bohemia, NY 11716.

TABLE 1 Chemical Composition of Corrosion Test Rods

Element	Chemical Analysis—Content (%)											
	A108								C22E		BS970–1	
	1015		1018		1020		1025		1.1151 ^A		070 M20	
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max
Iron, Fe	99.13	99.57	98.81	99.26	99.08	99.53	99.03	99.48	98.365	99.43	98.36	99.24
Carbon, C	0.13	0.18	0.14	0.2	0.17	0.23	0.22	0.28	0.17	0.24	0.16	0.24
Manganese, Mn	0.3	0.6	0.6	0.9	0.3	0.6	0.3	0.6	0.4	0.7	0.5	0.9
Sulfur, S	0	0.05	0	0.05	0	0.05	0	0.05	0	0.035	0	0.05
Phosphorous, P	0	0.04	0	0.04	0	0.04	0	0.04	0	0.03	0	0.05
Silicon, Si	0		0		0		0		0	0.4	0.1	0.4
Nickel, Ni	0		0		0		0		0	0.4	0	
Chromium, Cr	0		0		0		0		0	0.4	0	

^A (Cr + Mo + Ni = 0.63_{max})